

SSP-15 TDS

Property	Test Method	Value	Unit
Total Weight	-	510	g/SM
Tensile Strength (warp/weft)	ISO 13934-1 : 2013 C.R.E.STRIP METHOD	1600 1550	N/5cm
Elongation (warp/weft)	ISO 13934-1 : 2013 C.R.E.STRIP METHOD	27 30	%
Tearing Strength (warp/weft)	ISO 13937-2 : 2000	180 200	N

※ Tearing Strength (warp/weft): THREADS PULL OUT

For more information, visit our website at
www.star-flex.com