

Technical Data Sheet

Page 1 of 2

Properties: AKEMI® Quick Sealfix is a transparent 1-component adhesive which hardens by humidity based on MS-Polymer for making elastic constructive joints, which require a high strength. The product is for many purpose applicable and is characterized by the following qualities:

- solvent-, isocyanate- and PVC free
- high green strength
- rapid strength build-up
- very good ageing resistance
- very good anti-corrosion properties
- paintable (also wet on wet) with most paint- or lacquer systems
- weather-resistant
- a good adhesion on several substrates without the use of a primer
- neutral and odourless curing
- minimale volume shrinkage
- low electric conductivity
- safe to be spot welded through before cured
- for the powder or thermo varnishing

Application Area:

- Bonding of steel, metal, aluminium, wood, laminate, cork, plastic, concrete, stone, plaster, ceramics etc. in the construction and industrial sector
- Elastic bonding and sealing e.g. in bus, caravan, train and truck construction
- Elastic bonding as well as seam sealing and joint sealing in the sector body-making, wagon building, modular building construction and vehicle superstructures
- Elastic bonding in metal, apparatus, mechanical, electrical and plastics engineering, ventilation and air-conditioning technology etc.
- For all bonding tasks which require fast strength development as well as a high mechanical strength. Also in the case of silicone sealants, if there is the danger of silicone contamination and painting must take place afterwards

Instructions for Use: AKEMI® Quick Sealfix can be applied with normal manual or compressed air guns within the temperature range +5°C to +40°C.

1. To ensure good adhesion it is essential that the surfaces to be bonded are stable, clean, dry and free of oil and grease.
2. AKEMI® Quick Sealfix must be smoothed within 8 minutes (at 20°C/50% relative atmospheric humidity).
3. When used as an adhesive, parts to be bonded must be joined together within 8 minutes (at 20°C/50% relative atmospheric humidity) after the application of AKEMI® Quick Sealfix.
4. "Wet-in-wet" overpainting must take place within max. 4 hours.
5. If overpainting should take place later, it must be cleaned with AKEMI® Cleaner A first.

Special Notes: Adhesion Promoter:
On many clean fat-free surfaces good adhesion can be obtained without using an adhesion promoter. However, if the hardened product is to be exposed to a lot of moisture or temperature stress or in the event of problematic binding surfaces, we recommend pretreatment with afin® MS Prep for non-porous and adhesion promoter afin® MS Pro for porous surfaces. Tools can be cleaned and non-hardened remnants can be removed with a clean, dry cloth. Use afin® Acryclean if the soiled area is larger.

TDS 09.21

Technical Data Sheet

Page 2 of 2

Technical Data:	Colours:	black, grey, white
	Base:	modified MS polymer (MSP)
	Hardening method:	by atmospheric humidity
	Density:	1.40 +/- 0.05 g/cm ³ (23°C/50% rel.humidity)
	Working time:	max. 8 minutes
	Hardening:	approx. 3.5 mm/24h (23°C/50% rel.humidity) approx. 4.5 mm/48h (23°C/50% rel.humidity)
	Shore A hardness:	approx. 50 (DIN 53505)
	Volume change:	7% (DIN EN ISO 10563)
	Tensile strength:	3.0 N/mm ² (DIN 53504 S2)
	Tensile strength:	30.5 kg/cm ²
	Elongation at break:	350% (DIN 53504 S2)
	Module at 100% elongation:	approx. 1.2 N/mm ² (DIN 53504 S2)
	Temperature resistance:	-40°C to +90°C; short-term 200°C
	Working temperature:	+5°C to 40°C
	Chemical resistance:	
	- good against:	water, aliphatic solvents, oils, fats, diluted inorganic acids and alkalis
	- moderately against:	ester, ketone and aromatic solvents
	- not resistant against:	concentrated acids and chlorinated hydrocarbons
	- weather resistance:	very good

Storage: If stored in cool condition (10-25°C/50-77°F) in its closed original container at least 12 months from production

Health & Safety: Read Safety Data Sheet before handling or using this product.

Important Notice: The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trails of the product, in an inconspicuous area or fabrication of a sample piece.

TDS 09.21