

UN38.3 检测报告 **UN38.3 Test Report**

Client	Dongguan chengxing electronics co.,LTD
委托方	东莞市城星电子有限公司
Add. of Client 委托方地址	5 / f, 3 liyuankeng road, daping town, tangxia town, dongguan city 东莞市塘厦镇大坪黎园坑路 3 号 5 楼
Samples Description 样品名称	Li-ion Battery 锂离子电池
Model/Type 型号规格	802030
Testing Laboratory 测试机构	Shenzhen NCT Testing Technology Co., Ltd. 深圳诺测检测技术有限公司 1 / F, No. B Building, Mianshang Younger Pioneer Park, Hangcheng Road, Gushu Xixiang Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区西乡街道固戍航城大道绵商青年创业园 B 栋第 1 层
Report No. 报告编号	NCT18046225B1-1 2008
Issued Date 发行日期	Jan. 16, 2019

Test Conclusion 测试结论:

Shown in the Conclusion of test report. 见检测报告结论页.

Tested by 主检人: Bowie Lin Hely Wang Inspected by 审核人:

Approved by 批准人:

Seal of NCT 报告单位 Date of Issue 签发日期:



Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922 报告模板编号: TRF.UN38.3 Rev.6-V2

Page 1 of 19 第 1 页共 19 页 http://www.nct-testing.cn



I、Sample Description 样品描述

Product Name 产品名称		n Battery 离子电池	Sample Model 样品型号	8020	030
Manufacturer 制造商	Dongguan che 东莞市城星电	engxing electronics c 子有限公司	o.,LTD		
Address 地址		eng road, daping tow 大坪黎园坑路 3 号 5 t		ongguan city	
Factory エ厂	Dongguan che 东莞市城星电	engxing electronics c 子有限公司	o.,LTD		
Address 地址		eng road, daping tow 大坪黎园坑路 3 号 5		ongguan city	
Trade Mark 商标	17.5	Cell Shape 电芯形状	Prismatic 棱柱形	Battery Size 电池尺寸 (L×W×T)	(32.0 X20.4 X 7.3)mm
Nominal Voltage 标称电压	3.7V	Rated Capacity 额定容量	400mAh 1.48Wh	Limited Charge Voltage 充电限制电压	4.2V
Standard Charge Current 标准充电电流	80mA	Maximum Continuous Charge Current 最大持续充电 电流	400mA	End Charge Current 结束充电电流	12mA
Cut-off Voltage 放电截止电压	3.0V	Standard Discharge Current 标准放电电流	80mA	Maximum Discharge Current 最大放电电流	400mA
Cell Number 组成电芯数量	1PCS		Cell Model 电芯型号	8020	030
Receiving Date 接收日期	Nov.	14, 2018	Completing Date 完成日期	Nov. 28	, 2018

Ⅱ、Standard 标准

UNITED NATIONS "Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria" (ST/SG/AC.10/11/Rev.6 Section 38.3)

联合国《关于危险货物运输的建议书 实验和标准手册》第六修订版第38.3节

Ⅲ、Test Item 测试项目

T.1.

Altitude simulation 高度模拟 T.5.

区External short circuit 外部短路

□Impact / 図Crush 撞击/挤压 T.2. \(\summa\) Thermal test 温度试验 T.6.

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 2 of 19 第 2 页共 19 页 Fax: 86-755-27790922

http://www.nct-testing.cn



T.3. \(\subseteq \text{Vibration 振动} \)

T.4. Shock 冲击

T.7. □Overcharge 过充电

T.8. \(\simegraphi\) Forced discharge 强制放电

IV、Test Method and Requirement 测试方法和要求

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

用相同的电芯或电池按照顺序进行试验 T.1 至 T.5。试验 T.6 至 T.8 用没有进行其他试验的电芯。试验 T7 可以使用原先在试验 T1 至 T5 中使用过的未损坏的电池进行,以便测试交替充电放电的电池。

Single cell batteries of B1#~B14# are full charged after one cycle;

Single cell batteries of B15#~B18# are full charged after fifty cycles;

Rechargeable cells of C19#~C23# are 50% charged after one cycle;

Rechargeable cells of C24#~C33# are full discharged after one cycle;

Rechargeable cells of C34#~C43# are full discharged after fifty cycle;

Test environment condition: ambient temperature: 15-25℃, ambient humidity: 40-70%

单电芯电池 B1#~B14#为一次循环满电状态:

单电芯电池 B15#~B18#为 50 次循环满电状态:

可充电电芯 C19#~C23#为一次循环后 50%充电状态:

可充电电芯 C24#~C33#为一次循环完全放电状态;

可充电电芯 C34#~C43#为50 次循环完全放电状态:

试验环境条件:环境温度: 15-25℃,环境湿度: 40-70%

In order to quantify the mass loss, the following procedure is provided:

Mass loss (%) = (M1-M2)/M1 x 100

质量损失的量化值,可用以下公式计算:

质量损失(%)=(M1-M2)/M1×100

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table below, it shall be considered as "no mass loss".

式中: M1 是试验前的质量, M2 是试验后的质量。如果质量损失不超过下表所列的数值, 应视为"无质量损失"。

Mass M of cell or battery 电芯或电池的质量	Mass loss limit 质量损失限值
M<1g	0.5%
1g≤M≤75g	0.2%
M>75g	0.1%

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table above.

渗漏系指可以看到的电解液或者其他物质从电芯或者电池中漏出,或电芯或电池中的物质损失(不包括电池外壳、搬运装置、或标签),失去的质量超过上表所列的数值。

In test T.1 to T.4, cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Fax: 86-755-27790922

Page 3 of 19 第 3 页共 19 页

http://www.nct-testing.cn



not applicable to test cells and batteries at fully discharged states.

在测试 T.1 至 T.4 中,电芯和电池须满足无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.1. Altitude simulation 高度模拟

Test method 测试方法

Test cells and batteries are stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20±5°C).

试验电芯和电池被放置在压力等于或低于 11.6 kPa 和环境温度(20±5℃)下存放至少 6 小时。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.2. Thermal test 温度试验

Test method 测试方法

Test cells and batteries are to be stored for at least six hours at a test temperature equal to $72\pm2\,^{\circ}\mathrm{C}$, followed by storage for at least six hours at a test temperature equal to $-40\pm2\,^{\circ}\mathrm{C}$. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature ($20\pm5\,^{\circ}\mathrm{C}$). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.

试验电芯和电池放置在试验温度等于72±2℃的条件下存放至少6小时,接着再在试验温度等于-40±2℃的条件下存放至少6小时。两个极端试验温度之间的最大时间间隔为30分钟。此程序重复进行,共完成10次循环,接着将所有试验电芯和电池在环境温度(20±5℃)下存放24小时。对于大型电芯和电池,暴露于极端试验温度的时间至少应为12小时。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.3. Vibration 振动

Test method 测试方法

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face.

电芯和电池紧固于振动台台面,但不得造成电芯变形,并能准确可靠地传播振动。振动应是正弦波形,对数扫描频率在 7 Hz 和 200 Hz 之间,再回到 7 Hz,跨度为 15 分钟。这一振动过程须对三个互相垂直的电芯安装方位的每一方向重复进行 12 次,总共为时 3 小时。其中一个振动方向必须与端面垂直。

The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 报告模板编号: TRF.UN38.3 Rev.6-V2

e: 400-886-8419 Fax: 86-755-27790922

Page 4 of 19 第 4 页共 19 页

http://www.nct-testing.cn



12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).

作对数式频率扫描,对电芯和总质量不超过 12 千克的电池(电芯和小型电池),和对质量超过 12 千克的电池(大型电池)有所不同。

For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz.

对电芯和小型电池:从 7 Hz 开始,保持 1 gn 的最大加速度,直到频率达到 18 Hz。然后将振幅保持在 0.8mm(总位移 1.6mm),并增加频率直到峰值加速度达到 8 gn(频率约为 50 Hz)。将峰值加速度保持在 8 gn 直到频率增加到 200 Hz。

For large batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 gn is then maintained until the frequency is increased to 200 Hz.

对大型电池:从 7 Hz 开始,保持 1 gn 的最大加速度,直到频率达到 18 Hz。然后将振幅保持在 0.8mm(总位移 1.6mm),并增加频率直到峰值加速度达到 2 gn(频率约为 25Hz)。将峰值加速度保持在 2 gn 直到频率增加到 200 Hz。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.4. Shock 冲击

Test method 测试方法

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.

试验电芯和电池用刚性支架紧固在试验装置上,支架支撑着每个试验电池的所有安装面。

Each cell shall be subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjects to a half-sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds.

每个电芯须经受峰值加速度 150 gn 和脉冲持续时间 6 ms 的半正弦波冲击。不过,大型电芯须经受峰值加速度 50 gn 和脉冲持续时间 11 ms 的半正弦波冲击。

Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations.

每个电池须经受半正弦波冲击,峰值加速度需要根据电池的重量来决定。小型电池的脉冲持续时间为 6 ms,大型电池的脉冲持续时间为 11ms。下面的公式是用来计算合适的最小峰值加速度。

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 报告模板编号: TRF.UN38.3 Rev.6-V2 Fax: 86-755-27790922

Page 5 of 19 第 5 页共 19 页

http://www.nct-testing.cn

Battery	Minimum peak acceleration	Pulse duration
Small batteries	150 g _n or result of formula $Acceleration(g_n) = \sqrt{\left(\frac{100850}{mass*}\right)}$	6 ms
Large batteries	whichever is smaller 50 g _n or result of formula $Acceleration(g_n) = \sqrt{\frac{30000}{mass*}}$	11 ms
	whichever is smaller	

* Mass is expressed in kilograms.

电池	最小峰值加速度	脉冲持续时间
小型电池	150 gn 或计算结果中取最小的值加速度(gn)= $\sqrt{(\frac{100850}{mass})}$	6ms
大型电池	50 gn 或计算结果中取最小的值	11 ms

Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

每个电芯或电池须在三个互相垂直的电芯或电池安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受 18 次冲击。

Requirement 要求

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure.

电芯和电池须无渗漏、无泄气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一试验前电压的 90%。

T.5. External short circuit 外部短路

Test method 测试方法

The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of $57\pm4^{\circ}\mathrm{C}$, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at $57\pm4^{\circ}\mathrm{C}$ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm.

试验电芯或电池需要加热一段时间,以使其外壳温度均匀稳定地达到 57±4℃。加热时间的长短是由电芯或电池的尺寸和设计来决定的,这个加热时间需要评估并记录。如果这个加热时间不好评估的话,对于小电芯和小电池需要在此温度下放置至少 6 个小时,对于大电芯和大电池至少放置 12 个小时。然后使电芯或电池在 57±4℃下经受总外电阻小于 0.1Ω 的短路条件。

This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57\pm4^{\circ}$ C, or in the case of the large batteries, has decreased by half of the

Fax: 86-755-27790922

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 6 of 19 第 6 页共 19 页

http://www.nct-testing.cn



maximum temperature increase observed during the test and remains below that value.

短路测试持续到电芯或电池外壳温度回到 57±4℃后至少持续 1 小时,针对大电池,外壳温度需要下降到测试过程中监控到的最大温度的一半以下。

The short circuit and cooling down phases shall be conducted at least at ambient temperature.

短路测试和冷却阶段至少应该在环境温度下进行。

Requirement 要求

Cells and batteries meet this requirement if their external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after test.

电芯和电池外壳温度不超过 170℃,并且在试验过程中及试验后 6 小时内无解体、无破裂,无起火。

T.6. Impact / Crush 撞击/挤压

Test procedure - Impact (applicable to cylindrical cells not less than 18.0 mm in diameter)

测试步骤 - 撞击 (适用于直径大于等于 18.0 毫米以上的圆柱形电芯)

The test sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm \pm 0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg \pm 0.1 kg mass is to be dropped from a height of 61 \pm 2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

试样电芯或电芯组件放在平坦光滑表面上,一根316型不锈钢棒横放在试样中心,钢棒直径15.8毫米±0.1毫米,长度至少6厘米,或电芯最长端的尺度,取二者之长者。将一块9.1千克±0.1千克的重锤从61±2.5厘米高度跌落到钢棒和试样交叉处,使用一个几乎没有摩擦的、对落体重锤阻力最小的垂直轨道或管道加以控制。垂直轨道或管道用于引导落锤沿与水平支撑表面呈90度落下。

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm \pm 0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.

受撞击的试样,纵轴应与平坦表面平行并与横放在试样中心的直径 15.8±0.1 毫米弯曲表面的纵轴垂直。每一试样只经受一次撞击。

Test procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18.0 mm in diameter)

测试步骤-挤压(适用于棱柱形,袋状,硬币/纽扣电芯和圆柱形电芯直径小于18.0毫米)

A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

将电芯或电芯组件放在两个平面之间挤压,挤压力度逐渐加大,在第一个接触点上的速度大约为 1.5 cm/s。挤压持续进行,直到出现以下三种情况之一:

- (a) The applied force reaches 13 kN ± 0.78 kN;
- (b) The voltage of the cell drops by at least 100 mV;
- (c) The cell is deformed by 50% or more of its original thickness.
- (a)施加的力达到 13 kN ± 0.78 kN;
- (b)电芯的电压下降至少 100mV:
- (c)电芯形变达到原始厚度的50%或更多。

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

一旦达到最大压力、电压下降 100mV 或更多,或电芯形变至少达到原始厚度的 50%,即可解除压力。

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 7 of 19 第 7 页共 19 页

http://www.nct-testing.cn



applied perpendicular to the longitudinal axis.

棱柱形或袋装电芯须从最宽的面施压。纽扣/硬币形电芯应从其平坦表面施压。圆柱形电芯应从与纵轴垂直的方向施压。

Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.

每个试样电芯或电芯组件只做一次挤压试验。试样须继续观察6小时。试验须使用之前未做过其他试验的试样电芯或电芯组件进行。

Requirement 要求

Cell and component cells meet this requirement if their external temperature does not exceed 170 $^{\circ}$ C and there is no disassembly and no fire during the test and within six hours after test.

电芯和电芯组件外壳温度不超过170℃,并且在试验过程中及试验后6小时内无解体,无起火。

T.7. Overcharge 过充电

Test method 测试方法

The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

充电电流为制造商推荐的最大持续充电电流的两倍。试验的最小电压如下:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.
- (a) 制造商推荐的充电电压不大于 18 伏时, 试验的最小电压应是电池最大充电电压的两倍或 22 伏两者中的较小者。
- (b) 制造商推荐的充电电压大于 18 伏时,试验的最小电压应是电池最大充电电压的 1.2 倍。 Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours. 试验应在环境温度下进行。进行试验的时间应为 24 小时。

Requirement 要求

Rechargeable batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

充电电池应在试验过程中和试验后7天内无解体,无起火。

T.8. Forced discharge 强制放电

Test method 测试方法

Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer.

每个电芯在环境温度下与 12V 直流电电源串联在起始电流等于制造商给定的最大放电电流的条件下强制放电。

The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell is forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

试样电芯与一个适当大小的电阻负载串联以调节到规定大小的放电电流。每个电芯的放电时间(单位为 h)等于电芯的额定容量除以试验初始放电电流(单位 A)。

Requirement 要求

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 报告模板编号: TRF.UN38.3 Rev.6-V2

Fax: 86-755-27790922

Page 8 of 19 第 8 页共 19 页


http://www.nct-testing.cn



Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

原电芯或充电电芯应在试验过程中和试验后7天内无解体,无起火。

V、Test Procedure 测试流程



Fax: 86-755-27790922

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 9 of 19 第 9 页共 19 页

http://www.nct-testing.cn





VI、Main Test Apparatus 主要测试仪器

Serial No. 设备编号	Name of Equipment 设备名称	Model 型号	Calibration Date /Due Date 校准日期/到期日
NCT-030	Charge and discharge testing system	R2D6-5V-5A	2018. 02. 03
	充放电测试系统		2019. 02. 02
NCT-012	Low-pressure high-altitude simulation test chamber	GX-3020-Z	2018. 02. 03
	低压高空模拟试验箱		
NCT-017	Constant temperature and humidity test chamber 恒温恒湿试验箱	GX-3000-150LT	2018. 02. 03
	Vibration test instrument	19 1004	2018. 02. 03
NCT-021	振动测试仪器	ES-3-150	2019. 02. 02
	Shock test instrument	SY10-2	2018. 08. 04
NCT-022	冲击测试仪器	2019. 08. 03	
	Battery short circuit test		2018. 02. 03
NCT-018	instrument 电池短路测试仪器	BE-1000W	2019. 02. 02
NCT-019	Impact test instrument	BE-5066	2018. 02. 03
1101-015	撞击测试仪器	DE-0000	2019. 02. 02
NCT-020	Crush test instrument	BE-6045T	2018. 02. 03
1101-020	挤压测试仪器	008	2019. 02. 02
NCT-033	DC regulated power supply	PS1540	2018. 02. 03
1101-000	直流稳压电源	7 0 10 40	2019. 02. 02
NCT-016	Battery anti-explosion chamber	GX-FB-200	-
NC1-016	电池防爆箱	GA-FB-200	-
NOTOCO	Electronic Scale	10.0000	2018. 02. 03
NCT-003	电子秤	JC-223S	2019. 02. 02
NCT-053	Electronic Scale	JA-4100	2018. 08. 04
NO 1-003	电子秤	JA-4100	2019. 08. 03
NCT-052	Digital Multimeter	289C	2018. 02. 03
NO 1-002	数字万用表	2090	2019. 02. 02
NCT-029	Temperature recorder	34970A	2018. 02. 03
1101-029	温度记录仪	S 4 87UA	2019. 02. 02

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 10 of 19 第 10 页共 19 页

http://www.nct-testing.cn





Ⅶ、Test Data 测试数据

T.1. Altitude simulation 高度模拟

Pre-test 试	脸前 After te	est 试验后	Mass	Voltage after	
5 质量 月	Itage Mass 起压 质量 (V) (g)	Voltage 电压 (V)	loss 质量损失 (%)	test/Voltage pre-test 试验后电压/试 验前电压(%)	Status 结果
# 11.988 4.	193 11.987	4.190	0.008	99.928	Pass 合格
# 12.143 4.	194 12.142	4.190	0.008	99.905	Pass 合格
¥ 11.913 4.	190 11.911	4.187	0.017	99.928	Pass 合格
¥ 11.824 4.	191 11.823	4.187	0.008	99.905	Pass 合格
# 12.001 4.	194 11.999	4.190	0.017	99.905	Pass 合格
# 11.871 4.	193 11.869	4.190	0.017	99.928	Pass 合格
# 11.897 4.	195 11.896	4.191	0.008	99.905	Pass 合格
¥ 12.113 4.	191 12.112	4.188	0.008	99,928	Pass 合格
# 11.965 4.	190 11.963	4.186	0.017	99.905	Pass 合格
# 11.990 4.	193 11.989	4.190	0.008	99.928	Pass 合格
# 11.990 4		.193 11.989	11.989 4.190	11.989 4.190 0.008	1.193 11.989 4.190 0.008 99.928

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.1℃ After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. 测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

T.2. Thermal test 温度试验

		Pre-tes	it 试验前	After te	After test 试验后		Voltage after	
The state of cells 样品状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	loss 质量损失 (%)	test/Voltage pre-test 试验后电压/试 验前电压(%)	Status 结果
	B1#	11.987	4.190	11.984	4.181	0.025	99.785	Pass 合格
	B2#	12.142	4.190	12.136	4.178	0.049	99.714	Pass 合格
Full	B3#	11.911	4.187	11.908	4.178	0.025	99.785	Pass 合格
charged after one	B4#	11.823	4.187	11.817	4.175	0.051	99.713	Pass 合格
cycle	B5#	11.999	4.190	11.993	4.178	0.050	99.714	Pass 合格
一次循环后	B6#	11.869	4.190	11.866	4.181	0.025	99.785	Pass 合格
满电状态	B7#	11.896	4.191	11.890	4.182	0.050	99.785	Pass 合格
	B8#	12.112	4.188	12.109	4.176	0.025	99.713	Pass 合格
	B9#	11.963	4.186	11.960	4.177	0.025	99.785	Pass 合格
	B10#	11.989	4.190	11.983	4.178	0.050	99.714	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.2℃ After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. 测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922 报告模板编号: TRF.UN38.3 Rev.6-V2

Page 11 of 19 第 11 页共 19 页

http://www.nct-testing.cn



T.3. Vibration 振动

The state	Pre-tes	Pre-test 试验前		After test 试验后		Voltage after		
The state of cells 样品状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	loss 质量损失 (%)	test/Voltage pre-test 试验后电压/试 验前电压(%)	Status 结果
	B1#	11.984	4.181	11.983	4.178	0.008	99.928	Pass 合格
	B2#	12.136	4.178	12.134	4.174	0.016	99.904	Pass 合格
Full	B3#	11.908	4.178	11.907	4.175	0.008	99.928	Pass 合格
charged after one	B4#	11.817	4.175	11.815	4.171	0.017	99.904	Pass 合格
cycle	B5#	11.993	4.178	11.991	4.174	0.017	99.904	Pass 合格
一次循环后	B6#	11.866	4.181	11.865	4.178	0.008	99.928	Pass 合格
满电状态	B7#	11.890	4.182	11.888	4.178	0.017	99.904	Pass 合格
	B8#	12.109	4.176	12.108	4.173	0.008	99.928	Pass 合格
	B9#	11.960	4.177	11,959	4.173	0.008	99.904	Pass 合格
	B10#	11.983	4.178	11.981	4.175	0.017	99.928	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度:24.0℃ After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. 测试后,电池未渗漏、未泄气、未解体、未破裂和未起火。

T.4. Shock 冲击

		Pre-tes	it 试验前	After te	st 试验后	Mass	Voltage after	
The state of cells 样品状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	loss 质量损失 (%)	test/Voltage pre-test 试验后电压/试 验前电压(%)	Status 结果
	B1#	11.983	4.178	11.982	4.175	0.008	99.928	Pass 合格
	B2#	12.134	4.174	12.132	4.170	0.016	99.904	Pass 合格
Full	B3#	11.907	4.175	11.906	4.172	0.008	99.928	Pass 合格
charged after one	B4#	11.815	4.171	11.813	4.167	0.017	99.904	Pass 合格
cycle	B5#	11.991	4.174	11.989	4.170	0.017	99.904	Pass 合格
一次循环后	B6#	11.865	4.178	11.864	4.175	0.008	99.928	Pass 合格
满电状态	B7#	11.888	4.178	11.886	4.174	0.017	99.904	Pass 合格
	B8#	12.108	4.173	12.106	4.170	0.017	99.928	Pass 合格
	B9#	11.959	4.173	11.958	4.170	0.008	99.928	Pass 合格
	B10#	11.981	4.175	11.980	4.171	0.008	99.904	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.3℃ After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. 测试后, 电池未渗漏、未泄气、未解体、未破裂和未起火。

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 12 of 19 第 12 页共 19 页

http://www.nct-testing.cn





T.5. External short circuit 外部短路

The state of cells 样品状态	No. 编号	External Peak temperature(℃) 电池表面最高温度(℃)	Status 结果
	B1#	57.9	Pass 合格
	B2#	58.1	Pass 合格
	B3#	58.2	Pass 合格
Full charged after one	B4#	58.4	Pass 合格
cycle	B5#	57.8	Pass 合格
一次循环后满电状态	B6#	57.9	Pass 合格
	B7#	58.2	Pass 合格
	B8#	57.8	Pass 合格
	B9#	57.9	Pass 合格
	B10#	58.2	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.0℃ There is no disassembly, no rupture and no fire during the test and within six hours after test. 电池在测试中和测试后 6 小时内未解体、未破裂,未起火。

T.6. Crush 挤压

The state of cells 样品状态	No. 编号	External Peak temperature(℃) 电池表面最高温度(℃)	Status 结果	
5	C19#	26.2	Pass 合格	
50% charged after	C20#	25.9	Pass 合格	
one cycle -次循环后 50%充电	C21#	200 26.1	Pass 合格	
状态	C22#	25.8	Pass 合格	
	C23#	25.9	Pass 合格	

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.5℃ There is no disassembly and no fire during the test and within six hours after test. 电芯在测试中和测试后 6 小时内未解体、未起火。

T.7. Overcharge 过充电

The state of cells 样品状态	No. 编号	Status 结果
Full charged after one cycle 一次循环后满电状态	B11#	Pass 合格
	B12#	Pass 合格
	B13#	Pass 合格
	B14#	Pass 合格

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 13 of 19 第 13 页共 19 页

http://www.nct-testing.cn



	B15#	Pass 合格
Full charged after fifty cycles	B16#	Pass 合格
五十次循环后满电状态	B17#	Pass 合格
	B18#	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.4℃ There is no disassembly and no fire during the test and within seven days after the test. 电池在测试中和测试后 7 天内未解体,未起火。

T.8. Forced discharge 强制放电

The state of cells	No.	Status
样品状态	编号	结果
183	C24# C/	Pass 合格
	C25#	Pass 合格
	C26#	Pass 合格
	C27#	Pass 合格
Full discharged after one cycle	C28#	Pass 合格
一次循环完全放电状态	C29#	Pass 合格
	C30#	Pass 合格
	C31#	Pass 合格
0 16	C32#	Pass 合格
N S FOR	C33#	Pass 合格
0,	C34#	Pass 合格
	C35#	Pass 合格
	C36#	Pass 合格
	C37#	Pass 合格
ull discharged after fifty cycles	C38#	Pass 合格
五十次循环完全放电状态	C39#	Pass 合格
	C40#	Pass 合格
	C41#	Pass 合格
	C42#	Pass 合格
	C43#	Pass 合格

Notes 注释: Atmospheric pressure 大气压强:1.013×10⁵Pa, Ambient temperature 环境温度: 24.3℃ There is no disassembly and no fire during the test and within seven days after the test. 电芯在测试中和测试后 7 天内未解体,未起火。

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 14 of 19 第 14 页共 19 页

http://www.nct-testing.cn



Ⅷ、Conclusion 结论

No. 编号	Test item 测试项目	Sample number 样品数量	Test reference 测试参考	Conclusion 结论
1	Altitude simulation 高空模拟		UN Manual of Test and Criteria, part III, subsection 38.3.4.1 UN 试验和标准手册,第III部分,第 38.3.4.1 节	Pass 合格
2	Thermal test 温度试验	B1#~B10#	UN Manual of Test and Criteria, part III, subsection 38.3.4.2 UN 试验和标准手册,第III部分,第 38.3.4.2 节	Pass 合格
3	Vibration 振动		UN Manual of Test and Criteria, part III, subsection 38.3.4.3 UN 试验和标准手册,第III部分,第 38.3.4.3 节	Pass 合格
4	Shock 冲击		UN Manual of Test and Criteria, part III, subsection 38.3.4.4 UN 试验和标准手册,第III部分,第 38.3.4.4 节	Pass 合格
5	External short circuit 外部短路		UN Manual of Test and Criteria, part III, subsection 38.3.4.5 UN 试验和标准手册,第III部分,第 38.3.4.5 节	Pass 合格
6	Impact/Crush 撞击/挤压	C19#~C23#	UN Manual of Test and Criteria, part III, subsection 38.3.4.6 UN 试验和标准手册,第III部分,第 38.3.4.6 节	Pass 合格
7	Overcharge 过度充电	B11#~B18#	UN Manual of Test and Criteria, part III, subsection 38.3.4.7 UN 试验和标准手册,第III部分,第 38.3.4.7 节	Pass 合格
8	Forced discharge 强制放电	C24#~C43#	UN Manual of Test and Criteria, part III, subsection 38.3.4.8 UN 试验和标准手册,第III部分,第 38.3.4.8 节	Pass 合格

The submitted samples were complied with the stated requirements of UN manual of test and criteria, part III, subsection 38.3

经检测,提交的测试样品均符合 UN38.3 的要求,测试结论为合格。

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419 Fax: 86-755-27790922

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 15 of 19 第 15 页共 19 页

http://www.nct-testing.cn



IX、Photo of The Sample 样品图片

Model 型号: 802040




Photo 1 Front 正面




Photo 2 Rear 反面

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Fax: 86-755-27790922

Page 16 of 19 第 16 页共 19 页 http://www.nct-testing.cn






Photo 3 Internal Cell 内部电芯



Photo 4 Internal Cell 内部电芯

Fax: 86-755-27790922






Photo 5 Protection board 保护板




Photo 6 Protection board 保护板

Fax: 86-755-27790922

Report No. 报告编号: NCT18046225B1-1

Hotline: 400-886-8419

报告模板编号: TRF.UN38.3 Rev.6-V2

Page 18 of 19 第 18 页共 19 页

http://www.nct-testing.cn



注意事项

Important Notice

- 1. The test report is invalid without the official stamp of NCT. 本报告书无 NCT 盖章无效.
- Nobody is allowed to photocopy or partly photocopy this test report without written permission of NCT.

未经 NCT 书面同意,不得复制或部分地复制本报告书。

- 3. The test report is invalid without the signatures of Ratifier, Reviewer and Testing engineer. 本报告书无批准人、审核人、及主检人签名无效。
- 4. The report is invalid when anything of following happens illegal transfer, reproduce, embezzlement, imposture, modification or tampering in any media form.
 私自转让、复制、盗用、冒用、涂改、或以任何媒体形式篡改的报告书无效。
- 5. Objections to the test report must be submitted to NCT within 15 days. 对报告书若有异议,应于收到报告之日起 15 天内向本公司提出。
- 6. The test report is valid for the tested samples only. 本报告仅对测试样品有效。
- 7. The Chinese contents in this report are only for reference. 本报告中的中文内容仅供参考。

******End of Report 报告结束*****

Shenzhen NCT Testing Technology Co., Ltd. 深圳诺测检测技术有限公司

1 / F, No. B Building, Mianshang Younger Pioneer Park, Hangcheng Road, Gushu Xixiang Street, Baoan District, Shenzhen, Guangdong, China.

中国广东省深圳市宝安区西乡街道固戍航城大道绵商青年创业园 B 栋第 1 层

Search Number 查询编号: NCT18046225B1-1 Search System 查询系统: http://www.nct-testing.cn