

DurMark™ Chemical Resistance to Solvents

Stain Resistance

Stain	Results
Household Ammonia	No Change
Citric Acid (10%)	No Change
Coffee	No Change
Tea	No Change
Mustard	No Change
Olive Oil	No Change
Naptha	No Change
100 Proof Alcohol	No Change
Sodium Hydroxide (10%)	No Change
Wesson Oil	No Change
Beet Juice	No Change
Grape Juice	No Change
Butter	No Change
Hydrogen Peroxide (10%)	No Change
Wax Crayon	Slight Change
Hydrochloric Acid (10%)	Slight Change
Amyl Acetate	Definite Change
Methyl Alcohol	Definite Change

Tests run in accordance with NEMA Test LD-1-2.05

Immersion

Solvent	Results
Ethyl Alcohol (10%)	Swollen
Iso-Octane	No Change
Gasoline	No Change
JP-4 Jet Fuel	No Change
Motor Oil (SAE-30, ASTM #3)	No Change
Ethyl Acetate	Dissolved
Toluene	Dissolved
Sulfuric Acid (30%)	No Change
Nitric Acid (10%)	No Change

Tests run in accordance with ASTM D-543, 7 days immersion at 75°F

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ROWMARK expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein should be construed as an inducement to infringe any patent, and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.