

Sponsor: Amir Tafreshi Breathh, Inc. 9830 Siempre Viva Rd. Suite 15 San Diego, CA 92154

## Latex Particle Challenge Final Report

Test Article: M93i-BRL3246 Study Number: 1470053-S01 Study Received Date: 22 Nov 2021 Test Started Date: 21 Dec 2021 Test Finished Date: 22 Dec 2021

> Testing Facility: Nelson Laboratories, LLC

6280 S. Redwood Rd.

Salt Lake City, UT 84123 U.S.A.

Test Procedure(s): Standard Test Protocol (STP) Number: STP0005 Rev 08

Deviation(s): None

Summary: This procedure was performed to evaluate the non-viable particle filtration efficiency (PFE) of the test article. Monodispersed polystyrene latex spheres (PSL) were nebulized (atomized), dried, and passed through the test article. The particles that passed through the test article were enumerated using a laser particle counter.

A one-minute count was performed, with the test article in the system. A one-minute control count was performed, without a test article in the system, before and after each test article. Control counts were performed to determine the average number of particles delivered to the test article. The filtration efficiency was calculated using the number of particles penetrating the test article compared to the average of the control values. During testing and controls, the air flow rate is maintained at 1 cubic foot per minute (CFM) ± 5%.

The procedure employed the basic particle filtration method described in ASTM F2299, with some exceptions; notably the procedure incorporated a non-neutralized challenge. In real use, particles carry a charge, thus this challenge represents a more natural state. The non-neutralized aerosol is also specified in the FDA guidance document on surgical face masks. All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

> Test Side: Inside 91.5 cm<sup>2</sup> Area Tested: Particle Size: 0.1 µm

Laboratory Conditions: 22.1°C, 21% relative humidity (RH) at 1016; 21.7°C, 22% RH at

1124

Average Filtration Efficiency: 98.32%

Standard Deviation: 1.056





Curtis Gerow electronically approved

27 Dec 2021 17:14 (+00:00)

Study Completion Date and Time

Study Director

Curtis Gerow



## Results:

Test Article Number	Test Article Counts	Average Control Counts	Filtration Efficiency (%)
1	239	13,093	98.2
2	77	13,069	99.41
3	332	13,042	97.5
4	369	13,044	97.2
5	78	13,141	99.41