



C-POXY 5

5-MINUTE EPOXY ADHESIVE

DESCRIPTION

C-POXY 5 is a general purpose, structural, unfilled, fast-setting epoxy adhesive. Recommended for bonding metal, ceramics, stone, glass, concrete, wood, fiberglass and many plastics such as polyester, ABS, rigid PVC (not suitable for PTFE-PP-PE and rubbers).

PHYSICAL PROPERTIES

	PART A (RESIN)	PART B (HARDENER)
Composition	Epoxy Resin	Polymercaptan
Viscosity (25°C -cps)	14000-18000	12000-14000
Colour	Colourless / Cloudy	Colourless / Clear
Specific Gravity @ 25°C	1.19	1.12
Mixing Ratio (VOLUME)	1	1

CURING BEHAVIOUR (AT 25°C)

Pot life (Time detected using 6g total mass)	4-6 minutes
Cure Time (Functional)	25-35 minutes
Mixing Colour	Colourless / Clear
Shear Strength (ISO 4587)	11-15 N/mm ²
Hardness (Shore D)	75-80
Gap to fill	0.1-2.1 mm



C-POXY 5 5-MINUTE EPOXY ADHESIVE

CHEMICAL RESISTANCE (AFTER 24 HOURS FROM CURING)

CHEMICAL	TEMPERATURE	AFTER 100 HOURS	AFTER 500 HOURS
Motor Oil	40°C	EX	EX
Water	25°C	EX	EX
Cooling Gas	25°C	EX	EX
Gasoline	25°C	EX	EX

DIRECTIONS FOR USE

Part A and B need to be mixed thoroughly in the correct volume ratio for 1 minute before use. Gel time of the mixed product is 4–6 minutes at room temperature.

Parts requiring bonding should be assembled and kept close without any stress. Assembling is continued until full curing takes place.

Excess of the product can be cleaned with Acetone or any solvent-based cleaner compatible with the substrates to bond.

For best results, it is recommended to scratch (if possible) the surface, then gently degrease and clean the excess material off the area.

NOTE: Shear strength will increase roughly to 25–27 N/mm² if bonding parts are allowed to cure 15 minutes at room temperature 25°C (77°F) followed by 2 hours cure at 100°C (212°F) (if possible).

STORAGE

Product must be kept in a cool and dry room at 10°C to 25°C.

SHELF LIFE

Minimum two (2) years in unopened packaging at +5°C / +27°C.

SAFETY AND HANDLING

Consult Material Safety Data Sheet (MSDS) before use.

NOTE: The data contained herein is obtained in CEC Corp Laboratories and is provided for the sole purpose of informing. We do not accept responsibility for the results obtained by others whose methods are not under our control. It is the user's responsibility to determine suitability for their purpose of any product mentioned herein. CEC Corp disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose. CEC Corp specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profit.