



Technical Data Sheet

Oct. 19, 2020

INSTANT GLUE WOOD(BLACK)

Description:

Toughened low viscosity glue designed to bond surface insensitive material like **wood**, leather, rubber, plastics and metal.

Impact and shock resistance.

Physical properties:

Composition	Ethyl Cyanoacrylate
Viscosity (25°C -cps)	180-210
Gap to fill (Microns)	10-50
Temperature range (°C)	-50°C - 100°C

Fixture Time:

Steel	30-40 seconds
Aluminum	50-60 seconds
PVC/ ABS	60-70 seconds
Leather	5-15 seconds
NBR/ NEOPRENE	30-40 seconds
Ceramic	5-30 seconds
Wood (Teak)	5-30 seconds
Wood (Oak)	90-180 seconds
Wood (Balsa)	2-5 seconds
Wood (Pine)	5-20 seconds
Wood (Bay wood)	10-30 seconds
Wood (Chipboard)	30-90 seconds

Wood (Fir)	45-90 seconds
Paper	1-10 seconds

Properties of cured material (typical) for 24 hours @ 22 °C:

Tensile strength ISO 6922 1750-3625 psi

Softening range +160 °C /+170 °C

Lap shear strength ISO 4587 per table below:

Steel	2750 psi
Aluminum	2250 psi
EPDM	75 psi
Nitrile	65 psi

Directions:

Clean and degrease parts to bond.

Apply the glue to one part and fix two parts quickly.

Spread acceptable pressure to ensure the glue increase into a thin film.

Do not re-adjust until tolerable strength is accomplished.

Storage: Product must be kept in a cool and dry room at 10°C to 20°C.

Shelf life: 1 year in unopened packaging at +5°C / +27°C.

Safety and handling: Consult Material Safety Data Sheet (MSDS) before use.

Note: The data contained herein is obtained in CECCORP Laboratories and is provided for the sole purpose of informing. We do not accept responsibility for the results obtained by others whose methods are not under our control. It is the user's responsibility to determine suitability for their purpose of any product mentioned herein. CECCORP disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose. CECCORP specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profit.