

# SURFKOAT

Surface Coatings, Inc.  
Manufacturers of Industrial and Decorative Concrete Materials

## AGGRESEAL SUPREME™

UV resistant, 30% aggregate sealer (Brown, Clear, Gray)

### AGGREGATE PRODUCTS



Aggreseal Supreme is a high gloss, UV resistant solvent based acrylic exposed aggregate sealer available in clear, as well as brown and gray tinted. Aggreseal Supreme offers improved resistance to rain, the sun, freezing temperatures, stains, and other pollutants that sometimes can be hazardous to concrete. Aggreseal Supreme provides superior adhesion to properly prepared concrete. Applying Aggreseal Supreme to exposed aggregate will also help to eliminate loose pebbles and premature wear.

### Specifications / Compliances

- ASTM C-309, Type 1, Class A & B
- ASTM C-1315, Type 1, Class A
- AASHTO M-148, Type 1, Class A & B
- Dried coating is USDA accepted

### Key Features & Typical Benefits

- Can be used as a means of dustproofing most concrete surfaces.
- Provides superior sheen and ultimate resistance to the sun's UV rays.
- High solids, durable and weather resistant.
- UV resistant and high gloss finish make it an industry favorite.

### Recommended Applications

Effective on applications such as...

- Driveways
- Patios
- Sidewalks
- Use *brown tinted* on exposed pea gravel aggregate concrete only.
- Use *gray tinted* on exposed limestone gravel aggregate concrete only.

### Typical Properties & Technical Information

PROPERTY	VALUE
Solids/Active Content, Percentage by weight	30% +/- 1%
Dry Time - Tack Free	1 - 2 hours
Dry Time - Foot Traffic	4 hours - 6 hours
Dry Time - Heavy Traffic	24 hours - 48 hours
Re-Coat Time Window	4 - 24 hours
Application Temperature	50° F - 80° F
VOC (Volatile Organic Compound) Content	Less than 700 grams/Liter
Appearance - Wet	Transparent Clear, Brown, or Gray
Appearance - Dry	Clear or Tinted and High Gloss

Surface Coatings, Inc.  
134 Davis St. • Portland, TN 37148  
P: (615) 323-9461 • F: (615) 323-9816  
url: [www.surfcoat.com](http://www.surfcoat.com)



# Aggreseal Supreme

## Application Instructions

**SURFACE PREP:** Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature de-lamination and failure. May be applied when damp (not "wet") to freshly placed concrete surfaces as a cure & seal. Horizontal surfaces must be finished and show no "sheen" from bleed water.

Substrate and air temperature must be no less than 40° F and not exceed 80° F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, substrate temperature can exceed 150° F which can cause extreme bubbling issues.

**MIXING:** Stir well before using. Material may separate during long term storage.

**COVERAGE RATE:** *First Coat* : 100 - 150 ft<sup>2</sup> per gallon\*      *Optional Second Coat* : 200 - 300 ft<sup>2</sup> per gallon\*

\*Coverage rates may vary depending upon surface porosity, texture, application method and prior sealer application. Excessive build up should be avoided.

**APPLICATION:** Apply using an 1 1/4" long nap roller cover using long even uniform strokes at approximately 100-300 square feet per gallon depending on porosity and texture of substrate. A Chapin style solvent resistant sprayer is not recommended for this sealer due to high content of solids. Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4 – 6 hours between coats. **Do Not Thin!**

When using as a cure & seal, apply only one coat to meet specifications. Extreme bubbling and/or hazing may occur due to lack of permeability.

**PLEASE NOTE:** It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, do not exceed 400 sq. ft. per gallon. Applying too thin of a coating may cause inadequate film formation or performance expectations may be limited. **DO NOT USE ON BRICK.**

---

## Precautions and Limitations

- This product will not freeze during storage, however, allow temperature to rise to 50°F prior to application.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- If using indoor, use proper ventilation while applying and for hours after application to ensure fumes are removed.
- Keep away from open flames. Product is flammable and is very susceptible to ignition.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- This product performs best when applied as one or two medium-light coats, not one heavy coat.
- Please be aware that this product when cured may be slippery when wet. An anti-slip additive, such as Surf-Grip, can be added to reduce slip hazards.
- This product is not resistant to brake fluid, gasoline, and many similar products.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- Use only for exposed aggregate concrete, especially brown and gray formulas. Will leave an undesirable look on smooth concrete.
- Solvent vapors are heavier than air and may travel along the ground or may be moved by ventilation and ignited by pilot lights, other flames, sparks, heaters, smoking, electric motors, static discharge, or other ignition source locations distant from material handling point.

---

**CLEAN-UP:** Use xylene. Dispose of containers in accordance with local, state and federal regulations.

**PRODUCT REMOVAL:** Dried, cured sealer may be removed with a commercial paint stripper, such as *Nock-Off* or by using a diamond grinding method, sandblasting method or similar mechanical action.

**SHELF LIFE:** Up to one year from manufacture date in its original, unopened container stored at room temperature.

**PACKAGING:** Available in 1 gallon, 5 gallon and 55 gallon containers.

Always read all technical information, label and SDS prior to use. This information can be found online or by calling customer service at the number below.