

No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 1 of 6

CUSTOMER NAME: KINGKUS NEW MATERIAL CO., LTD.

ADDRESS: ZHITANG TOWN, CHANGSHU CITY, JIANGSU PROVINCE, CHINA

Sample Name : POLYESTER FIBER ACOUSTIC PANEL

Product specification : 2420×1220×9mm

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Test Required : To determine the flame spread index (FSI) and smoke-developed index

(SDI) of the sample's surface burning characteristics when it is subjected to the conditions of specified in ASTM E84-16 "Standard Test Method for $\frac{1}{2}$ "

Surface Burning Characteristics of Building Materials"

Date of Receipt : Mar. 08, 2018
Testing Start Date : Mar. 08, 2018
Testing End Date : Mar. 26, 2018

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

Erin Huang Authorized signatory





No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 2 of 6

I. TEST CONDUCTED

This test was conducted in accordance with ASTM E84-16 Standard Test Method for Surface Burning Characteristics of Building Materials.

II. INTRODUCTION

The method, designated as ASTM E84-16, "Standard Method of Test for Surface Burning Characteristics of Building Materials", is designed to determine the relative surface burning characteristics of materials under specific test conditions. Results are expressed in terms of flame spread index (FSI) and smoke developed index (SDI).

The purpose of this test method is to determine the relative burning behavior of the material by observing the flame spread along the specimen. Flame spread and smoke developed index are reported. However, there is not necessarily a relationship between these two measurements.

III. TEST PROCEDURE

The tunnel is preheated to 150°F, as measured by the floor-embedded thermocouple located 23.25 feet downstream of the burner ports, and allowed to cool to 105°F, as measured by the floor-embedded thermocouple located 13 feet from the burners. At this time the tunnel lid is raised and the test sample is placed along the ledges of the tunnel so as to form a continuous ceiling 24 feet long, 12 inches above the floor. The lid is then lowered into place.

Upon ignition of the gas burners, the flame spread distance is observed and recorded every 15 seconds. Flame spread distance versus time is plotted ignoring any flame front recessions. If the area under the curve (A) is less than or equal to 97.5 min·ft, FSI = 0.515·A; if greater, FSI = 4900/(195-A). Smoke developed is determined by comparing the area under the obscuration curve for the test sample to that of inorganic reinforced cement board and red oak, arbitrarily established as 0 and 100, respectively.

IV. CONDITIONING

Prior to testing, the sample was conditioned, to a constant weight at a temperature of 73.4±5°F (23±2.8°C) and at a relative humidity of 50±5%.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing / inspection report & certificate, pease contact us at telephone: (86-755) 8307

No.69, Block 1159, East Kang Qiao Read, Pudong District, Shanghai, China. 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 www.sgsgroup.com.cn 中国 - 上海 · 浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 e sgs.china@sgs.com



No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 3 of 6

V. SAMPLE DETAILS

Name	Polyester fiber acoustic panel
Color	White
Density	About 2.0 kg/m ²

Exposed face:

The front face

MOUNTING METHODS:

The specimen was self-supporting and placed directly on the inner ledges of the tunnel.

The specimen consisted of 6 pieces of 600mm wide×1220mm long×9.0mm and all sections jointed end-to-end.

TEST RESULTS

FSI	SDI
0	181

RATING:

The National Fire Protection Association Life Safety Code 101, Chapter 10, Section 10.2.3 "Interior Wall and Ceiling Finish Classification", has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, ASTM E84, UL 723 "Method of Test of Surface Burning Characteristics of Building Materials".

International Building Code, Chapter 8, Interior Finishes, Section 803 "Wall and Ceiling Finishes", was classified in accordance with ASTM E 84 or UL 723. Such interior finish materials shall be grouped in the following classes in accordance with their flame spread and smoke-developed indexes.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing / inspection report & certificate, pease contact us at telephone: (86-755) 8307

No.69, Block 1159, East Kang Qiao Read, Pudong District, Shanghai, China. 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 www.sgsgroup.com.cn 中国 - 上海 · 浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 e sgs.china@sgs.com



No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 4 of 6

The classifications are as follows:

	Class A	Class B	Class C
Flame Spread Index	0-25	26-75	76-200
Smoke-developed Index	0-450	0-450	0-450

Since the tested sample received a Flame Spread Index 0 and a Smoke Developed Index 185, it would meet the requirement of Class A interior Wall & Ceiling Finish Category.

OBSERVATIONS

Time to ignition (sec)	NA
Time to Max. FS (sec)	0
Maximum FS (feet)	0

GRAPHICAL RESULTS:

Flame Spread Chart




Figure 1 Flame Spread Chart



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Cond

No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China. 201319 t(86-21) 61196300 f(86-21) 61191853 /68183920 www.sgsgroup.com.cn 中国・上海・浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 61191853 /68183920 e sgs.china@sgs.com



No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 5 of 6

Smoke Developed Chart




Figure 2 Smoke Developed Chart

WARNING:

The use of supporting materials on the underside of the test specimen has the ability to lower the flame spread index from those which might be obtained if the specimen could be tested without such support. These test results do not necessarily relate to indices obtained by testing materials without such support.

Testing of materials that melt, drip, or delaminate to such a degree that the continuity of the flame front is destroyed, results in low flame spread indices that do not relate directly to indices obtained by testing materials that remain in place.

The test results relate only to the specimens of the product in the form in which were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and may therefore invalidate the test results. Care should be taken to ensure that any product, which is supplied or used, is fully represented by the specimens, which were tested.

The specimen was supplied by the sponsor and SGS-CSTC Lab was not involved in any selection or sampling procedure.

Note: The test was performed by SGS other internal laboratory.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alterion, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) acceptance retained for 30 days only.

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307

No.69, Block 1159, East Kang Qiao Read, Pudong District, Shanghai, China. 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 www.sgsgroup.com.cn 中国 - 上海 · 浦东康桥东路1159弄69号 邮编: 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 e sgs.china@sgs.com



No.: SHIN18082170CCM

Date: Mar. 28, 2018

Page: 6 of 6

Sample photo:



****** End of report******

