



ResinTek CRU

Chemical Resistant Polyester/Polyurethane Coating

TECHNOLOGY DESCRIPTION

ResinTek coatings represent the next generation of epoxy flooring technology. Many of these high performance coatings utilize domestically produced soy bean oil and environmentally friendly packaging.

PRODUCT DESCRIPTION

ResinTek CRU is a two-component, high solids gloss aliphatic polyurethane coating designed for industrial maintenance applications. ResinTek CRU is VOC compliant. It offers excellent wear properties and chemical resistance for high performance applications. It is suited for use as a topcoat over an epoxy system or alone over primed floor surfaces.

TYPICAL PROPERTIES AT 70°F

Abrasion Resistance, 1000 cycles/CS-17, 1000 gm (ASTM D-4060)	22 mg
Coefficient of Friction.....	0.84
VOC	1.94 lb/gal; 335 gm/L
Volume Solids	60%

The data shown above reflects typical results based on laboratory testing under controlled conditions. Variations from the data shown may result. Test methods are modified where applicable.

INSTALLATION DATA

Storage Environment	Dry area, 45–90°F
Application Temperature, ambient	45–90°F
Application Temperature, substrate	Minimum 5°F above dew point
Shelf Life	1 Year
Pot Life, @ 77°F	3 hours
Foot Traffic, @ 77°F	24 hours
Full Service, @ 77°F	72 hours

IMPORTANT INFORMATION

1. Vehicles should not be parked on coating within 48 hours of installation.
2. Not designed for exterior use or immersion applications.
3. Floors should be sloped to drain to prevent standing water or chemicals.
4. Confirm product performance in specific chemical environment prior to use.
5. Prepare substrate according to "Surface Preparation" portion of this document.
6. Do not apply to slabs on grade unless a heavy unruptured vapor barrier has been installed under the slab or where moisture or MVT is present.
7. Always use protective clothing consistent with OSHA regulations during use.
8. Refer to Safety Data Sheet for detailed safety precautions.
9. For industrial/commercial use. Installation by trained personnel only.

TECHNICAL DATA SHEET

BENEFITS

- Excellent gloss and color retention
- Non-yellowing, UV stable formula
- Resists attack by most acids, alkali, detergents, lubricating oils, solvents and chemicals
- Good abrasion resistance
- VOC compliant

RECOMMENDED USES

- Warehousing & manufacturing facilities
- Stadiums & other entertainment venues
- Educational & institutional facilities
- Aircraft hangars
- Automotive service bays
- Laboratories
- Hospitals & healthcare facilities
- Animal holding areas

GENERIC DESCRIPTION

Polyester/Aliphatic Polyurethane Coating

TYPICAL APPLICATION

Final Top Coat over ResinTek epoxy

STANDARD COLORS

Clear. Variety of color pack options available

PACKAGING

3 Gallon and 15 gallon Units

COVERAGE

320–500 ft² / gallon @ 3–5 mils WFT

SURFACE PREPARATION

Concrete: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

- *New concrete should be cured a minimum of 28 days.*
- *Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.*
- *Remove any laitance or weak surface layers.*
- *Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.*
- *Surface profile shall be CSP-3 to CSP-5 meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 60-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.*
- *Moisture vapor transmission should be 3 pounds or less per 1,000 square feet over a 24 hour time period, as confirmed through a calcium chloride test, as per ASTM E-1907. Quantitative relative humidity (RH) testing, ASTM F-2170, should confirm concrete RH results <75%.*
- *All surface irregularities, cracks, expansion joints and control joints should be properly addressed prior to application.*
- *Outgassing may occur due to the porosity of some concrete surfaces. To reduce the effect of outgassing, the primer and coating should be applied when the temperature of the concrete substrate is dropping. This usually occurs in the evening; however, the concrete substrate temperature should be measured with a surface thermometer for verification. Double priming will greatly reduce the effects of outgassing by additionally filling the pores in the concrete.*

INSTALLATION STEPS

1. ResinTek CRU is normally applied over a ResinTek Coating, such as ResinTek MVE or ResinTek HPE. ResinTek CRU is used as a finish coat over a ResinTek epoxy floor coating system. See applicable data sheets for detailed installation instructions of these products.
NOTE: For use as a topcoat for ResinTek epoxy coatings, apply within 24 hours of epoxy installation. If 24 hours has passed, sand the coating using 100 grit or smaller pads and wipe with a 50:50 mixture of water and isopropanol. Once cleaner solution has flashed, proceed with application of ResinTek CRU.
2. Premix Part A Resin with a mechanical jiffy-type mixer operated at medium speed.
3. If a Color pack is to be used, blend color pack with Part A prior to adding Part B
4. Pour Part B Hardener into Part A Resin and mix for two additional minutes at medium speed.
5. For best results pour material into roller pan and apply by dip and roll. Apply at 3 to 5 WFT using 1/4" or 1/8" nap rollers; coating may foam at a greater film thickness. To minimize lap lines in finish coat, immediately cross roll material (uniform 90° angle to initial coat). Use 18" rollers whenever possible.

© Copyright 2015 ResinTek. All rights reserved. Published technical data and instructions are subject to change without notice. Please contact ResinTek for the most current technical data and instructions.

Rev 09/15

ResinTek warrants its products to be free from defects in material and workmanship. ResinTek sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ResinTek option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ResinTek in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ResinTek of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ResinTek makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ResinTek be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ResinTek, whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ResinTek cannot guarantee that color will conform to sample, if provided.