





Binders

2K200 Binder for Topcoat Colour Preparation

Product Description
 Binder added into 2K solid colours to improve the gloss of the paint.

Technical Characteristics
 Colour: transparent Shelf life: 24 months at 25°C

Pre-treatment
 See process described in **TDS of HAMR Solid Topcoats**

	Mixing Ratio	Stir well before use. 2K Solids 100 g 2K200 15 g Note: 2K200 should NOT be mixed into 1K paint or poor-covering 2K paint. Strain before application.
	Spray Viscosity	16 to 18 seconds DIN 4 cup at 25°C
	Application	See process described in TDS of HAMR Solid Topcoats .
	Drying	See process described in TDS of HAMR Solid Topcoats .
Further Treatment		See process described in TDS of HAMR Solid Topcoats .



The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet directly from your supplier.

HAMR Coatings Pty Ltd. Australia. Tel (03 8797 5515) HAMRCOATINGS.COM ISSUE 15/10/2021 This supersedes all older data sheets.