



2K Clears

Elite HS Clear (H.S)

Product Description







Elite HS Clear is our elite grade clear, designed for restoration work and full resprays, Elite is similar to 9900, though has a harder final finish. This finish is similar to many high end European vehicles.

Technical Characteristics

Colour: transparent Shelf life: 24 months at 25°C Theoretical spreading rate: 350-400 m²/l (avg) at 1 µm

Pre-treatment

Elite High Solid Clear is suitable to be applied on top of a clean and dust-free HAMR basecoat. See TDS of basecoat for other preparation of substrate.

 Mixing Ratio  Spray Viscosity Potlife  Sprayguns  Application  Drying  IR Drying Further Treatment	<table border="0"> <tr> <td>Elite Clear</td> <td>2</td> <td>100 (vol)</td> <td>100 g</td> </tr> <tr> <td>E02 Hardener</td> <td>1</td> <td>50 (vol)</td> <td>50 g</td> </tr> <tr> <td>950 Thinner</td> <td>15-20%</td> <td>15 - 20 (vol)</td> <td>13 - 18 g</td> </tr> </table> <p>Mix well and strain before application. Note: E01/ 940 is for temperatures between 5°C - 15°C E02/ 950 is for temperatures between 15°C - 25°C E03/ 960 is for temperatures above 25°C 970 Thinner is for temperatures above 35°C or when refinishing large surfaces.</p> <p>15 to 17 seconds DIN 4 cup at 25°C 4-5 hours at 25°C</p> <table border="0"> <tr> <td>HVLP gravity-feed spray gun</td> <td>1.2 - 1.3 mm</td> <td>1.5 - 2.0 bar</td> <td>10 - 15 cm</td> </tr> <tr> <td>Compliant gravity-feed spray gun</td> <td>1.3 - 1.6 mm</td> <td>3.0 - 4.0 bar</td> <td>15 - 20 cm</td> </tr> </table> <p>Number of coats: 1 thin + 1 wet coat Flash-off: 8 - 10 mins Film thickness: 60 - 70 µm</p> <p>Drying 60°C Dust free after Bake Immediately Ready for assembly after 30 mins Ready for polish after 70 mins</p> <p>IR drying after dust free Step 1 - short wave: 5 mins at a 80 cm distance Step 2 - medium wave: 20 mins at a 80 cm distance</p> <p>Polish after specified drying times and cooling.</p>	Elite Clear	2	100 (vol)	100 g	E02 Hardener	1	50 (vol)	50 g	950 Thinner	15-20%	15 - 20 (vol)	13 - 18 g	HVLP gravity-feed spray gun	1.2 - 1.3 mm	1.5 - 2.0 bar	10 - 15 cm	Compliant gravity-feed spray gun	1.3 - 1.6 mm	3.0 - 4.0 bar	15 - 20 cm
	Elite Clear	2	100 (vol)	100 g																	
	E02 Hardener	1	50 (vol)	50 g																	
	950 Thinner	15-20%	15 - 20 (vol)	13 - 18 g																	
	HVLP gravity-feed spray gun	1.2 - 1.3 mm	1.5 - 2.0 bar	10 - 15 cm																	
	Compliant gravity-feed spray gun	1.3 - 1.6 mm	3.0 - 4.0 bar	15 - 20 cm																	

The products are suitable for professional use only. The data contained in this publication are based on our current knowledge and experience. You can obtain the latest version of technical data sheet directly from your supplier.

HAMR Coatings Pty Ltd. Australia. Tel (03 8797 5515) HAMRCOATINGS.COM ISSUE 16/06/2022 This supersedes all older data sheets.