

AB-366



18-03

FEATURES

- FDA Grade and Dairy 3A Specs
- Excellent resistance to petroleum-based hydraulic fluids
- Wide range of service temperatures
- Very good resistance to alkalis and acids
- ASTM Grade

GRADE	Industrial
FINISH	Smooth
POWDER	No
TRIMMED	Yes
COLOR	White

	GAUGE IN (MM)	WIDTH IN (MM)	SURFACE/ROLL SFT (M ²)	LENGTH/ROLL LFT (M)	WEIGHT/ROLL LBS (KG)
307-04-362	1/16 (1.59)	36 (914.4)	300 (27.87)	100 (30.48)	129 (58.5)
307-04-482	1/16 (1.59)	48 (1219.2)	400 (37.16)	100 (30.48)	171 (77.6)
307-06-362 ¹	3/32 (2.38)	36 (914.4)	225 (20.9)	75 (22.85)	147 (66.7)
307-08-362	1/8 (3.7)	36 (914.4)	150 (13.93)	50 (15.24)	129 (58.5)
307-08-482	1/8 (3.7)	48 (1219.2)	200 (18.58)	50 (15.24)	171 (77.6)
307-12-362	3/16 (4.76)	36 (914.4)	120 (11.15)	40 (12.19)	152 (68.9)
307-12-482	3/16 (4.76)	48 (1219.2)	160 (14.86)	40 (12.19)	202 (91.6)
307-16-362	1/4 (6.35)	36 (914.4)	120 (11.15)	40 (12.19)	206 (93.4)
307-16-482	1/4 (6.35)	48 (1219.2)	160 (14.86)	40 (12.19)	274 (124.3)
307-24-482	3/8 (9.52)	48 (1219.2)	120 (11.15)	30 (9.14)	309 (140.2)
307-32-482	1/2 (12.70)	48 (1219.2)	120 (11.15)	30 (9.14)	417 (189.2)

¹ Made to order



TECHNICAL SPECIFICATIONS AB-366



18-03

SPECIFICATION ASTM D2000 : 1BF610 meets FDA requirements
POLYMER : NBR/SBR (White)

ASTM	DESCRIPTION	VALUE
	SPECIFIC GRAVITY (gr/cc)	1.4
D2240	HARDNESS (Shore A)	60
D412	TENSILE (psi)	1000 min.
	ULTIMATE ELONGATION (%)	300 min.
D395B	COMPRESSION SET	22 hrs @ 100°C 50% max.
D573	HEAT AGING	70 hrs @ 100°C Changed Hardness: +/- 15 points max. Tensile: +/- 30% max. Elongation: -50% max.
D471	OIL AGING (#3)	70 hrs @ 100°C Changed Volume: 60% max.
TEMPERATURE RANGE (general guideline)		-40° to 200° F -40° to 93°C
Maximum pieces per roll : 2		
Minimum piece length : 10'		
Width tolerance: -0 / + 1"		
Length tolerance: +/- 10%		
Material is within RMA commercial gauge tolerances.		

Please ensure the product meets your application specification prior to order placement.
Specifications are subject to change without notice. The website version prevails.