

Garlock Style 9938 100% Fluoroelastomer Sheet

TYPICAL PHYSICAL PROPERTIES

Material:	100% Fluoroelastomer
Color:	Black
Hardness:, Shore "A" +/- 5:	70 +/-5
Temperature*:	-15 F (-26 C) to 400 F (204 C)
Pressure, max.*:	250 psig (17 barg)
Tensile Strength, Typical	1,000 psi.
Ultimate Elongation, min.:	180 %
Thickness Available (inches):	1/16" – 1/4"
Sheet Finish:	Satin

Note: This is a general guide and should not be the sole means of selecting or rejecting this material. Test results are in accordance with ASTM requirements.

* When approaching the maximum or minimum ratings consult Garlock Applications Engineering.