RESOLUTE®

UNLIMITED MOISTURE VAPOR BARRIER, HARD-SET, ELASTOMERIC ADHESIVE

SIGNATURE LINE®



TECHNICAL DATA SHEET

January 2022 Version 1.0

DESCRIPTION

Chasing moisture can cost valuable time and money, but with Resolute, you can stop it in its tracks. Designed with safe, single-part, moisture-cured chemistry, Resolute is a faster, more install friendly alternative to twopart epoxy systems. Resolute is engineered for heavy rolling loads and challenging environments, and its waterproof design forms an unlimited moisture vapor barrier that can also take the punishment introduced by topical liquids.

APPROVED FLOORING TYPES

RESILIENT: Linoleum, Modular (LVP, LVT, rigid core [dryback], SVT, VET, VCT, woven), Rubber (crumb, sheet, tile), Sheet (felt-backed, fiberglass, heterogeneous, homogeneous, woven), Stair Treads (rubber, vinyl) CARPET: Artificial Turf, Modular (hard-backed, soft-backed, walk-off) WOOD: Cork (flooring, cork-backed hard surface, underlayment).

APPROVED SUBSTRATES & SURFACES

- APA underlayment grade plywood and OSB
- Association grade particleboard
- · Cement backer board
- Cementitious and anhydrite screeds
- Concrete and radiant heated subfloors that do not exceed 85°F (30°C)
- Existing well-bonded non-cushion-backed vinyl, tile and sheet flooring
- Fully secured cork underlayments
- Gypsum and lightweight concrete (primed with Taylor 2025 or Enhance®)
- Terrazzo (properly prepared with all waxes and surface finishes removed)

SUBSTRATE TESTING

RH - No testing required [100%] [ASTM F2170]

pH - No testing required [5-14]

MVER - No testing required [ASTM F1869]

POROSITY - CSP 1+, must pass [ASTM F3191]

SUBSTRATE & SURFACE PREPARATION

Follow flooring manufacturer's guidelines. Substrate must be prepared per ASTM F710 standards including, but not limited to the following:

- · Concrete floors must be dry, clean, smooth and structurally sound. They shall be free of any foreign materials that might prevent adhesive bond, including dust, dirt, solvent, paint, wax, oil, grease, residual adhesive, adhesive removers, incompatible sealers, fire-retardant chemicals, fungicides, release agents, alkaline salts, excessive carbonation, laitance, mold, mildew, and curing, sealing, hardening or parting compounds.
- Fill all surface cracks, grooves, depressions, control joints and non-moving joints with moisture resistant patching and self-leveling compounds, allow to fully cure and correct high spots before applying adhesive.
- The substrate, adhesive and flooring must be acclimated in an enclosed building with the HVAC operational between 60-95°F (15-35°C), and between 30-65% relative humidity, for at least 72 hours before, during and after the installation.
- When installing over radiant heated subfloors, turn the heat off for 24 hours before, during and after installation. Failure to turn the heat off may result in shortened working time of the adhesive. When turning radiant heat back on, raise it incrementally, not to exceed a change of more than 5 degrees per hour to a maximum of 85°F (29°C).















PRECAUTIONARY NOTES:

- Concrete must be placed in strict accordance with applicable standards and specifications. Concrete must be fully cured (at least 45 days), porous (see ASTM F3191), without hydrostatic pressure, without pressurized liquid from any source, and free of surface alkaline salt crystallization.
- Flooring must be acclimated per manufacturer's guidelines.
- · When used as a concrete moisture vapor barrier, substrate must be porous per ASTM F3191.

APPLICATION INSTRUCTIONS

Resolute may only be used as a wet-set adhesive. Follow flooring manufacturer's guidelines for layout, design and any special precautions for installation.

- 1. Spread adhesive using required tools (see tool chart below). Adhesive ridges will dissipate, and Resolute does not require back-rolling under normal circumstances.
- 2. Install flooring per the instructions below dependent upon desired application method. (Do not walk, kneel, or work directly on top of flooring without the proper use of knee-boards for at least 60 minutes after flooring is installed).
 - Tile products
 - Wait 10 minutes after adhesive is spread to build surface tack and reduce movement.
 - Working time is approximately 45 minutes under acceptable temperature and humidity conditions.
 - Use a hand roller and apply normal pressure to ensure a good bond.
 - Periodically lift flooring material to verify proper transfer of adhesive
 - Sheet goods and stair treads
 - Install flooring or stair treads immediately after adhesive is spread.
 - Working time is approximately 45 minutes under acceptable temperature and humidity conditions.
 - Periodically lift flooring material to verify proper transfer of adhesive.
- 3. Roll and cross roll floor with a 75-100 lbs (34-45 kg) roller at the end of the installation to ensure proper transfer of adhesive.
 - · Wait a minimum of 1 hour, but no more than 2 hours, after the installation to roll and cross roll floor.

PRECAUTIONARY NOTES:

- Moisture protection applications must have 100% adhesive transfer.
- Use of knee-boards is required when working on top of freshly installed flooring (60+ minutes).
- · Wait 6 hours before heat welding sheet goods.
- Wait 6 hours before wet mopping, stripping/finishing the floor.
- Reseal lid when not in use to protect product.

REQUIRED TOOLS AND COVERAGE

*Trowel dimensions are width X depth X spacing. Coverage is approximate and may vary depending on porosity of substrate and the angle at which the trowel is held.

FLOORING TYPES	TOOL* (IMAGES NOT TO SCALE)		ESTIMATED COVERAGE	
MOISTURE BARRIER & SOUND CONTROL				
RESILIENT: Linoleum, Modular (rigid core [dryback], woven), Rubber (crumb, sheet, tile), Sheet (felt-backed, fiberglass, heterogeneous, homogeneous, woven), Stair Treads (rubber, vinyl) CARPET: Modular (hard-backed, soft-backed, walk-off) WOOD: Cork (flooring, cork-backed hard-surface, underlayment)	1/16" x 1/16" x 1/16" Sq Notch		75-125 ft²/gal	
RESILIENT: Modular (LVP, LVT, SVT, VCT, VET)	1/16" x 1/32" x 1/32" U Notch		180-250 ft²/gal	
CARPET: Artificial Turf	1/8" x 1/8" x 1/16" U Notch		50-65 ft²/gal	

[&]quot;It is the sole responsibility of the contractor/installer to determine the proper porosity of the subfloor, apply the correct amount of adhesive for the job conditions and ensure that all instructions, procedures and practices are strictly adhered to.



CLEANING INSTRUCTIONS

While product is still wet: Use a damp cloth and water to remove.

While product is still soft: Use a remover/stripper, denatured alcohol or mineral spirits. Always check compatibility on a piece of scrap flooring.

STORAGE

This product should be stored at temperatures between 50-90°F (15-32°C). While this product is freeze-thaw stable, it is necessary to protect it from freezing. Freeze/thaw stable to 10°F (-12°C).

CAUTION

DO NOT take internally. If swallowed, DO NOT induce vomiting. Call a physician immediately. KEEP OUT OF REACH OF CHILDREN.

WARRANTY INFORMATION

For warranty information, call Technical Services at **706-712-5823**, visit us on the web at **www.tayloradhesives.com** or e-mail us at **tech@tayloradhesives.com**. Flooring manufacturer's and Taylor's written pre-installation and installation instructions must be strictly followed or the Taylor warranty will be void.

RESOLUTE PRODUCT INFORMATION				
	Product Classification	Moisture Barrier, Wet-set flooring adhesive		
PRODUCT CHARACTERISTICS	Base Chemistry	Modified urethane (isocyanate free)		
	Curing Method	Moisture cure		
	Appearance/Color	Off white		
	Odor	Extremely low		
	Consistency	Smooth, low viscosity liquid		
	Application	Easy troweling		
	Flammability	Non-flammable		
	Freeze/Thaw	Stable to 10°F (-12°C) [5 cycles]		
	Shelf Life [Unopened Container at 70°F]	1 year		
TESTING	Moisture Control	Protects flooring against unlimited moisture (100% RH) substrate moisture vapor & topical liquids		
	RH [ASTM F2170]	No testing required (100%)		
	рН	No testing required (5-14)		
	MVER [ASTM F1869]	No testing required		
	Porosity [ASTM F3191]	Must pass (CSP 1+)		
	Open Time	0 min (Sheet goods and stair treads)		
TIME	Flash Time	10 min (Tile products)		
	Working Time	45 min		
	Cure Time	6 hrs		
	Pot Life	N/A		
	Light Traffic	3 hrs		
TRAFFIC	Heavy Traffic	4 hrs		
	Heavy Rolling Loads	8 hrs		
ACOUSTICS*	STC	66 dB		
	IIC	68 dB		
	Delta IIC	18 dB		
	Solvents	No		
	Isocyanates	No		
	VOC Wet Applied [g/L] [SCAQMD Rule #1168]	<0.1 g/L		
SUSTAINABILITY	Bio-Based Content	No		
	Post-Consumer Receycled Content	No		
	Mineral Abundant Content	Yes		
	LEED v4/4.1 Points	Contributes to low emitting materials		
	Certifications	FloorScore®, Green Label Plus®, GREENGUARD®, Material Health Certificate - Bronze		
	Transparency	mindful MATERIALS Library, Red List free (LBC version 3.1)		
	Duration (non CFI Certified)	10-Year Performance Warranty		
WARRANTY**	Duration (CFI Certified)	Lifetime Performance Warranty		
	Coverage	Bond, 100% Substrate Moisture Vapor, Topial Liquids		

^{*}IIC (delta) and STC (delta) ranges are flooring assembly specific based on third party testing and verification in a controlled environment. For any questions or further information, please contact Taylor Technical at 706-712-5823.





(□) 706.712.5823

 $[\]ensuremath{^{**}}\xspace For warranty information, view Product Warranty Certificate.$