



WATERPROOFING

APPLICATIONS

ROOFS

ELASTOCOL STICK

TECHNICAL DATA SHEET 210907SCANE

(supersedes 190729SCANE)

DESCRIPTION

ELASTOCOL STICK is a primer composed of SBS synthetic rubbers, adhesive enhancing resins and volatile solvents. It is designed to enhance the adhesion of self-adhesive membranes.

RECOMMENDED SUBSTRATES

ELASTOCOL STICK can be applied over concrete, fibre cement, metal, and wood and on porous surfaces such as "DENS GLASS GOLD" and "DENS DECK".

APPLICATION

ELASTOCOL STICK can be applied with a brush, a roll or a spray can. It must be thoroughly dry before applying the waterproofing membrane. ELASTOCOL STICK must be shaken well before use.

Application temperatures is above -10 °C (14 °F).

WARNING: Do not accelerate drying of ELASTOCOL STICK by heating it with a torch.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

COVERAGE

Substrate Type	Coverage*	
	3.78 L (1 US gal)	19 L (5 US gal)
Porous	7 to 12 m ² (80 to 133 ft ²)	38 to 63 m ² (400 to 665 ft ²)
Non-porous	15 to 37 m ² (160 to 400 ft ²)	76 to 190 m ² (800 to 2000 ft ²)

*Coverage rate is approximate and may vary due to the application technique and surface roughness.
(All values are nominal)

PROPERTIES

Specifications	ELASTOCOL STICK
Colour	Copper
Packaging	3.78 L, 19 L (1 US gal, 5 US gal) and 350 g spray can
Specific Gravity at 20 °C (68 °F)	0.79 kg/L
Solids by Weight	24 %
Viscosity, Brookfield at 25 °C (77 °F)	200 cP
Drying time	15 to 60 minutes, depending on temperature and quantity applied.

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

TDS-ELASTOCOL-STICK-Soprema-en.indd

ELASTOCOL STICK



WATERPROOFING

APPLICATIONS

ROOFS

TECHNICAL DATA SHEET 210907SCANE

(supersedes 190729SCANE)

CLEANING

Tools can be cleaned with petroleum solvents such as mineral spirits, varsol, xylene, etc.

STORAGE AND HANDLING

Shelf life: Up to 60 months in original sealed containers, in cool and ventilated area.

Store in a well ventilated area. Keep away from any source of heat, dampness, humidity, oxidizing agents or direct sunlight. Flammable before curing. Keep away from sources of ignition.

For more information, refer to the instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE: All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.