Model: CARRARA BLANCO NATURAL L 59,6X59,6(A) Codes: 100325566 Water absorption: BIa - Porcelanico (E<=0.1%)







| DIMENSIONAL FEATURES<br>UNE-EN ISO 10545-2 |             |          |  |  |  |
|--|-------------|----------|--|--|--|
| Thickness                                  | 8.5 MM      | +/-5%*   |  |  |  |
| Width                                      | 596 MM      |          |  |  |  |
| Length                                     | 596 MM      |          |  |  |  |
| Length and width deviation                 | Below 0.15% | +/-0.3%* |  |  |  |
| Side straightness deviation                | Below 0.15% | +/-0.3%* |  |  |  |
| Squareness deviation                       | Below 0.15% | +/-0.3%* |  |  |  |
| Surface flatness deviation                 | Below 0.15% | +/-0.4%* |  |  |  |
| *ISO-13006:2018 LINE-EN 14411:2016         |             |          |  |  |  |

| MECHANICAL FEATURES<br>UNE-EN ISO 10545-4-6-7-11 |                  |            |  |  |
|--|------------------|------------|--|--|
| Breaking strength                                | 2338.2 N         | >1300N*    |  |  |
| Modulus of rupture                               | 54.8 N/MM2       | >=35N/mm2* |  |  |
| Abrasion resistance                              | PEI 4 / 1500v    |            |  |  |
| Crazing resistance                               | Resists 3 cycles |            |  |  |
| *ISO-13006:2018 UNF-EN 14411:2016                |                  |            |  |  |

|   | HYGIENIC FEATURES<br>UNE-EN ISO 10545-13-14:1995   |         |
|---|--|---------|
| Chemical resistance                                   | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance<br>*ISO-13006:2018 UNE-EN 14411:2016 | Class 5. Easy cleaning with water  | 3 Min.* |

SCOPE OF USE

Technical code-1

Use on heavy traffic floors

## ANTI-SLIP VALUE UNE 41901:2017 EX, UNE 41902:2017 EX, DIN-51130 y ASTM C1028

Slip resistance (pendulum-wet)

| *ISO-13006:2018 UNE-EN 14411:2016 |               |
|-----------------------------------|---------------|
|                                   | PACKING       |
| Sales units per box               | 1.7761 M2/BOX |

CLO

S Sales units per pallet 56.8343 M2/PAL 0.3552 M2/PIECE Sales units per unit



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.