



DIAMOND PRO 60

The Mirror Sheen Finish Package

PRO 60 is a 2-stage, professional tier nanodiamond coating. Resulting in a mirror-life sheen and intense slickness, PRO 60 makes vehicle washing and protection a breeze. With proper preparation, PRO 60 will yield up to 5 years of hardened, hydrophobic protection.

The PRO 60 Package offers 5 years protection in a highly advanced single ingredient, two-layer protective coating. It is engineered to preserve the effects commonly achieved by professional paint correction while keeping your car protected from the everyday harmful elements in the environment.

This package consists of PRO 60, our 100% inorganic polysilazane basecoat that offers one of the most extreme scratch resistant coatings available, while providing a moderate level of hydrophobicity. The optional topcoat Hydro PRO, our nanodiamond hydrophobic coat formula which provides a long-lasting high performance hydrophobicity, is recommended for those which are seeking a high level of hydrophobicity.

One of the most notable features of the PRO 2K Package is the mirrored sheen finish, creating the illusion of a vehicle shrouded in flawless glass.

APPLICATION INSTRUCTIONS

APPLICATION TIPS

Hand polish/buff after application (do not use machine tool).
Apply PRO 60 BASE to headlights, rubber and metal trim elements.
Apply PRO Hydro to headlights and metal trim elements, but not to rubber/plastic trim.
If application in hot climate (over 30C/90F), lower flashing time to 1 min.
IR Curing Lamp settings:
Temperature: 50-60C / 120-140F.
Distance to Paintwork: 60-70 cm / 24-28 inches.
Time: 15 minutes for each element.

PRECAUTIONS

Apply in temperatures between 10-30C, 50-90F.
Apply in a closed, well ventilated, indoor area with air humidity not exceeding 70%.
Use fresh suede & microfiber towels for application of additional layers (do not use previously used towels).

WHAT YOU'LL NEED

- 3 Microfiber Towels
- 3 or 4 Microfiber Applicators
- Diamond Body Prep
- Protective Gloves

APPLICATION

PRO 60

Wash, polish and prepare the car body with Diamond Body Prep. Shake well for 15 seconds and then apply 15 drops on an applicator.
Apply on 1-2 elements of the car in crosshatch fashion.
Wait up to 1-3 mins and polish off excess with a microfiber towel.
Wait one hour and apply a second coat repeating the process.
Wait one hour and begin to apply a coat of PRO HYDRO.
If curing with IR lamps, do so prior to applying PRO HYDRO.

PRO HYDRO

Shake well for 15 seconds and then apply 15 drops on an applicator. Apply on 3-4 elements of the car in crosshatch fashion.
Wait up to 7-10 mins and polish off excess proceed to softly polish the treated areas with a microfiber towel.
Wait one hour and apply a second coat repeating the process.
Wait two hours.
Car is ready to drive away!