Dorus Hot Melt Adhesive KS 350/2




EVA HOTMELT ADHESIVE FOR EDGEBANDING – UNFILLED

CHARACTERISTICS

- Medium viscosity
- Universal hotmelt adhesive
- · Very clean working, produces tight joints virtually not visible
- High glue mileage
- Very good wetting
- Permits smooth surfaces even with very flexible edgebanding materials

RECOMMENDED APPLICATIONS:

PVC*, ABS*, VENEER, POLYESTER, MELAMINE, HPL*



TECHNICAL DATA:

Viscosity - (Brookfield) at 200°C	:	1
Softening Point	:	1
Heat Resistance	:	8

110,000 mPas 125°C 85°C

DIRECTIONS FOR APPLICATION:

Processing Temperature

•	Application roller	:	190-210°C
-	Malting container		100 21000

Melting container
Feed Speed

: 190-210°C : 50ft./min.

STOCK COLORS AVAILABLE: PACKAGING:

CLEAR 55 LB. SACKS

SAFETY DATA:

Serious burns can result from contact with molten hot adhesives. Hot Melt vapors can irritate respiratory organs. Adequate ventilation should be provided.

STORAGE:

Dorus Hot Melt is to be kept dry and cool and may be stored for at least 1 year.

Statements made are based on our experience and tests. However, recommendations and suggestions are made without guarantee since the conditions of use are beyond our control. Please test and establish for yourself our product's suitability for your particular purposes.

*Conditionally recommended applications: Suggest testing on specific application to determine suitability.

Dorus is the registered trademark of Dorus Klebetechnik GmbH + Co KG.

7566 Bath Road, Mississauga, Ontario L4T 1L2 350 West Armory Drive, South Holland, II, 60473 800-461-0061 or 905-673-5156 800-426-6362 or 905-673-5156

