

# Fluoroelastomer (FKM) 70 Durometer



## Colour

Black

## Finish

Smooth

## Physical Characteristics

Tensile: 1100 PSI

Elongation: 200%

Hardness: 70 SHORE "A" +/- 5

Temperature Range: -30°C to 180°C (-22°F to 356°F)

## Notes

Black Fluoroelastomer (FKM) sheet provides excellent resistance to heat, oil and chemicals. These properties make Fluoroelastomer (FKM) sheet well suited for hot grease, engine and compressor type applications. In addition this fluoroelastomer sheet is resistant to a wide range of concentrated acids. Application for Fluoroelastomer (FKM) sheet should be known and specified prior to use.

## COMMERCIAL GRADE ISO/ASTM DESIGNATION = FKM

Parts No.	Gauge x Width	Length	Wt. Per SF lbs.
VITI70-.063-48	1/16" X 48	50FT	0.56
VITI70-.125-48	1/8" X 48	50FT	1.11
VITI70-.188-48	3/16" X 48	50FT	1.67
VITI70-.25-48	1/4" X 48	50FT	2.23

# JJD

JJ DOWNS INDUSTRIAL PLASTICS INC.



416.236.1884

Toronto, ON

JJDOWNS.COM