

CHLORINATED RUBBER PAINT

TOPCOAT WITH GOOD RESISTANCE TO SALT WATER, WIDE RANGE OF CHEMICALS AND ACIDS

PERFORMANCE ADVANTAGES

- > Excellent adhesion
- > Resistance to salt water, chemicals and acids
- > Interior or exterior use

USES

For waterproofing roof cladding, tank linings, swimming pools, plant rooms and dairies.

- > Can be brush, roller (solvent resistant) or spray applied.

COLOUR RANGE

- > White, yellow, blue, black, red and green

PACK SIZE

- > 5lt, 20lt containers

SURFACE FINISH

- > Semi-gloss

SPREADING RATE

These will vary depending on substrate ,the site conditions and Longevity required.

Typically spreading rates will vary depending on the end use.

- > 8-12 sqm² /litre per coat by Brush or Roller (Solvent Resistant Roller).



Airless Spray: Thin 5% with Britannia Special solvent,

Nozzle size: 017 thou - 21 thou are recommended at 150 BAR.

- > Should be applied at 5°C or above.

Note: If USED for Waterproofing on Metal Clad Roofs then further Advice regarding the specification should be sought from the Technical Department.

DRYING TIME

Drying times

Substrate Temp 20 °C	Touch Dry 1 hour	Through Dry 4 hours
-------------------------	---------------------	------------------------

Overcoating Times

Substrate Temp 20 °C	Minimum Overnight	Maximum Indefinite
-------------------------	----------------------	-----------------------

Note: Low temperature and humidity will adversely affect application, drying and performance of any coating.

PREPARATION

- > Surfaces to be painted should be free from nibs, cavities and other imperfections.
- > Mould, oil stains, if any, must be removed.
- > Moisture content of concrete should be below 14% prior to application of any coating.
- > Concrete and render should be treated with an Acid Etch prior to painting to remove any dirt and laitance and to create a good "key" for the paint.
- > Apply a 10% thinned coat of the Britannia Chlorinated Rubber Paint to prime and seal the surface prior to applying any unthinned coats.
- > Surfaces previously painted with Britannia Chlorinated Rubber Paint that are in good condition can be scrubbed clean and the surface roughened to help adhesion of the new coating.
- > Old perished Chlorinated Rubber coatings should be removed mechanically and treated as new substrate and prepared accordingly.

APPLICATION

- > **STIR WELL BEFORE USE**
- > Please follow the Coverage rates shown in SPREADING RATE SECTION.
- > Apply between 5°C - 30°C.
- > As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during the application and drying.

CLEANING

- > Remove as much Chlorinated Rubber paint as possible from application equipment before cleaning.
- > For cleaning equipment use Britannia special solvent (not white spirit).

SHELF LIFE AND STORAGE

- > Up to one year in an unopened original container at moderate temperatures.
- > Store in a safe place in accordance with the instructions in section 7 of the relevant MSDS sheet.



PRECAUTIONS

- > **Flammable** keep away from sources of ignition.
- > Ensure good ventilation during application.
- > Wear gloves, goggles and suitable protective clothing.
- > In case of contact with eyes rinse immediately with plenty of water and seek medical advice.
- > Remove splashes from the skin with a recognised hand cleaner or plenty of soap and water.
- > Keep out of reach of children.
- > Do not use near fishponds.
- > Harmful to aquatic organisms. May cause long term adverse effects in the aquatic environments.
- > Do not empty into drains.

SAFETY

Good working practice should be followed and safety/walking boards should be utilised where required.

The specification and coverage rates are given in good faith and are based on our experience and knowledge but without liability.

As Britannia Paints Limited has no direct control over the methods employed by the user in applying its products, any warranty either written or implied is given in good faith and can only cover the material itself.

If in doubt regarding any of the above points, please contact our technical services department for advice.

A Material Safety Data Sheet is available on request.

It is the users responsibility to ensure that this data sheet is current prior to using the product.



Certificate Number 8516
ISO 9001



Unit 7/8 King Street Trading Estate, Middlewich, Cheshire CW10 9LF
T: 01606 834015 F: 01606 837006 E: sales@britanniapaints.co.uk www.britanniapaints.co.uk

Version 2 / Apr 2020