

330X



NASHUA® 330X Extreme Weather Foil Tape


APPLICATIONS

- Designed for taping joints and seams in duct work for heating, A/C, and refrigeration systems
- Specifically intended for use over a wide temperature range
- Suitable for general repairs and a variety of insulation uses

FEATURES & BENEFITS

- · High performance acrylic adhesive
- Excellent performance of a wide temperature range
- · High adhesion and quick stick
- · Extremely conformable foil backing
- · Matches most laminated duct work

CONSTRUCTION



PRODUCT DESCRIPTION

Single-Coated w/Liner Construction Backing:

1.75 mil Aluminum Foil

Adhesive:

Extreme Weather Acrylic

Liner:

Paper

Colors:

Aluminum

TEST DATA

| Test | Typical Value | Typical Value (Metric) | Test Method |
|---------------------------------|----------------|---------------------------|-------------|
| Total Thickness | 3.5 mils | 88.90 μ | ASTM D-1000 |
| Adhesion to Steel | 45 oz./in. | 4.93 N/cm | PSTC-1 |
| Adhesion to Backing | 40 oz./in. | 4.38 N/cm | PSTC-1 |
| Tensile Strength | 14 lb./in. | 24.52 N/cm | ASTM D-1000 |
| Working Temperature Range | -35°F to 260°F | -37°C to 126°C | |
| Minimum Application Temperature | -25° F | -32°C | |

The information presented herein was prepared at COVALENCE ADHESIVES, LLC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Covale knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, a case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws a regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty merchantability or of fitness for a particular purpose), or a representation for which COVALENCE ADHESIVES assumes any legal responsibility.



^{**}Recommended storage conditions: 40-60% Humidity, 60°F-80°F