

**HIGH IMPACT POLYSTYRENE MIRROR**

**WITH GOOD IMPACT RESISTENCE**

**APPLICATIONS: - DISPLAY ARTICLES, PRINTED SIGNS**

**EASY TO FORM**

PS Sign/Advertising Technical Data	Value FT230	Unit	Standard	Test Conditions
<b>Mechanical Properties</b>				
Tensile Modulus	1850	Mpa	ISO 527	1mm/min
Yield Stress	21	Mpa	ISO 527	50mm/mm
Yield Strain	-	%	ISO 527	50mm/mm
Strain at break	60	%	ISO 527	50mm/min
Flexural strength	38	Mpa	ISO 178	2mm/min
Flexural modulus	-	Mpa	ISO 178	2mm/min
Izod impact strength	10	Kj/kvm	ISO 180	23 grC
Izod impact strength	6,5	Kj/kvm	ISO 180	-30 grC
Ball indentation hardness	65	Mpa	ISO 2039	-
<b>Thermal Properties</b>				
Vicat softening temperature	99	C	ISO 306	50 N/50 grC
Temperature of deflection under load	85	C	ISO 75	0,45 Mpa
<b>Physical Properties</b>				
Density	1,04	g/cm <sup>3</sup>	ISO 1183	-
Burning behaviour UL 94	HB	UL Klass	UL94	1,6mm
<b>Other Properties</b>				
Mould shrinkage	0, 4-0,7	%	-	-
Gloss, smooth surface	-	%	-	60 degree reflection
Gloss, smooth surface	-	%	-	60 degree reflection

Delivery Programme	
Max width	1250
Tolerance, length och width	+/- 2,0 mm
Min thickness	2,0 mm
Max thickness	9.0 mm
Tolerance, thickness	+/- 0,15 mm
Embossings	Smooth
Foil	Gold, Silver, Customer demand
Colours	FT-standard, customer-demand

Product Description
High impact. Indoor applications
Applications in the area of advertising and point.

Our technical consultation, either done orally, in writing, or by tests, is made to the best of our knowledge and according to up to date technical science, but without obligation. It does not exempt you from testing our products in view of their suitability for the application in question. Processing and use of the products are beyond our control and therefore exclusively in your own responsibility.