

Australian Species Correction Table - CSIRO chart 1999

Meter Readings (Moisture Content %)	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	
Trade Common Name	Trade Reference Name																			
Fir, Douglas (DIC) *	Pseudotsuga menziesii	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24
Ash, Alpine	Eucalyptus delegatensis syn. E. gigantea	8	9	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23	24	25
Ash, Mountain	Eucalyptus regnans	8	9	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23	24	25
Ash, Silver, Queensland	Flindersia bourjotiana	8	9	10	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	24
Baltic, White	Picea abies syn. P. excelsa	8	9	10	11	12	13	14	15	16	17	18	20	21	22	23	24	25	26	27
Beech, White (Queensland)	Gmelina leichhardtii	7	8	9	10	11	12	13	14	14	15	16	17	18	19	19	20	21	22	23
Blackbutt	Eucalyptus pilularis	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25
Blackwood	Acacia melanoxylon	8	9	9	10	11	12	12	13	14	15	16	16	17	18	19	20	20	21	22
Box, Brush (NSW)	Tristania conferta	5	6	7	7	8	8	9	9	10	11	11	12	12	13	14	--	--	--	--
Cedar, Red	Toona australis syn. Cedrela toona var. aus.	8	9	10	11	12	13	14	16	17	18	19	20	21	22	23	25	26	27	27
Cedar, White	Melia azedarach var. australasica syn Melia dubia	8	9	10	11	12	13	14	15	16	17	18	18	19	20	21	22	23	24	24
Coachwood	Ceratopetalum apetalum	5	6	7	8	9	10	11	12	13	14	14	15	16	17	18	19	20	21	22
Fir, Douglas (Vic.)	Pseudotsuga menziesii	8	9	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25
Gum, Blue, Southern	Eucalyptus saligna	8	9	10	11	12	12	13	14	15	15	16	17	18	19	19	20	21	22	23
Gum, Manna	Eucalyptus Viminalis	6	7	7	8	9	10	11	12	13	14	14	15	16	17	18	19	20	21	21
Gum, Red, Forest	Eucalyptus tereticornis	9	10	11	12	12	13	14	15	16	17	18	18	19	20	21	22	23	24	24
Gum, Red, River	Eucalyptus camaldulensis syn. E. rostrata	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27
Gum, Rose	Eucalyptus grandis	8	9	10	11	12	13	14	14	15	16	17	18	18	19	20	21	22	23	24
Gum, Shining	Eucalyptus nitens	7	8	9	10	11	11	12	13	14	15	16	17	18	19	20	20	21	22	23
Gum, Spotted (N.S.W.)	Eucalyptus maculata	7	8	8	9	9	10	10	11	12	12	13	13	14	14	15	15	16	17	--
Ironbark, Grey	Eucalyptus paniculata	7	8	9	10	11	12	13	14	15	15	16	17	18	19	20	21	22	23	24
Ironbark, Red	Eucalyptus sideroxylon	10	11	12	12	13	14	15	16	16	17	18	19	20	21	22	22	23	24	24
Jarra	Eucalyptus marginata	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25
Karri	Eucalyptus diversicolor	7	7	8	9	10	11	12	13	13	14	15	16	17	18	18	19	20	21	22
Kauri, New Zealand	Agathis australis	8	9	10	10	11	12	12	13	13	14	14	15	16	16	17	17	18	18	19
Mahogany, African	Khaya spp. ivorensis	7	8	10	11	12	13	15	16	17	18	19	20	22	23	24	25	26	27	29
Marri	Eucalyptus calophylla	7	7	8	9	9	10	11	11	12	13	13	14	15	15	16	17	17	18	19
Oak, Silky, Northern	Cardwellia sublimis	7	8	8	9	10	11	12	13	14	15	16	17	17	18	19	20	21	22	23
Oak, Silky White	Stenocarpus sinuatus	7	8	9	9	10	11	11	12	13	13	14	15	15	16	17	17	18	19	19
Pine, Cypress, White	Callitris columellaris sent. lat. (=C. glauca)	8	9	10	10	11	12	13	14	15	16	17	18	19	20	21	22	22	23	24
Pine, Hoop	Araucaria cunninghamii	9	10	11	12	12	13	14	15	16	16	17	18	19	20	21	22	22	23	24
Pine, Huon	Dacrydium franklinii	9	10	10	11	12	13	13	14	15	15	16	17	18	18	19	20	20	21	22
Pine, Radiata (NZ)	Pinus radiata	6	7	8	10	11	12	13	14	16	17	18	19	20	22	23	24	25	27	28
Pine, Radiata (Vic.)	Pinus radiata	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26
Pine, Slash	Pinus elliotii	6	7	8	9	10	11	12	14	15	17	18	20	21	22	24	--	--	--	--
Stringybark, Messmate	Eucalyptus capitellata	8	9	10	11	11	12	13	14	15	16	17	18	19	19	20	21	22	23	24
Tallowwood	Eucalyptus microcorys	6	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24
Teak	Tectona grandis	6	7	8	9	9	10	11	12	12	13	14	15	16	16	17	18	19	19	20
Turpentine	Syncarpia glomulifera syn. S. laurifolia	7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	24
Woollybutt	Eucalyptus longifolia	9	10	10	11	12	13	14	15	15	16	17	18	19	20	21	22	23	24	24

***NOTE:**

- A. Fir, Douglas (DIC) is the nominal base calibration of the Delmhorst meters.
- B. Source of data: CSIRO 1974 Special Report, except for Douglas Fir (U.S.), African Mahogany and Teak.
- C. When using insulated pins, set meter at 2-pin mode or read the 2-pin (insulated pins) scale, depending on meter used.