



# EPOXYMALLENSHOP



mengverhouding: 100:60

HARS (A) GRAM	VERHARDER (B) GRAM	TOTAAL GRAM
5	3	8
10	6	16
15	9	24
20	12	40
25	15	32
30	18	48
35	21	56
40	24	64
45	27	72
50	30	80
55	33	88
60	36	196
65	39	104
70	42	112
75	45	120
80	48	128
85	51	136
90	54	144
95	57	152
100	60	160
105	63	168
110	66	176
115	69	184
120	72	192
125	75	200