

# Nexus Grippa-Fast 400 Adhesive

## TECHNICAL DATA SHEET

### DESCRIPTION & USES

**Nexus Grippa-Fast 400** is ideal for bonding carpet gripper, woods, metal trims, metal nosing, aluminium & many other types of products where a quick bond is required to concrete, timber and most other common building substrates. **Grippa-Fast 400** has excellent resistance to high temperatures and water when cured (conforms to Class D4-DIN EN 204)

### PREPARATION

All surfaces must be clean & sound, free of dust and any other contaminants that may affect bond.

### APPLICATION

Apply thin bead of adhesive to one surface. Press the two surfaces to be bonded firmly together. Pressure may need to be applied to keep the two surfaces in contact while adhesive cures. Large extrusions should also be secured with appropriate fixing screws.

### CURING TIME

**Grippa-Fast 400** is a moisture cure system. Allow approx one hour curing time for thin bead. This process may be accelerated by spraying a light mist of water to one of the surfaces. This product needs moisture to cure, the less moisture available the longer the product will take to cure.

### CLEAN UP

Remove any wet adhesive with suitable solvent cleaner before it cures. When cured remove by mechanical means.

### Typical Properties

Appearance:	Beige paste
Viscosity:	Thick paste
Specific Gravity:	Approx 1.45

**Note:** Always carry out your own test to confirm suitability of this product with your application. Additional information on physical properties, health hazards, storage, handling and transport is available in the Material Safety Data Sheet (MSDS), available on request.

November 2012

### Nexus Adhesives Pty Ltd

ABN 61 121 120 036

42 Healey Road  
Dandenong South VIC 3175 Australia  
**Tel** +61 3 9706 4022  
**Fax** +61 3 9706 4122  
info@nexusadhesives.com.au  
www.nexusadhesives.com.au