

URBAN

| | | | |
|--|----------------------------------|---|-----------------------------------|
| SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE | | 100% POLIESTER / 100% POLIESTER 100% POLYESTER / 100% POLYESTER 100% POLIESTERSKO VLAKNO / 100% POLIESTERSKO VLAKNO 100% POLYESTER / 100% POLYESTER 100% POLIESTERE / 100% POLIESTERE | |
| ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA | 140 cm +/-2% | TEŽA WEIGHT TEŽINA GEWICHT PESO | 280 gr/m2 +/-5% |
| TEST | STANDARD | REZULTAT/RESULTS/REZULTAT/ERGENIS/ RISULTATI | |
| | | OSNOVA/WARP/ OSNOVA/KETTE/ORDITO | VOTEK/WEFT/ POTKA/SCHUSS/TRAMA |
| PRETRŽNI RAZTEZEK ELONGATION PRETRŽNA RASTEZLJIVOST AUSDEHNUNG RESISTENZA ALLA TRAZIONE | EN ISO 13934-1 | 1460 N (33,3 %) | 1389 N (26,7 %) |
| RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE | EN ISO 13937-3 | 80,4 N | 72,1 N |
| DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORRIMENTO DELLA CUCITURA | EN ISO 13936-2 | 2,5 mm | 2,3 mm |
| OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA ALL'ABRASIONE | EN ISO 12947-1 EN ISO 12947-2 | >100.000 OBRATOV/REVS./OBRATAJA /TOUREN/GIRI | |
| PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA AL PILLING | EN ISO 12945-2 | 5 | |
| OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE | EN ISO 105-B02 METHOD 2 | >5 | |
| OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA DEL COLORE ALL'ABRAZIONE | EN ISO 105-X12 | SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO | MOKRO/WET/ MOKRO/NASS/UMIDO |
| | | 4 | 4-5 |
| VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI | DIN EN 14362-1 DIN EN 14362-3 | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE | |
| VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFFE CONTENUTO DEI COLORANTI ALLERGENICI | DIN 54231 | NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE | |

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631

Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

| | | |
|--|--|--|
| TEST NEGORLJIVOSTI: FIRE RETARDANT: TEST NEGORIVOSTI: BRENNVERHALTEN: IGNIFUGO: | BS 5852 source 0 without soaking- DIN EN 1021 part 1 without soaking | PRESTAL TEST PROŠAO TEST PASSED UEBERSTANDEN SUPERATO |
| ZAŠČITA TKANINE: FABRIC PROTECTION: ZAŠTITA TKANINE: STOFFSCHUTZ: PROTEZIONE TESSUTO: | VODOODBOJNI NANOS WATER REPELLENT VODOODBOJNI NANOS WASSERABWEISEND IDROPEPELENTE | |

MED BARVNIMI PARTIJAMI SO MOŽNA ODSSTOPANJA V BARVI
 COLOUR DIFERENCES BETWEEN DYING LOTS ARE POSSIBLE
 MOGUĆA SU ODSUPANJA U BOJI KOD PROIZVODNJE
 FARBNIANSSEN SIND MOEGLICH
 TRA I VARI LOTTI POSSONO VERIFICARSI DELLE VARIAZIONI NEL COLORE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
 Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si