



## MONOFLASH CL • Liquid Additive - Accelerator



### PRODUCT DESCRIPTION

MonoFlash CL is used to reduce the initial setting time of cement and lime-based renders including MonoCal GM/GF, MonoPass GM/GF & TradiBatard GM/GF.

### SUPPORTING PRODUCTS

- Monocal GM/GF
- MonoPass GM/GF
- TradiBatard
- RenoPass Inter – Painted Substrates
- RenoJet

### PRODUCT PREPARATION

(Ensure the guidance for mixing including water settings/proportions are followed)

- Add 0.5-1.5 Litres of MonoFlash CL to the mixing water for 8 bags of 25kg Mortar.
- Water content per bag should be reduced by the same amount of admixture added to the mixing water ensuring all polymers and aggregates are dispersed.
- For guidance purposes only setting time can be reduced by upto 4 hours at the standard dosage rate. Setting times are based on temperature, substrate and general weather conditions.
- For machine application please consult machine manufacturer prior to use.

**MONOFLASH CL IS NOT AN ANTIFREEZE NORMAL PRECAUTIONS SHOULD BE ADHERED TO**

### APPLICATION CONDITIONS

- Temperature: +5°C +30°C.
- Do not apply in wet weather
- Do not apply if there is a risk of Frost or Freezing Conditions

### SUBSTRATE PREPARATION

Please contact VPI UK Ltd for specific application procedures

- Substrate must be clean, dry, dust free: e.g: formwork oil, curing agent....
- Construction should conform to BS 5628 code of practice for use of masonry
- Remove excess render/plaster, mould/release oil, paint and masonry coatings.

### TECHNICAL CHARACTERISTICS

APPEARANCE: Creamy/Yellow coloured liquid

COMPOSITION: Synthetic liquid additive.

DENSITY: 1.4

pH: 7

### PRECAUTIONS FOR USE

To protect your health and the environment, and for safe use of this product, follow the precautionary statements which are labelled on the packaging. You will find the safety instructions for this product in the Safety Data Sheet.

### PRODUCT CURING TIMES AT 20°C

- Time between coats: 1-2 Hours
- Setting times 1 to 24 Hours

*Information provided in this document is based on our knowledge and experience of the products supplied, application results can vary depending on the application methods and skill of the installer of the products. Before application of the products in the information sheet it is recommended to check if this is the most current and up to date version of the document.*





## MONOFLASH CL • Liquid Additive - Accelerator



### PRODUCT CONSUMPTION

- Approx 100m<sup>2</sup> per 25 Litre tub

### PACKAGING

25 Litre Tub/Buckets – 1000 Litre IBC

### STORAGE

18-month shelf life – Stored in a cool dry, environment without contact with the ground at a consistent temperature.

### HEALTH & SAFETY

Suitable protective clothing required when handling and using this product. The product contains materials which can cause an allergic reaction, irritation to eyes and harmful consumed. Seek medical advice in case of contact with eyes. Keep out of the reach of children and minors. Always read and follow the guidance set out in the Health and Safety data sheet for this product.



*Information provided in this document is based on our knowledge and experience of the products supplied, application results can vary depending on the application methods and skill of the installer of the products. Before application of the products in the information sheet it is recommended to check if this is the most current and up to date version of the document.*

