

Characteristics

Sterile nitrile pairs, tested for use with chemotherapy drugs. Meets all requirements of USP 800. Designed to allow easy double gloving. Pair packaged, inner wrapper in ozone resistant multi-vac packaging.



**Exam Glove
Sterile Pairs**



**NitriDerm®
EC Pairs**

**Powder-Free Nitrile
Series 114**

Extended Cuff

PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
XS	GLVNITRSTXSUS	50 Pairs/box, 4 boxes/case	Gloves, Exam, Nitrile, Chemo, Sterile, Powder-Free, Pairs, Extended Cuff
S	GLVNITRSTSUS	50 Pairs/box, 4 boxes/case	
M	GLVNITRSTMUS	50 Pairs/box, 4 boxes/case	
L	GLVNITRSTLUS	50 Pairs/box, 4 boxes/case	
XL	GLVNITRSTXLUS	50 Pairs/box, 4 boxes/case	

Product Attributes

- Non-Latex
- Ambidextrous
- Tacky Finish

Benefits

- No Risk of Latex Allergens
- Donning Versatility
- Improved Wet/Dry Grip

✓ **Tested for use with
Chemotherapy Drugs**

Product Solutions You Trust





NitriDerm® Extended Cuff ▾ Powder-Free Sterile Chemo

ONE STERILE PAIR

**Ambidextrous Nitrile Exam Gloves
Tested for use with Chemotherapy Drugs**

Extended Cuff ▾ Ambidextrous



NitriDerm® Sterile Chemo is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D6319	Standard Specification for Nitrile Examination Gloves for Medical Application
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens
ASTM D6978	Standard Practice for Assessment of Resistance of Medical Gloves to Permeation by Chemotherapy Drugs

Average Length	Average Palm Thickness	Average Finger Thickness
11.5 in ♦ 290 mm	4.7 mil ♦ 0.12 mm	6.3 mil ♦ 0.16 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	32	33
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	691	667
ASTM Requirement Min. (%)	500	400

Clean Air
Essentials **797/800**

1 800 476 2010

cleanairessentials.com

Chemotherapy Drug Permeation (Breakthrough detection time in minutes, 0.01µg/cm ² /min.)	(ASTM D6978) Breakthrough Detection Time
5-Fluorouracil (Adrucil) (50.0 mg/mL)	>240
Cisplatin (1.0 mg/mL)	>240
Cyclophosphamide (Cytoxan) (20.0 mg/mL)	>240
Dacarbazine (DTIC) (10.0 mg/mL)	>240
Doxorubicin Hydrochloride (Adriamycin) (2.0 mg/mL)	>240
Etoposide (Toposar) (20.0 mg/mL)	>240
Paclitaxel (Taxol) (6.0 mg/mL)	>240
Thio-Tepa (10.0 mg/mL)	144.49
Carmustine (BiCNU) (3.3 mg/mL)	WARNING: Do Not Use

- ▾ Gloves used for protection against Chemotherapy Drug Exposure should be selected specifically for the type of chemicals used.
- ▾ Users should review Material Safety Data Sheets for each drug to determine the required level of protection.
- ▾ Storage: Avoid storing at temperatures above 104°F (40°C). Shield gloves from direct sunlight, fluorescent light, x-rays, moisture and ozone.