

Product Technology Service

Report No.: NB2009021908

Test Report

Testing institute : Ningbo Product Technology Service Co., Ltd.
6&7F, 59#, Huayu Road,
Yinzhou District, Ningbo 315192 P.R. China

Applicant : Dewei Plastic & Mould Co.,Ltd
No.163 Wangxi Road,Eastcity,Huangyan, Zhejiang, P.R. of China 318020

Test item(s) : PET bottle

Model/type : 8OZ

Colour : RED

Material : PET

Sample receive date : 2009-02-20
Completes date : 2009-02-25

Testing location : Product Technology Service (Ningbo) Co., Ltd.

Test specification(s) : US FDA Extraction Test
In accordance with 21 CFR 177.1630

Test Result : According to the kind and extend of tests performed the test item passed the test specification.



Authorized Signature: Waterson Liu

Ningbo, 2009-02-25

The test results exclusively refer to the samples examined. This report shall not be reproduced except in full without written approval and does not authorize the use of Ningbo Product Technology Service Co., Ltd. label

Product Technology Service (Ningbo) Co., Ltd.

6 & 7F, Huayu Road, 59#
Yinzhou District
Ningbo 315192 P.R.China
<http://www.pts-lab.com>
NO: RC-SHC-003/01

Tel: 86-574-83036506
Fax: 86-574-83036508
P.R.: 315192
E-mail: info@pts-lab.com

宁波中普检测技术服务有限公司
6 & 7F, Huayu Road, 59#
Yinzhou District
Ningbo 315192 P.R.China
<http://www.pts-lab.com>

Tel: 86-574-83036506
Fax: 86-574-83036508
P.R.: 315192
E-mail: info@pts-lab.com

1. US FDA 21 CFR 177.1630: Closures with sealing gaskets for food containers

Tested Sample: PET bottle			
Parameter	Unit	Result	Limit
Aqueous water 120 ^o F / 24 hours	mg/in ²	<0.01	0.5
50% Alcohol 120 ^o F /24 hours	mg/in ²	0.20	0.5
N-heptane 70 ^o F /30min	mg/in ²	0.25	0.5
8% Alcohol 120 ^o F /24 hours	mg/in ²	0.18	0.5

Remark: mg/in² = mg per square inch

Sample photo(s), see annex 1

---End---

ANNEX 1

Sample photos, consists of 1 page



PET bottle