



Vipond's Paints Pty Ltd

58 Barrie Road, Tullamarine VIC 3043

Phone (03)9350 4188

Email info@viponds.com.au

www.viponds.com.au

PRODUCT INFORMATION

METALLIC PASTES

Description

Gold, silver and copper powders that are dispersed into a paste that readily mix with Vipond's clear mediums such as Goldsize, Feature Gloss clear, Polyurethane clear, Acrylic Gloss and Low Sheen glaze, Acrylic Trim clear, Tautflex clear and Signcryn clear to make a metallic paint.

Use

On all surfaces where a metallic finish is required.

Surface Preparation

Apply to a dry clean surface that has been properly primed and undercoated.

Mixing

Mix at a rate of 180 gms of silver per litre of clear and 220 gms gold or copper per litre of clear. Add the clear to the paste in small amounts and stir well until the metallic dissolves into the clear without any lumps. Continue to add the clear and stir until uniformly mixed.

Note Only mix enough paint for your immediate requirements as unused paint may become unstable after a few days in storage.

Application

Brush, roll or spray. The best result is achieved with spraying. When brushed or rolled the metallic particles align themselves randomly and a motley finish results. It is important to lay off in one direction.

Durability

Metallic paint will tarnish if exposed to air. It is important that the metallic powders are completely encapsulated in the medium. A final coat of clear is recommended.

Coverage

Approximately 12 square metres per litre when mixed at the recommended ratios.

Metallic Paste

Clean up and Thinning

Use appropriate thinners as recommended for the clear

Caution

Keep the container closed to prevent the paste from drying out.

Pack Size

Gold and Copper 220gms (1 litre), 880 gms (4 litre)

Silver 180 gms (1 litre), 720 gms. (4 litre)

Revised January 2021