

DULUX® FleetShield® 488 ULTRABUILD EPOXY PRIMER



Dulux Australia
ABN 67 000 049 427

Product Description

Dulux® FleetShield® ULTRABUILD Epoxy Primer is a two pack epoxy- polyamide primer that has excellent adhesion to metal substrates. Ultrabuild contains anti-corrosion pigmentation and has excellent water resistance.

Dulux® FleetShield® ULTRABUILD Epoxy Primer is available in three colours:

488S0055 FleetShield® Ultrabuild White
488S0056 FleetShield® Ultrabuild Black
488S0057 FleetShield® Ultrabuild Grey

Dulux® FleetShield® ULTRABUILD Epoxy Primer is easy to sand. The top coat may be applied after 2 hours without sanding at 20°C. The primer may be top coated with Autospeed and Fleetshield 2K products without sanding up to 5 days after application of the primer if the temperature is below 20°C. The primer will require sanding prior to application of a topcoat after five days.

For applications which require rapid processing, the use of ULTRABUILD HP Pt B 980-S0069 allows ULTRABUILD Epoxy Primer to be topcoated between 30 minutes and 5 days after primer application without sanding where temperatures do not exceed 20°C.

Ultrabuild Cold Cure Thinner is to be used for application conditions where the temperature will fall below 10°C during curing. **Note, 920-S0063 Cold Cure Thinner and 980-S0069 Ultrabuild HP Hardener are not compatible.**

Suitable Dulux® FleetShield® and AutoSpeed® top coats include:

Dulux® FleetShield™ 2K Mixed colour, 428 line
Dulux® FleetShield™ 2K White Base, 428S0204
Dulux® FleetShield™ 2K Black Base, 42889843
Dulux® FleetShield™ 2K Red Base, 428S0011
Dulux® FleetShield™ 2K Yellow Base, 428S0062
Dulux® AutoSpeed® PT Basecoat (440-Line)
Dulux® AutoSpeed® CV 2K 2:1 mixed colour (488-Line)

Substrates

All substrates must be thoroughly prepared and cleaned. For metal substrates, it is recommended that the surface be abrasive blasted or thoroughly sanded prior to the application of the primer. Polyester filler can be applied over sanded Ultrabuild, and Ultrabuild can be applied over polyester filler.

It is recommended that Dulux® AutoSpeed® Prepwash 965-89784 is used for cleaning and degreasing of surfaces.

Suitably prepared surfaces:

- Sound existing finishes
- Steel, 316 grade Stainless steel, Aluminium and galvanized surfaces
- Fibreglass
- ABS plastic
- Polyester filler

DULUX® FleetShield® 488 ULTRABUILD EPOXY PRIMER



Dulux Australia
ABN 67 000 049 427

Product & Additives:

Part A

Dulux® FleetShield® ULTRABUILD Epoxy Primer Pt A 488-Line

Part B

Dulux® FleetShield® ULTRABUILD Pt B 980-S0058

Dulux® FleetShield® ULTRABUILD HP Pt B 980-S0069

Thinners

Dulux® FleetShield® ULTRABUILD Cold Cure Thinner 920-S0063









Dulux® AutoSpeed® 2K Thinner- Normal 920-89292

Dulux® AutoSpeed® RP Thinner 920-89819

Dulux® AutoSpeed® 2K Thinner- Slow 920-89847

Please select thinner for Ultrabuild using the table below.

Temperature degrees (C)	5-10	10-15	15-20	20-25	25-30	30-35
Ultrabuild Cold Cure Thinner, 920S0063						
RP thinner, 920-89819			Small area only			
2K Thinner- Normal 920-89292						Small area only
2K Thinner- Slow 920-89847						

	Mixing Ratio	4 Parts 488-S Ultrabuild Part A by volume	
	Hardener	1 Part Ultrabuild Part B 980-S0058 by volume Or 1 Part Ultrabuild HP Part B 980-S0069 by volume for Rapid Processing	
	Thinner	20% 920-89292 by volume 10-20% 920-S0063 by volume Cold Cure thinner Note: 920-S0063 Cold Cure Thinner and 980-S0069 Ultrabuild HP Hardener are not compatible	
	Spray Viscosity DIN Cup 4 @ 25°C	25 seconds at 15% thinning	
	Gravity & Suction Feed	Fluid Tip: CONVENTIONAL: 1.4 – 1.8mm	Spraying Pressure: 350-450 kPa. Or refer to manufacturer's recommendations
	Pressure pot	CONVENTIONAL: 1.1 – 1.8mm	350-450 kPa. Or refer to manufacturer's recommendations
	Application	1 to 2 even coats for a dry film build of 60-80 micron	
	Air Flash	10 - 15 minutes air flash between coats at 25°C.	

DULUX® FleetShield® 488 ULTRABUILD EPOXY PRIMER



Dulux Australia
ABN 67 000 049 427

	Baking/Drying	8 hours at 25°C 60 mins at 50°C
	Sanding - Manual	Wet: P600 - P800 Grit
	Sanding - Manual	Dry: P400 - P600 Grit
	Sanding - Mechanical	Dry: P400 - P600 Grit
	Spraying	Use air fed mask at all times. Refer applicable AS/NZS Standards
	Pot Life	When mixed, 6 hours at 25°C
	Topcoat time - non sand	ULTRABUILD HP Pt B 980-S0069 Minimum 30 Minutes Maximum 2 Hours <i>*recommendation at temperatures at or below 20°C</i>

HBC Formulae

Ultrabuild White Part A 488-S0055 and Ultrabuild Black Part A 488-S0056 can be mixed to provide the HBC colours in the table below,

HBC colour	Ultrabuild White Part A 488-S0055 (Grams per litre)	Ultrabuild Black Part A 488-S0056 (Grams per litre)	Total (Grams per litre)
1	1759.00	-	1759.00
2	1580.45	158.04	1738.49
3	731.12	909.84	1640.96
4	264.56	1322.81	1587.37
5	-	1557.00	1557.00

Ready for use charts:

Weight Mixing Ratios for 488-Line Fleetshield Ultrabuild Primer Using the Intelligent balance and adding by percentage addition

Note: This order of addition must be maintained when using the intelligent balance.

HBC	Part A	Part B	Thinner
1	100.00%	12.80%	10.66-17.76%
2		12.95%	10.78-17.96%
3		13.72%	11.43-19.05%
4		14.19%	11.81-19.68%
5		14.46%	12.04-20.07%

The quantity of thinner added can be varied to suit your spraying conditions.

DULUX® FleetShield® 488 ULTRABUILD EPOXY PRIMER



Dulux Australia
ABN 67 000 049 427

See notes below regarding alternate thinners and hardener.

For safe handling:

Please refer to the Material Safety Data Sheet number: 3000 for this product before use.

In the event of an emergency contact: 1 800 033 111 (ALL HOURS) NZ 0800 734 607

For further information contact:

Dulux Australia

1956 Dandenong Rd, Clayton, Victoria,
3168

Australia

ABN 67 000 049 427

Telephone:

1 800 810 114

Fax:

61 3 8787 4502

Dulux New Zealand

31B Hillside Road

Glenfield, Auckland
New Zealand

Telephone:

0800 800 424

Dulux and Autospeed are registered trademarks. FleetShield and marks followed by the symbol ™ are trademarks.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux Refinish Coatings to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux Refinish Coatings provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux Refinish Coatings by any condition or warranty implied by applicable legislation, regulation or other Government ordinance voiding or prohibiting such exclusion, limitation or modification