



AIRCOLOR PRIMERPLAST plastic primer

H38

VERSION: 230531
Page:1/2

ADHESION PRIMER


DEFINITION

Adhesion promoter for plastics aiding good adhesion on most plastic parts of the car both interior and exterior, including bumpers, mirrors and other plastic parts. Topcoat can be applied after approximately 10 minutes air dry at 20°C.

PHYSICAL CHARACTERISTICS





Resin:	Chlorinated polyolefin
Propellant:	BP
Colour:	Colourless
Specific weight:	0,73 kg/l a 20°C
Yield:	3 m ² /spray
Dry film thickness:	2-4 µ/coat
Resistance of the container to heat:	< 50 °C
VOC:	718 g/l Application 2004/42/EC - IIB (e)(840)

SURFACE PREPARATION

PROCESS	Plastics (*)
 ROBRITE VF DA93	✓

(*) PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, PPO, PBT, PUR flexible foam, UP-GF plastics


APPLICATION

			
2'	20-25 cm	1 coat	10'

REMARKS

Shake the aerosol before use for 2 minutes after hearing the steel mixing balls move.
Apply on clean, degreased and properly prepared surfaces.
Apply a thin layer of the product.
Do a test to verify compatibility with the surface and colour.

EQUIPMENT CLEANING



After use, turn
can upside
down and spray
for several
seconds

SAFETY

Follow instructions on the product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

STORAGE

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

SHELF LIFE

One year in unopened original packaging.

These products are for professional use only. The Safety Data Sheet should be consulted before use and the precautionary warnings on the product packaging should be observed. Its correct use, according to its purpose and respecting its technical and security data, provided in these documents, is the sole and exclusive responsibility of the user. ROBERLO S.A.U declines any liability due to the incorrect use of any product.

The information included in this documentation is based on our scientific and technical knowledge on the date of its issuance. ROBERLO S.A.U reserves the right to modify and/or discontinue all or part of the information at any time and without prior notice. It is the user's responsibility to verify the update of the information. The latest version of this document replaces all previous versions.

*All clauses contained herein apply to any future changes or modifications.
For any additional technical information please consult with our Customer Service or our Technical Department.*