R (\mathbf{R}) stainable and ARRA itied AR cladd \mathbf{C} Grotius is a development by Provast, K N E K A S H P R O ______ ביצוע פרויקטים אדריכליים ELL Aroven Syroven Syrable - stable neutral

Bamboo: the fastest growing plant in the world



certified durable fire resistant

sustainable

CO₂

proven

Since 2008 over 6 million m² decking and cladding installed, in more than 60 countries.



High stability, fast installation and hidden fasteners

MOSO[®] Bamboo X-treme[®]

With Bamboo X-treme®, MOSO® has developed a truly **ecological** and **durable** alternative to increasingly scarce tropical hardwood and nonrenewable materials. MOSO® uses a **unique** Thermo-Density® **process** of heat-treatment at 200°C followed by High Density® compression to enhance the **hardness**, **dimensional stability**, **fire resistance** and **durability** to a level **superior** to the best tropical hardwood species. MOSO® Bamboo X-treme® can be used not only for **outdoor cladding** but also for **outdoor decking, fencing and outdoor furniture**.

table of contents

from bamboo to Bamboo X-treme®	4
benefits	5
Bamboo X-treme® Outdoor Cladding Varibo profile Varibo Closed profile Rebated & Trapezium profile Rhombus profile Varibo GRAD® profile	6 8 10 12 14
Bamboo X-treme® Outdoor Beams	16
test results	18
sustainability	20
user information	22
endless possibilities	22



Private Residence Buenos Aires (100 m²) Buenos Aires, Argentina

from bamboo to Bamboo X-treme®

The fast growth and abundant availability make bamboo a rapidly renewable resource, and a perfect material for many applications in and around buildings. With good reason, it's often called '**the building material of the future**'. However, bamboo as a raw material cannot be used outdoors without a protective treatment. Due to its high "sugar"-components, bamboo is more susceptible to being attacked by micro-organisms and fungi. Let us explain how we get from the raw bamboo material to the final product, MOSO® Bamboo X-treme®, through a production process called Thermo-Density®.

stem to strands

After harvesting, the mature bamboo stems are split in a longitudinal direction and the outer and inner skins are removed. The strips are then crushed using a number of incision rollers which create cross linked strands. The untreated strands are a light yellow colour.

thermal modification

In several steps, the strands are heated up to 200°C in the presence of saturated steam (to protect the wood from charring or burning) and cooled down. During thermal modification, the moisture content changes and the sugar content is removed from the material. Furthermore, this process changes the colour of the bamboo from white/yellow to deep/dark brown.

from strands to product

The dark bamboo strands are dipped into phenolic glue (< 10% of the weight of the bamboo). After drying, the strands are put into a mould, and are then compressed under high temperature and pressure to cure the glue. The output is a large panel, which is cut into smaller sections (boards or beams). These are then further processed and profiled to become the required shape (for example, for decking: a grooved surface and edge grooves to allow installation with fasteners). As a last step, depending on the customer's request, the boards can be finished.

ready to harvest after 4-5 years



with a heat-treatment at 200°C

modifying the bamboo strands



V

Thermo-Density®

We call the combination of compressing and thermally modifying the bamboo strands a Thermo-Density® process. It increases the density from 650-700 kg/m³ to approx. 1150 kg/m³ and improves the hardness of this product significantly. After pressing, the material is stronger and harder than almost any other hardwood in the world. At the same time, the dimensional stability of bamboo is improved by approximately 50%.

Besides stability and hardness improvements, the durability is improved to the best durability class possible, from Class 5 to Class 1: Class 1 (EN 350) CEN/TS 15083-2 - simulated graveyard test and Class 1 (EN 350) CEN/TS 15083-1.

durability class according to EN 350 (CEN/TS 15083-2 / CEN/TS 15083-1)

5	4	3	2	1
MOSO [®] Bar	nboo X-trem	e*		
lpé				
Strand Wov	ven Bamboo			
Bangkirai				
Oak				
Scots Pine				
	range of durability results			

MOSO® Bamboo X-treme® is also well protected against superficial fungi Class 0 (EN 152), and achieves the use/risk Class 4 according to EN 335.

Only MOSO^{*} can ensure you have the original, unique Bamboo X-treme^{*} product. Other products that attempt to copy the original, do not offer the same quality or level of durability, dimensional stability and ecology. With a look-alike product, there is a large risk of claims after installation. Always ask for the original, certified MOSO^{*} Bamboo X-treme^{*} products!

split the Moso bamboo stems, remove the outer skin and crush the strips into strands



compressing the strands into Thermo-Density® material



creating the final profile and surface



MOSO[®] Bamboo X-treme[®]: material

A-treme": material more stable, harder and stronger than almost any other hardwood in the world!

benefits of Bamboo X-treme® **Cladding**



hard & durable

- Biological durability Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test / Class 1 (EN 350 / CEN/TS 15083-1).
- Use Class 4 in accordance with EN 335.
- Effectiveness against blue stain Class 0 (EN 152).
- Exceptionally hard: Brinell ± 9.5 kg/mm² (harder than any tropical hardwood available).
- MOSO[®] provides Bamboo X-treme[®] outdoor products^{*} with up to 25 years warranty.



high stability

- Very stable as a result of a unique Thermo-Density® process of heat-treatment combined with High Density® compression.
- Far more stable than tropical hardwoods enabling an end-match system (tongue & groove on ends).
- Limited tendency to torsion.
- No gap between the ends of the boards necessary.
- Closed profile allows for an installation without space between the boards.



maintenance-free

- Does not require periodic maintenance.
- Choice between natural greying or retaining the brown colour with an exterior finish.



fire resistant

- Achieves fire resistance Class B-s1-d0 (EN 13501-1) without use of fire retardants.
- Achieves flame spread index Class A following ASTM E84.
- As a result, MOSO[®] Bamboo X-treme[®] can be easily applied in public projects without additional protective measures.



beautiful appearance

- A beautiful, natural hardwood look.
- Use of hidden MOSO[®] Fasteners avoids face screwing and plugging.
- Free of knots and natural plant resins.



endless resource

- Made from bamboo; with a growing speed of up to 1 meter per day it is the fastest growing plant on earth.
- Ready to harvest after 4-5 years (compared to up to 100 years for hardwood species).
- Consisting of approx. 90% natural bamboo.



CO₂ neutral

- Official LCA and carbon footprint studies (EN 15804) confirm that MOSO® Bamboo X-treme® is CO2 neutral during the product lifespan**.
- No use of fungicide in the production.



economical

- Simple and fast
- installation.
- Reduced waste because of the end-matched connection.
 Cost effective transportation because
- transportation becau of the fixed 1850 mm length.




Villa by Studio Osiris Hertman The Netherlands




Showroom Varios Beautiful products Hoek van Holland, the Netherlands

Hostel Stayokay Noordwijk, the Netherlands



MOSO® Bamboo X-treme® Varibo Outdoor Cladding

MOSO® Bamboo X-treme® Varibo Cladding are solid boards in various widths for exterior applications. The boards are made from bamboo strips that have been compressed and thermally modified at 200°C. This unique Thermo-Density® process provides MOSO® Bamboo X-treme® with the highest durability class possible in the appropriate EU norms, increases the stability and density, and consequently the hardness. Furthermore, contrary to wood products, this material can achieve fire resistance Class B-s1-d0¹ (EN 13501-1) without impregnation with expensive and eco-damaging fire retardants. MOSO® Bamboo X-treme® Varibo Cladding is available in various dimensions. The Varibo boards can be fixed with MOSO® Fasteners (18 mm). Like any tropical hardwood species, when exposed to outdoor conditions, Bamboo X-treme® will turn grey over time creating a very natural look.



					(mm)*	(mm)
Unfinished	Flat	Yes	R3	2 mm x 45°	65	1850x65x18
Unfinished	Flat	Yes	R3	2 mm x 45°	100	1850x100x18
Unfinished	Flat	Yes	R3	2 mm x 45°	137	1850x137x18
Unfinished	Flat	Yes	R3	2 mm x 45°	178	1850x178x18
Unfinished	Flat	Yes	R3	2 mm x 45°	65	1850x65x30
Unfinished	Flat	Yes	R3	2 mm x 45°	100	1850x100x30
	Unfinished Unfinished Unfinished Unfinished	UnfinishedFlatUnfinishedFlatUnfinishedFlatUnfinishedFlat	UnfinishedFlatYesUnfinishedFlatYesUnfinishedFlatYesUnfinishedFlatYesUnfinishedFlatYes	UnfinishedFlatYesR3UnfinishedFlatYesR3UnfinishedFlatYesR3UnfinishedFlatYesR3UnfinishedFlatYesR3	UnfinishedFlatYesR32 mm x 45°UnfinishedFlatYesR32 mm x 45°UnfinishedFlatYesR32 mm x 45°UnfinishedFlatYesR32 mm x 45°UnfinishedFlatYesR32 mm x 45°	Unfinished Flat Yes R3 2 mm x 45° 65 Unfinished Flat Yes R3 2 mm x 45° 100 Unfinished Flat Yes R3 2 mm x 45° 100 Unfinished Flat Yes R3 2 mm x 45° 137 Unfinished Flat Yes R3 2 mm x 45° 178 Unfinished Flat Yes R3 2 mm x 45° 65


*) Effective width without gap between the boards, recommended gap 6 mm.

installation

- MOSO[®] guarantees the bamboo material and the mounting materials (fastener/screw) it supplies but does not guarantee the connection with other materials (such as sub frame joist/battens). It is the responsibility of the installer to make sure the used screw matches such materials during the full lifetime of the product.
- For installation with fasteners, the MOSO[®] Fasteners CLIP-SCREW-BX09 with screws and MOSO[®] Fasteners CLIP-BX09 without screws are available. More information about the MOSO[®] Fasteners can be found: ▶www.moso-bamboo.com/x-treme/accessories
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust.
- Full version available at: >www.moso-bamboo.com/varibo

technical characteristics and certifications

- Density: ± 1150 kg/m³
- Dimensional stability: length: + 0.1 %; width: + 0.9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534)
 Reaction to fire: Class B-s1-d0 (EN 13501-1) ¹⁾
- Flame spread index: Class A (ASTM E84)
- Thermal emittance: 0.81 (ASTM C1371) ²⁾
- Solar Reflectance (SR): 0.32 (ASTM C1549)²⁾
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980) ²⁾
- Modulus of Elasticity: 13565 N/mm² (mean value EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
 Biological durability: Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test /
- Class 1 (EN 350 / CEN/TS 15083-1) • Effectiveness against Blue Stain: Class 0 (EN 152)
 - Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi) Use Class: Class 4 (EN 335)
- CO₂ neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/lca)
- Environmental Product Declaration EPD (EN 15804) (www.moso-bamboo.com/epd)
- FSC^{*}: Products available with FSC^{*} certification on request. Contribution LEED BD+C - v4: MR 1, MR 2, MR 3 (FSC^{*}), SS 7
- v2009: MR 6, MR 7 (FSC*)
- Contribution BREEAM: MAT 1, MAT 3 (FSC*), MAT 5 (HD)
- Guarantee: 25 years
- ¹⁰ Tested on 18 mm thickness, without gaps between boards, with ventilation space behind boards. ²⁰ Tested on 3 years weathered MOSO* Bamboo X-treme*.





Also available with FSC[®] certification.







Grotius residential Towers (2200 m²) The Hague, the Netherlands



Water Authority Limburg (600 m²) Roermond, the Netherlands


Notiz Hotel NHL Stenden





MOSO® Bamboo X-treme® Varibo Outdoor Cladding **Closed** profile

MOSO® Bamboo X-treme® Closed Cladding are solid boards in various widths for exterior applications. The boards are made from bamboo strips that have been compressed and thermally modified at 200°C. This unique Thermo-Density® process provides MOSO® Bamboo X-treme® with the highest durability class possible in the appropriate EU norms, increases the stability and density, and consequently the hardness. Furthermore, contrary to wood products, this material achieves fire resistance Class B-s1-d0¹⁰ (EN 13501-1) without impregnation with expensive and eco-damaging fire retardants. MOSO® Bamboo X-treme® Cladding with the Closed profile is developed to meet the highest fire requirements and is installed with a hidden screw. A closed profile is also available for fast and easy installation with the GRAD® system*. Like any tropical hardwood species, when exposed to outdoor conditions, Bamboo X-treme® will turn grey over time creating a very natural look.




Product Code	Snape	Finish	Surrace	End-matched	Length edges	Ena eages	Effective width (mm)	Dimensions (mm)
BO-DTHT537	Closed	Unfinished	Flat	Yes	R1	2 mm x 45°	52,5	1850x65x18
BO-DTHT536	Closed	Unfinished	Flat	Yes	R1	2 mm x 45°	87,5	1850x100x18
BO-DTHT530	Closed	Unfinished	Flat	Yes	R1	2 mm x 45°	124,5	1850x137x18
BO-DTHT538	Closed	Unfinished	Flat	Yes	R1	2 mm x 45°	142,5	1850x155x18
BO-DTHT538-2	Closed	Unfinished	Flat with false groove	Yes	R1	2 mm x 45°	142,5	1850x155x18

installation

- MOSO® guarantees the bamboo material and the mounting materials (screw) it supplies but does not guarantee the connection with other materials (such as sub frame joist/ battens). It is the responsibility of the installer to make sure the screw used matches such materials during the full lifetime of the product.
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust
- Full version available at: >www.moso-bamboo.com/closed
- For more information about the GRAD* system please see the product datasheet Bamboo X-treme® Outdoor Cladding GRAD® profile or check our website: ▶www.moso-bamboo.com/cladding/grad

technical characteristics and certifications

- Density: ± 1150 kg/m³
- Dimensional stability: length: + 0.1 %; width: + 0.9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534) Reaction to fire: Class B-s1-d0 (EN 13501-1) ¹⁾
- Flame spread index: Class A (ASTM E84) Thermal emittance: 0.81 (ASTM C1371) 2
- Solar Reflectance (SR): 0.32 (ASTM C1549) 2)
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980) 2)
- Modulus of Elasticity: 13565 N/mm² (mean value EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
- Biological durability: Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test / Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class O (EN 152)
 - Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi) Use Class: Class 4 (EN 335)
- CO2 neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/lca)
- . Environmental Product Declaration - EPD (EN 15804) (www.moso-bamboo.com/epd)
- FSC*: Products available with FSC* certification on request.
- Contribution LEED BD+C v4: MR 1, MR 2, MR 3 (FSC*), SS 7
- v2009: MR 6, MR 7 (FSC*) Contribution BREEAM: MAT 1, MAT 3 (FSC*), MAT 5 (HD)
- Guarantee: 25 years
- ⁹ Tested on Bamboo X-treme® Closed profile 137x18 mm, with ventilation space behind the boards. ²⁾Tested on 3 years weathered MOSO* Bamboo X-treme*.





Also available with FSC[®] certification.







Leisure Space Burgos Villacienzo, Burgos, Spain




Garden House by Wouter Bink (60 m²) Amersfoort, the Netherlands Public Elementary School "IKC"


(320 m²) Amsterdam, The Netherlands



MOSO[®] Bamboo X-treme[®] Outdoor Cladding Rebated & Trapezium profile

MOSO® Bamboo X-treme® Outdoor Cladding are solid boards in various widths for exterior applications. The boards are made from bamboo strips that have been compressed and thermally modified at 200°C. This unique Thermo-Density® process provides MOSO® Bamboo X-treme® with the highest durability class possible in the appropriate EU norms, increases the stability and density, and consequently the hardness. Furthermore, contrary to other wood products, this material can achieve fire resistance Class B-s1-d0¹ (EN 13501-1) without impregnation with expensive and eco-damaging fire retardants. Bamboo X-treme® Cladding with the Rebated profile is made for installation with MOSO® Fasteners (18 mm) and screws and the Trapezium profile is made for installation with screws. Like any tropical hardwood species, when exposed to outdoor conditions, MOSO® Bamboo X-treme® will turn grey over time creating a natural look.





11

Product Code	Shape	Finish	Surface	End- matched	Length edges	End edges	Effective width (mm)*	Dimensions (mm)
BO-DTHT500G	Rebated profile	Unfinished	Flat	Yes	R3	2 mm x 45°	125	1850x137x18
BO-DTHT505G	Rebated profile	Unfinished	Flat	Yes	R3	2 mm x 45°	63	1850x75x18
BO-DTHT510	Trapezium profile	Unfinished	Flat	Yes	R3	2 mm x 45°	132	1850x137x18
BO-DTHT515	Trapezium profile	Unfinished	Flat	Yes	R3	2 mm x 45°	70	1850x75x18
BO-DTHT525	Trapezium profile	Unfinished	Flat	No	R1	1.5 mm x 45°	70	1850x75x12

*) Effective width without gap between the boards, recommended gap 6 mm.

installation


- MOSO[®] guarantees the bamboo material and the mounting materials (fastener/screw) it supplies but does not guarantee the connection with other materials (such as sub frame joist/battens). It is the responsibility of the installer to make sure the used screw matches such materials during the full lifetime of the product.
- For installation with fasteners, the MOSO[®] Fasteners CLIP-SCREW-BX09 with screws and MOSO[®] Fasteners CLIP-BX09 without screws are available. More information about the MOSO[®] Fasteners can be found: **>www.moso-bamboo.com/x-treme/accessories**
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust.
- Full version available at: >www.moso-bamboo.com/x-treme/cladding

technical characteristics and certifications

- Density: ± 1150 kg/m³
- Dimensional stability: length: + 0.1 %; width: + 0.9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534)
- Reaction to fire: Class B-s1-d0 (EN 13501-1) ¹⁰
 Flame spread index: Class A (ASTM E84)
- Thermal emittance: 0.81 (ASTM C1371) ²⁰
- Solar Reflectance (SR): 0.32 (ASTM CI371)²²
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980)²⁾
- Modulus of Elasticity: 13565 N/mm² (mean value EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
- Biological durability: Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test / Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class 0 (EN 152)
 Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi)
- Use Class: Class 4 (EN 335)
- CO2 neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/lca)
- Environmental Product Declaration EPD (EN 15804) (www.moso-bamboo.com/epd)
- FSC®: Products available with FSC® certification on request.
- Contribution LEED BD+C v4: MR 1, MR 2, MR 3 (FSC*), SS 7

breeam


- v2009: MR 6, MR 7 (FSC*)
- Contribution BREEAM: MAT 1, MAT 3 (FSC*), MAT 5 (HD)
- Guarantee: 25 years
- $^{\rm D}$ Tested on 18 mm thickness, without gaps between boards, with ventilation space behind boards. 20 Tested on 3 years weathered MOSO* Bamboo X-treme*.





FSC





Briga Towers Penthouses & Apartments (10.000 m²) Netanya, Israel



Private residence Del Mar California, United States of America


Apartments De Drie Hofsteden (20.000 m) Courtrai, Belgium



MOSO[®] Bamboo X-treme[®] Outdoor Cladding Rhombus profile

MOSO® Bamboo X-treme® Rhombus Outdoor Cladding is a range of solid, Thermo-Density® exterior boards, made from compressed bamboo strips. A special, unique heat-treatment process at 200°C provides MOSO® Bamboo X-treme® with the highest durability class possible in the appropriate EU norms, increases the stability and density, and consequently the hardness. Furthermore, contrary to other wood products, this material can achieve fire resistance Class B-s1-d0¹⁰ (EN 13501-1) without impregnation with expensive and eco-damaging fire retardants. MOSO® Bamboo X-treme® Cladding with Rhombus profile can be fixed with MOSO® Fasteners (18 mm). Like any tropical hardwood species, when exposed to outdoor conditions, Bamboo X-treme® will turn grey over time creating a very natural look.


Triple Rhombus profile











13

Product Code	Shape	Finish	Surface	End-matched	Length edges	End edges	Effective width (mm)*	Dimensions (mm)
BO-DTHT520G	Triple Rhombus	Unfinished	Flat with 2 grooves	Yes	R1	2 mm x 45°	129	1850x137x20
BO-DTHT520G-2	Double Rhombus	Unfinished	Flat with 1 groove	Yes	R1	2 mm x 45°	129	1850x137x20
BO-DTHT520G-1	Single Rhombus	Unfinished	Flat	Yes	R1	2 mm x 45°	129	1850x137x20


*) Effective width without gap between the boards, recommended gap 6 mm.

installation

- MOSO[®] guarantees the bamboo material and the mounting materials (fastener/screw) it supplies but does not guarantee the connection with other materials (such as sub frame joist/battens). It is the responsibility of the installer to make sure the used screw matches such materials during the full lifetime of the product.
- For installation with fasteners, the MOSO[®] Fasteners CLIP-SCREW-BX09 with screws and MOSO[®] Fasteners CLIP-BX09 without screws are available. More information about the MOSO[®] Fasteners can be found: **>www.moso-bamboo.com/x-treme/accessories**
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust.
- Full version available at: >www.moso-bamboo.com/rhombus

technical characteristics and certifications

- Density: ± 1150 kg/m²
- Dimensional stability: length: + 0.1 %; width: + 0.9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534)
 Reaction to fire: Class B-s1-d0 (EN 13501-1) ¹⁾
- Reaction to fire: Class B-s1-d0 (EN 13501 Flame spread index: Class A (ASTM E84)
- Flame spread index. Class A (ASTM E64)
 Thermal emittance: 0.81 (ASTM C1371) ²⁾
- Solar Reflectance (SR): 0.32 (ASTM C1549)²⁾
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980) ²⁾
- Modulus of Elasticity: 13565 N/mm² (mean value EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
- Biological durability: Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test / Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class O (EN 152)
 Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi)
 - Use Class: Class 4 (EN 335)
 - CO₂ neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/Ica)
 - Environmental Product Declaration EPD (EN 15804) (www.moso-bamboo.com/epd)
 - FSC*: Products available with FSC* certification on request.
 - Contribution LEED BD+C v4: MR 1, MR 2, MR 3 (FSC*), SS 7
 - v2009: MR 6, MR 7 (FSC*)
 - Contribution BREEAM: MAT 1, MAT 3 (FSC[®]), MAT 5 (HD)
- Guarantee: 25 years
- ¹⁰ Tested on 18 mm thickness, without gaps between boards, with ventilation space behind boards. ²⁰ Tested on 3 years weathered MOSO[®] Bamboo X-treme[®].





Also available with





Luxurious garden with a touch of Bali Arnhem, the Netherlands



SPEEHUIS (10.000 m) Oisterwijk, the Netherlands

Oker Meeting Venue (125 m²) Schipluiden, the Netherlands



MOSO[®] Bamboo X-treme[®] Varibo Outdoor Cladding **GRAD**[®] profile

MOSO® Bamboo X-treme® GRAD® Cladding are solid boards in various widths for exterior applications. The boards are made from bamboo strips that have been compressed and thermally modified at 200°C. This unique Thermo-Density® process provides Bamboo X-treme® with the highest durability class possible in the appropriate EU norms, increases the stability and density, and consequently the hardness. MOSO® Bamboo X-treme® GRAD® Cladding is designed for installation on the GRAD® demountable and hidden installation system. Contrary to wood products, this material can achieve fire resistance without impregnation with expensive and eco-damaging fire retardants. The Closed profile achieves the fire resistance Class B-s1-d0 $^{
m D}$ (EN 13501-1) with the GRAD® installation system. Like any tropical hardwood species, when exposed to outdoor conditions, Bamboo X-treme® will turn grey over time creating a very natural look.



Product Code	Shape	Finish	Surface	End-matched	Length edges	End edges	Effective width (mm)*	Dimensions (mm)
BO-DTHT1180-BG	GRAD [®]	Unfinished	Flat	No	R3	2mm x 45°	45	1850x45x20
BO-DTHT1190-BG	GRAD [®]	Unfinished	Flat	No	R3	2mm x 45°	64	1850x64x20
BO-DTHT220-BG	GRAD [®]	Unfinished	Flat	No	R3	2mm x 45°	119	1850x119x20
BO-DTHT540-1-BG	GRAD*	Unfinished	Flat	Yes	R1	2mm x 45°	136	1850x136x20

*) Effective width without gap between the boards, distance after installation on GRAD® system 6 mm (except for Closed profile).

11

The mark of responsible forestry

FSC* C002063

installation

- Installation instructions are available from MOSO®
- www.moso-bamboo.com/cladding/grad
- MOSO[®] guarantees the bamboo material and the mounting materials (fastener/screw) it supplies but does not guarantee the connection with other materials (such as sub frame joist/battens). It is the responsibility of the installer to make sure the used installation method matches such materials during the full lifetime of the product.
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust
- Installation instructions for the GRAD® installation system are available from GRAD®: www.gradconcept.com

Elat Rail



CO₂ **E1** Also available with FSC[®] certification. нсно NEUTRAL Class 4 Class 1 EPD Class M FSC EN15804 EN335

technical characteristics and certifications

- Density: ± 1150 kg/m³
- Dimensional stability: length: + 0.1%; width: + 0.9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534)
- Reaction to fire: Class B-s1-d0 (EN 13501-1) Flame spread index: Class A (ASTM E84)
- . Thermal emittance: 0.81 (ASTM C1371) 2
- Solar Reflectance (SR): 0.32 (ASTM C1549) 2)
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980) 2)
- Modulus of Elasticity: 13565 N/mm² (mean value EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
- Biological durability: Class 1 (EN 350 / CEN/TS 15083-2), simulated graveyard test / Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class 0 (EN 152)
- Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi)
- Use Class: Class 4 (EN 335)
- CO2 neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/lca)
- Environmental Product Declaration EPD (EN 15804) (www.moso-bamboo.com/epd)
- FSC*: Products available with FSC* certification on request
- Contribution LEED BD+C v4: MR 1, MR 2, MR 3 (FSC*), SS 7
- v2009: MR 6, MR 7 (FSC*)
- Contribution BREEAM: MAT 1, MAT 3 (FSC*), MAT 5 (HD)
- Guarantee: 25 years

¹ Tested on 18 mm thickness, without gaps between boards, with ventilation space behind boards. ²⁾Tested on 3 years weathered MOSO® Bamboo X-treme®.







Event complex Oxygen La Défense (5500 m) Paris, France



Orientarium in the Municipal Zoological Garden (43.000 m) Łódź, Poland

Alfonso X residential building (5100 m) Madrid, Spain




MOSO[®] Bamboo X-treme[®] Outdoor Beams

A unique heat-treatment process at 200°C and compression of the bamboo strips to increase the density make the MOSO® Bamboo X-treme® material extremely durable and stable. This durability and stability, and the pre-profiled rounded edges, make MOSO® Bamboo X-treme® Beams ideal for use in outdoor furniture and facades. The elaborate manufacturing process provides MOSO® Bamboo X-treme® Outdoor Beams with the highest durability class possible in the applicable EU norms. As with tropical hardwoods, the colour of the material changes under the influence of wind, rain, frost and sunshine (UV-light). This results in a typical weathered natural grey-tone. Regular cleaning and maintenance with a finish/sealer protects the material against this weather related discolouration.

BO-DTHT2171-2-01 2000 x 80 x 40 mm

BO-DTHT2173-2-01 2000 x 40 x 40 mm





Product Code	Finish	Edges (also on ends)	Dimensions (mm)
BO-DTHT2170-2-01	Sikkens Cetol	R4	2000x115x40
BO-DTHT2175-2-01	Sikkens Cetol		2000x90x40
BO-DTHT2171-2-01	Sikkens Cetol	R4	2000x80x40
BO-DTHT2172-2-01	Sikkens Cetol	R4	2000x60x40
BO-DTHT2174-2-01	Sikkens Cetol	R4	2000x55x40
BO-DTHT2173-2-01	Sikkens Cetol		2000x40x40

Other dimensions, bevel and finish can be produced custom made

installation summary

- To allow natural shrink- and swell behaviour, install beams with a minimum of 4 mm distance. MOSO® Bamboo X-treme® Beams must be mechanically fixed, using screws/bolts. The fixing method depends on the application.
- Use stainless steel A2 screws/bolts.
- For all our standard size beams, except 40x40 mm, we advise a minimum of 2 screws per fixing point, 40x40 mm beams can be fixed with 1 screw per fixing point.
- Horizontal installation:

Class 1

- The number of fixing points is depending on the application and applicable load. · In general, a 2 meter beam should at least have 3 fixing points (2 on the sides and 1 connection in the middle).
- Vertical installation:
- · End of the beam should be angled (min. 15°) to improve water drainage
- Beams longer than 1 meter have to be fixed in at least 3 points.
- To avoid cracks caused by excessive water uptake, the (cut) ends of the beams must be treated with a sealer.
- Store in a cool and dry place away from direct sunlight, and protected from weather influences, dirt and dust
- Full version available at **>www.moso-bamboo.com/x-treme/beams**

E1

НСНО

Class 4

EN335

technical characteristics and certifications

- Density: ± 1150 kg/m
- Dimensional stability: length: + 0,1%; width + 0,9% (24 hours in water 20°C)
- Resistance to Indentation Brinell Hardness: ± 9.5 kg/mm² (average value EN 1534)
- Reaction to fire: Class B-s1-d0 " (EN 13501-1), applicable as a material test
- Flame spread index: Class A (ASTM E84) Thermal emittance: 0.81 (ASTM C1371) 2
- .
- Solar Reflectance (SR): 0.32 (ASTM C1549) 2)
- Solar Reflectance Index (SRI): Low 27, Medium 30, High 33 (ASTM E1980) 2) Modulus of Elasticity: 13565 N/mm² (mean value - EN 408)
- Bending strength: 54.4 N/mm² (characteristic value EN 408)
- Biological durability: Class 1 (EN 350 / CEN/TS 15083-2),
- simulated graveyard test Class 1 (EN 350 / CEN/TS 15083-1)
- Effectiveness against Blue Stain: Class 0 (EN 152)
- Effectiveness against European Termites: Class M (EN 350 / EN 117 Coptotermes gestroi) Use Class: Class 4 (EN 335)
- CO₂ neutral: LCA report TU Delft (ISO 14040/44) (www.moso-bamboo.com/lca)
- Environmental Product Declaration EPD (EN 15804) (www.moso-bamboo.com/epd)
- FSC®: Products available with FSC® certification on request. Contribution LEED BD+C - v4: MR 1, MR 2, MR 3 (FSC*), SS 7
- v2009 MR 6 MR 7 (ESC*)
- Contribution BREEAM: MAT 1, MAT 3 (FSC*), MAT 5 (HD)
- Guarantee: 10 years
- ⁹ Tested on panel material with 18 mm thickness, without gaps between boards, with ventilation space behind boards.
- ²⁾Tested on 3 years weathered MOSO* Bamboo X-treme*





Also available with FSC[®] certification. NEUTRAL

> The mark of responsible forestry FSC* C002063





MOSO[®] Bamboo X-treme[®] test results



The excellent performance of MOSO[®] Bamboo X-treme[®] has been extensively tested by acknowledged research institutes. Find a summary of the most important test results below. Full reports are available upon request. **Only MOSO[®] can ensure you have the original, unique Bamboo X-treme[®] product.** Other products that copy the original do not offer the same hardness and level of durability, dimensional stability and ecology. With a look-alike product, there is a large risk of claims after installation. Always ask for the original, certified MOSO[®] Bamboo X-treme[®] products!

D / ·		resistance aga	inst soft-rotting micro fung	i according to CEN/ ⁻		CEN/TS 15083 (ENV 807) / EN 350
Report code:	17.0083-C		Date: 29 March 2017		Page: 8/14	EN 350
the median ma references. Hau neither softwoo sapwood and E Based on the m treme, <i>Heat Tre</i> method describ MOSO Bamboo	ss loss or the te rdwoods are con d nor hardwood Beech. nass loss found eated Strand Wi bed in EN 350. o X-treme, Heat	st species is co mpared to Beec I a comparison i and the compar oven Bamboo, co Treated Strand	termined based on the x-va mpared to the median mass h, Softwoods are compare s made with both referenc ison to Beech and Pine, th an be classified in durabili Woven Bamboo, performa	ess loss of the Beech d to Pine. As Bambo e wood species Pine ne tested MOSO Bar ty class 1 when usin	or Pine po is e mboo X- ig the	class 1
Merbau. Little v	variance is found	I between the d	ifferent boards.			
SHF	₹₩	-	et treated strand woven ba / Basidiomycetes accordir		•	durability CEN/TS 15083 (EN 113) / EN 350
Report code:	17.0083-B		Date: 29 March 2017		Page: 8/14	class 1
fungus resultin implies that, wi	g in the highest hen using the El	median mass lo N 350 to determ	lculated based on the mas oss. For all fungi the mass ine the durability, MOSO ied in durability class 1.	loss is less than 5%	. This	
fungus resultin implies that, wh	g in the highest hen using the El <i>I Woven Bambo</i>	median mass lo N 350 to determ lo can be classif	oss. For all fungi the mass ine the durability, MOSO	loss is less than 5% Bamboo X-treme, <i>H</i>	. This leat	resistance against b
fungus resultin implies that, wi	g in the highest hen using the El <i>I Woven Bambo</i>	median mass lo N 350 to determ to can be classif	oss. For all fungi the mass ine the durability, MOSO ied in durability class 1.	loss is less than 5% Bamboo X-treme, <i>H</i>	. This leat	

susceptibility of this Heat Treated Strand Woven Bamboo towards blue stain is very low.

harder and more durable than almost any other hardwood

durability class

class 1


(EN 350 (CEN/TS 15083-2 / CEN/TS 15083-1)



average brinell hardness

± 9.5 kg/mm²

(EN 1534)



	Classific	ation Dural	bility Class		
Use Class	1. very durable	2. durable	3. moderately durable	4. slightly durable	5. not durable
1 interior	0	0	0	0	0
2 moist interior	0	0	0	(0)	(0)
3 exterior, above ground	0	0	(0)	(0)-(x)	(0)-(x)
4 ground contact / fresh water	ο	(0)	(x)	х	×
5 salt water	*	(x)	(x)	х	×

0 Natural durability sufficient.

(0) Natural durability normally sufficient, but for certain end uses treatment may be advisable.

Natural durability may be sufficient, but depending on end use, preservative treatment may be necessary. (0)-(x)

(x) Preservative treatment is normally advisable.

Preservative treatment necessary x

Natural durability of Bamboo X-treme® not tested in salt water.



	Classification ASTM E84	
Classification	Flame Spread Index	Smoke Developed Index
А	0 - 25	0 - 450
В	26 - 75	0 - 450
С	76 - 200	0 - 450

	ootprint (kg Co uring product li	• •			tprint (kg CO2 ² after inciner	
CSC*	PRODUCTION**	TRANSPORT	TOTAL	CSC RELEASED	END OF LIFE***	TOTAL
-31.84	24.457	5.198	-2.185	31.84	-6.003	23,65

In line with circular economy principles, MOSO* always recommends trying to upcycle or repurpose your bamboo products at the end of their life and looks at incineration as a worst case scenario. In 2021 MOSO* fully investigated bamboo incineration for green energy production together with Renewi (Dutch waste company) and confirmed that MOSO* Bamboo Products are classified as B grade wood (in the Netherlands) and can be safely burnt in an incineration plant fo energy recovery. nlant for



The life cycle and the carbon footprint of MOSO* Products are evaluated according to ISO 14040/44. For more information: www.moso-bamboo.com/Ica The full report is available on request. Confidentia1 - This information is the property of Moso International BV, Zwaag, the Netherlands. Any use or reproduction without permission will be prosecuted.



Author: **uthor:** IBE experts in sustainability r. Ir. Pablo van der Lugt, Sustainability Manager Moso International B.V. . Nicholson, Sustainability Specialist Moso International B.V.

durability

EN 350 (CEN/TS 15083-2 / CEN/TS 15083-1)

class 1

use/risk class EN 335

class 4

EN 13501-1

class B-s1-d0

reaction to fire

(FSI 25 / SDI 45)

ASTM E84 class A WUI approved CAN/ULC-S102

carbon footprint

ISO 14040/44

CO₂ neutral



the sustainability of Bamboo X-treme®


MOSO® Bamboo X-treme® offers clear sustainable advantages and is even proven to be CO₂ neutral during the product lifespan! The inclusion of Bamboo X-treme® contributes to a higher LEED, BREEAM, Green Star, HQE and DGNB certification score for green building projects. That's one of the reasons why you can find MOSO® Bamboo X-treme® and other MOSO® Products in many sustainable reference projects all over the world.

carbon footprint

MOSO® Bamboo X-treme®: CO2 neutral during the product lifespan*


MOSO® has conducted several LCA studies, including carbon footprint studies, together with Delft University of Technology (TU Delft) and NIBE (LCA experts). The 2015 LCA report, available at www.moso-bamboo.com/lca, was the first of its kind and resulted in many new findings about the carbon footprint of bamboo products. The environmental impact of MOSO® Bamboo Products, excluding the carbon sequestration effect, has also been published in 2016 and updated in 2022 in an official Environmental Product Declaration (EPD) following EN 15804 (www.moso-bamboo.com/epd).

*) This includes the CO₂ (biogenic carbon - EN 16449) stored in the product.



Office Hesselink Koffie (Coffee Roastery)


BREEAM - Winterswijk, the Netherlands



unsurpassed growing speed

bamboo: the fastest growing plant in the world

Because of the fast growth, Moso bamboo is managed as an agricultural crop: the annual harvest of the 4 to 5-year-old stems – compared to 60-80 years for tropical hardwood! – provides a steady annual income to farmers and stimulates the bamboo plant to reproduce even faster. Therefore, by default, no deforestation occurs with production of MOSO® Bamboo X-treme®, while large amounts of CO₂ are captured in the bamboo forests and products (www.inbar.int/understanding-bamboos-climate-change-potential).





carbon storage in bamboo

biobased materials act as CO2 sinks

Through photosynthesis, plants absorb carbon dioxide (CO₂) and convert it into glucose (building block for biomass) and oxygen. The CO₂ is stored in the material for the lifetime of the product, and even longer if the product is recycled into new, durable products. Due to the fast growth – and related high yields - Moso bamboo locks far more CO₂ in durable products compared to wood species. The locked amount of CO₂ can be calculated rather simply by looking at the density of the material and taking into account the biobased content. For example, Bamboo X-treme[®] locks almost 1.660 kg CO₂ per m³ of bamboo, which is the equivalent of the CO₂ emissions of 14.000 km driven by a mid-range car.



Check out how bamboo can save the world at: www.moso-bamboo.com/sustainability



Notiz Hotel NHL Stenden - Green Key Award Gold (1200 m²) Leeuwarden, the Netherlands



Contributes to a higher score for green building projects worldwide



Alfonso X residential building - ASPRIMA-SIMA Award (5100 m) Madrid, Spain

MOSO[®] Bamboo X-treme[®] Outdoor Cladding user information

appearance and colour

MOSO* Bamboo X-treme* is a natural product, which can vary in colour, grain and appearance. Colour will change over time depending on the maintenance schedule. The boards have a brown to dark brown colour when installed, which turns into a lighter caramel colour several weeks after installation. Without further maintenance the colour gets greyish relatively fast (similar to most other wood species).

If a brown colour is preferred, maintenance should be done with an exterior finish. For further details see the installation instructions.

MOSO® Bamboo X-treme® shows similarity to other hardwoods in grain and structure. The characteristic bamboo nodes however can still be recognised and provide the product with a special and lively look.

normal phenomena

N-2022-

22

Cracks on the surface and on the ends of the boards can occur due to the different drying characteristics of the surface and board ends. This does not affect the stability or durability of the board.


The surface side of the boards will become rougher over time and can form (small) splinters as a result of continuous water absorption and desorption due to dry and wet weather periods. Dimensional change or cupping of the boards can occur after installation. These phenomena are normal for most hardwood species and MOSO® Bamboo X-treme®.

After installation, there might be some bleeding or leaching of colour from the bamboo material when it gets wet, e.g. when it rains. This possible bleeding is typical for wood and will disappear over time. The brownish liquid can easily be cleaned from the Bamboo X-treme[®] material, however controlled water drainage and prevention of splash water is required to prevent any discoloration of surrounding or underlying building components.

Luxurious garden Cladding installed with Grad's invisible rail installation system - Arnhem, the Netherlands



Endless possibilities with **MOSO® Bamboo** X-treme®



Grotius residential towers Closed cladding installed at the crown of the buildings - The Hague, the Netherlands

Since 2008 over 6 million n² decking and cladding installed in more than 60 countries

Jumbo Head office Photo taken 5 years after installation (2.500 m²) Schiedam, The Netherlands



Public Elementary School "IKC" Photo taken 5 years after installation - (320 m²) Amsterdam, The Netherlands



Oxygen La Défense Photo taken 4 years after installation (5500 m) Paris, France

Office Hesselink (Coffee Roastery)

(200 m² Varibo) Winterswijk, Netherlands



Housing project De Krijgsman (320 m² Closed) Muiden, Netherlands

 Moke Architects

Leisure Space Burgos

(120 m²) Villacienzo, Burgos, Spain





More information about MOSO[®] Bamboo X-treme[®] Cladding at: www.moso-bamboo.com/bamboo-cladding

Headquarters:

Moso International B.V. Adam Smithweg 2 1689 ZW Zwaag the Netherlands T +31 (0)229 265 732 info@moso.eu

Sub-Saharan Africa:

Moso Africa Pty. Ltd. 7 Glosderry Road Kenilworth 7708 Cape Town South Africa T +27 2167 11214 contact@moso-bamboo.co.za

www.moso-bamboo.com

Spain, France, Portugal, North Africa, Latin America and Middle East:

Moso Europe S.L.U. C/ Pau Claris, 83 - Principal 2ª 08010 Barcelona Spain T +34 (0)93 574 9610 contact@moso.eu

Gulf Cooperation Council (GCC) Countries:

Moso Middle East LLC Office G-058, Techno Hub 1, Silicon Oasis, Dubai United Arab Emirates T +971 4 258 9337 contact@moso-bamboo.ae North America:

Moso North America Inc. PO Box 793, 1741 Valley Forge Road Worcester, PA 19490 United States of America T +1 855 343 8444 info@moso-bamboo.com

Italy:

Moso Italia S.R.L Via Antonio Locatelli 86 20853 Biassono (MB) Italy T +39 (0)39 900 5440 mosoitalia@moso.eu



