

## **SRT-19**



# STOPS RUST<sup>®</sup> RUST INHIBITOR SPRAY

## **DESCRIPTION AND USES**

Rust-Oleum<sup>®</sup> Stops Rust<sup>®</sup> Rust Inhibitor is a clear coating that protects untreated, bare metal surfaces against moisture and other corrosive elements. It is suitable for use on garden tools, bicycles, metal sporting equipment, lawn equipment, iron railings and other metal surfaces.

# PRODUCT

SKU DESCRIPTION (10.25 oz. Aerosol)

224284 Rust Inhibitor

## **PRODUCT APPLICATION**

#### SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove all loose rust, scale, and previous coatings with a wire brush, scraper, or Rust-Oleum Rust Stripper.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to <u>www.epa.gov/lead</u>

# **PRODUCT APPLICATION (cont.)**

#### PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between  $50-90^{\circ}F$  (10- $32^{\circ}C$ ) and humidity is below 85% to ensure efficient use of the product. Do not apply to an area that, when heated, will exceed  $120^{\circ}F$  (49°C). Avoid spraying in windy, dusty conditions. Cover surrounding area to protect from spray mist.

### APPLICATION

Shake can well before using and often during use. Hold can upright 12-16" from the surface and apply a light, thin, even coat to cover the surface. Additional coats provide increased protection. Wipe off excess with a clean cloth if the coating is too heavy. Re-apply every 1-2 years for indoor uses and every 6 months for outdoor uses.

#### PAINTING

If surfaces are to be painted in the future, remove Rust Inhibitor from the surface with a solvent such as acetone or mineral spirits prior to painting.

# PHYSICAL PROPERTIES

	RUST INHIBITOR
Composition	Petroleum Distillates
Fill Weight	10.25 Oz.
VOC	325 g/l
Shelf Life	5 Years
Flash Point	-156°F (-104°C)
Safety Information	For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation 11 Hawthorn Parkway Vernon Hills, Illinois 60061

Phone: 877·385·8155 www.rustoleum.com