



ACHILLES CORPORATION

22 Daikyo-cho, Shinjuku-Ku,
Tokyo, 160-8885 Japan
Tel: +81-3-3225-2184
Fax: +81-3-3351-6963



OCT.2014

MEASURED VALUE

ITEM
NH3737CR

SUPPORT FABRIC	Type		polyamide
	Yarn		470dtex
	Contexture (/inch)	 wp × wf	37 × 37
COATING	outside coating		CSM※
	inside coating		polychloroprene
THICKNESS		mm	0.77
WIDTH		mm	1230

PHYSICAL PROPERTY

(STANDARDS)

(UNITS)

NH3737CR

Total mass per unit area	ISO 2286-2	g/m ²	1070
Tensile strength	ISO 1421	daN/5cm	warp 233
			weft 214
Tear Resistance	JIS K 6404-4	daN	warp 16
	Single-Tang		weft 17
Adhesion	ISO 2411	daN/cm	≥2
	ISO 4675		
Low-temperature resistance	bend test	°C	-30°C pass
Determination of Weathering test	weather meter		
	1000h		none crack

The value is measurement value, not guarantee value.

※CSM=Chlorosulfonated Polyethylene