

ProGlas 4:1 Slow Curing Agent



4:1 Slow CURING AGENT

Description:

ProGlas 4:1 Slow is a modified aliphatic amine, light colored, low viscosity epoxy curing agent. Use with ProGlas 1300 series Epoxy Resin systems.

Features:

- Reduced vapor pressure
- Low mixed viscosity
- Low shrinkage
- Good Chemical resistance
- High clarity

Uses:

- Yacht/Boat Construction
- High Performance manufactured parts
- RTM/VARTM/Vacuum bagging
- Hand Lay-up application (fast wet out)
- Electrical Potting
- Tooling compounds
- Metal and plastics adhesive

TYPICAL PROPERTIES 25:100 weight

Uncured Curing Agent

Flash Point, ASTM D-3278, °F	>200
Mix ratio, ProGlas 1300 series	25:100
Gel Time 77° F	30-35 minutes (ProGlas 1300)

Handling Properties at 77 °F

Initial Viscosity	495 cps (ProGlas 1300)
Pot Life at 77° F	30-35 minutes (ProGlas 1300)

The information herein is general information designed to assist customers in determining whether ProGlas products are suitable to their applications. ProGlas products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. **Nothing herein constitute any warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Fiberlay Inc. - 24 S Idaho St Seattle WA, 98134 (800)942-0660

ProGlas 4:1 Slow Curing Agent

Cured Resin¹

<u>Test</u>	PROGLAS 1300 <u>Value</u>
Heat deflection temperature, °F	143.1
Tensile strength, psi	11947.6
Flexural strength, psi	19912.7
Flexural modulus, psi	526263.7
Barcol Hardnes (934-1)	41

Handling & Storage

All epoxy Resin/ Curing Agents, should be kept in tightly closed containers in a cool, dry place. Product will absorb moisture and carbon dioxide which may affect viscosity or create foaming when reacted with Resin/Curing Agents. This product will have a minimum shelf life of one year if properly stored in unopened containers.

ProGlas 4:1 Slow Curing Agent is available in 55-Gallon metal drums.

To ensure maximum stability and maintain optimum resin properties, resins should be stored in closed containers at temperatures below 75°F and away from heat sources and sunlight. All storage areas and containers should conform to local fire and building codes. Inventory levels should be kept to a reasonable min with first-in, first-out stock rotation.

Safety

Read and understand the Material Safety Data Sheet before working with this product

The information herein is general information designed to assist customers in determining whether ProGlas products are suitable to their applications. ProGlas products are intended for sale to industrial and commercial customers. We require customers to inspect and test our products before use and to satisfy themselves as to contents and suitability for their specific applications. **Nothing herein constitute any warranty express or implied, including any warranty of merchantability or fitness for a particular purpose**, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is limited to replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.

Fiberlay Inc. - 24 S Idaho St Seattle WA, 98134 (800)942-0660