Palmetto Pool Base is carefully formulated to give more coverage for each bag, good value, and a quality product which spreads easily, especially on walls and slopes. It is important to follow the mixing instructions for best results.

## Palmetto Pool Base Mixing Directions --on the Back of every Bag

- 1. Start with  $6\frac{1}{2}$  8 gallons of water in the mixer. (6  $\frac{1}{2}$  for stiff mix, up to 8 gallons maximum)
- 2. Turn the mixer on and "cut in" (gradually pour) one bag of Palmetto Pool Base. (1 Bag)
- 3. Mix for 30 seconds. Stop.
- 4. Add remaining water, if needed. Mix for no more than 1 minute.
  - Mix 1 bag at the time for Palmetto Pool Base.
  - For "stiffer mixture" (for slopes and walls) start with 6 ½ gallons of water.
  - If you add the rest of the water, <u>up to 8 gallons</u>, Do NOT mix for more than one minute.
  - Like pancake batter, if you mix too much, the mixture will become runny!

Competitive pre-mix brands use the following ratios of bag mix and water:

- 2 bags of mix with 5 gallons of water
- 1 bag of mix with 4-5 gallons of water
- 1 bag of mix with 4-6 gallons of water

Remember, Palmetto Pool Base calls for 1 bag of mix and <u>6.5-8 gallons of water</u> -- allows your product to go farther for more coverage and good value.

1. What if a customer uses 5 gallons of water instead of following Palmetto directions? This is not enough water and the mix will crumble.

## 2. Why the range of 6 $\frac{1}{2}$ –8 gallons water with Palmetto Pool Base?

A pool builder may use 6.5 gallons of water for a stiffer mix for pool walls and slopes. 8 gallons of water is the max amount to be used with a bag of Palmetto Pool Base.

3. What if a customer doesn't measure the water OR dumps in 8 gallons of water, then opens additional bag(s) of Palmetto Pool Base and free-pours it in to try to thicken the mix? This will make a runny mess, stirred too much.