

# **Belt Repair-Kit**



Fast application without tools Highly elastic, wear-resistant, impact- and abrasion resistant High resistance to chemicals and pressure

WEICON Belt Repair-Kit is a 2-component polyurethane system for the fast repair and coating of rubber surfaces.

It has a high curing speed, high elasticity and wear resistance, is impact-resistant and abrasion-resistant, and has a particularly high tear resistance.

Thanks to its high mechanical strength, it is suitable especially for repairs on rubber and metal components, which are exposed to impacts, abrasion or vibrations.

The Belt Repair- Kit offers fast and easy processability. After just 30 minutes, the treated surface can already be sanded and smoothed.

The system is suitable for various applications, such as the repair and coating of conveyor belts, the repair of rubber coatings, for use as flexible wear protection, and for the fast repair of worn-out rubber surfaces.

In addition to the polyurethane system, the set comprises a primer for surface pre-treatment, and a spatula to spread the compound evenly.

In order to cover a broader application range, in addition to the classic 500 g working package, which needs to be mixed by hand, the product is also available as easy-to-use 540 g double cartridge.

## **Technical Data**

Polyurea
black
10:100
1,1 g/cm <sup>3</sup>
20 min.
6 - 8 h
24 h

Shore hardness A	85
Elongation at break (DIN EN ISO 527)	470 %
Tensile strength ISO 527 max.	7,8 N/mm²
Strength-E-Module (DIN EN ISO 527)	9,6 N/mm²
Resistance to further tearing	31 kN/m
average tensile shear strength with Primer G according to DIN EN 1465 on	
Steel sand blasted	8 N/mm²
Sandblasted stainless steel	8 N/mm²
Sand-blasted Aluminium	7 N/mm²
Galvanized steel	4 N/mm²
Swelling in water (7 days)	<1,5 %
Temperature resistance (wet)	-60 to +60 °C
Temperature resistance (dry)	-60 to +100 °C
Technical data Primer G	
Base	Urethane
Colour	yellowish, transparent
Mixing ratio by weight resin/hardener	32:1
Viscosity at +20°C (+68°F) according to Brookfield	40 mPa·s
Pot life at +20°C (+68°F)	15 min.
Overcoating with polyurethane	after 30 to 60 min.

Information about surface pre-treatment and processing can be found in the manual.

### Storage

Store WEICON Urethane at room temperature (+20°C) in a dry place. Unopened containers can be stored for at least 6 months after delivery at temperatures from +18°C to +25°C. Opened containers must be used within 3 months.

# Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

## Available sizes:

10851005	Belt Repair-Kit 550 work package in a set
10851015	Belt Repair-Kit 590 double cartridge in a set

#### Accessories:

10653490	Dispenser 2 Comp., 10:1 490 m
10953001	Processing Spatula,
10953003	Processing Spatula,
10953020	Contour Spatula Flexy,
13955050	Primer Applicator,

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de www.weicon.de

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za www.weicon.co.za WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae www.weicon.ae

WEICON South East Asia Pte Ltd Singapore phone (+65) 6710 7671 info@weicon.com.sg www.weicon.com.sg WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca www.weicon.ca

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz www.weicon.cz WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr www.weicon.com.tr

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es www.weicon.es WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com www.weicon.com.ro

WEICON Italia S.r.I. Italy phone (+39) 0102924871 info@weicon.it www.weicon.it