

# Flex 310 M® 2 K MS-Polymer



## fast-curing

The WEICON Flex 310 M 2 K adhesive and sealant is very strong, non-corrosive, overpaintable (wet in wet), sandable, weather-resistant, resistant to UV rays and is free of silicone, isocyanate, or solvents.

Flex 310 M 2 K is a strong 2-component system on a hybrid polymer basis which enables fullsurface bonding of larger parts and which can be used to fill gaps of up to 10 millimetres. It is suitable for the bonding of almost all materials such as metal and many plastics.

WEICON Flex 310 M 2 K can be used in metal construction, tank and apparatus engineering, machine and system construction, in the furniture industry, in ventilation and air conditioning systems, in the electrical industry, yacht and boat construction and in all applications where silicones or products containing silicones are not suitable.

## Technical Data

Composition	2-C-hybrid-Polymer
density	1,40 g/cm <sup>3</sup>
Viscosity adhesive	solid paste
Processing temperatur	+5 to +35 °C
Pot-life (at +23°C and 50% rel. Humidity)	5 min.
Processing time	10 min.
Set to load bearing	60 min.
Cure type	chemical polymerisation
Volume change (DIN 52451)	1 %
Gap filling up to max.	10 mm

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Shelf life (+5°C to +25°C / +41°F to +77°F)	12 months
Shore A hardness (DIN 5355 / ASTM D 224) ± 5	40
Elongation at break (DIN 53504/ASTM D 2240) ± 5	350 %
Tensile strength of pure adhesive and sealant	2,2 N/mm <sup>2</sup>
Average tensile shear strength (DIN 53283 / ASTM D 12)	1,3 N/mm <sup>2</sup>
Building material category (DIN 412)	B 2
Temperature resistance	-40 to +90 °C

\*Measured at 50% relative air humidity and +23°C

## Surface pre-treatment

The surfaces must be clean and grease-free. Many surface contaminants, e.g. oil, dust and dirt, can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend WEICON Cleaner Spray S; WEICON Sealant and Adhesive Remover is suitable for removing old paint or adhesive residues. Most materials can be bonded well to themselves and among each other. For certain materials or extreme requirements, we recommend the use of an adhesion agent (primer). Detailed information on this subject is contained in the Primer selection table. A mechanical surface pretreatment, e.g. sanding or sand-blasting, can considerably improve the adhesion.

## Processing

The special coax cartridge with the included static mixer can be used with the help of commercial cartridge guns. We recommend the use of the WEICON Cartridge Gun "special", art. No. 13250002. Reject the first 5 – 8 cm of the dosed bead. The adhesive may be applied to only one of the surfaces to be bonded.

## Storage

When unopened and stored in a normal climate (+23°C and 50 % rel. humidity), WEICON elastic one-component adhesives and sealants have a shelf life of 12 months.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

13305250 Flex 310 M® 2 K MS-Polymer 250 ml grey

## Accessories:

10604025 Mould Release Agent Liquid F 1000, 250 ml  
 11202400 Sealant and Adhesive Remover, 400 ml  
 11207400 Surface Cleaner, 400 ml  
 11850200 Hand Protective Foam, 200 ml  
 13250001 Cartridge Gun,  
 13250002 Cartridge Gun Special,

WEICON GmbH & Co. KG  
 (Headquarters)  
 Germany  
 phone +49 (0) 251 9322 0  
 info@weicon.de

WEICON Middle East L.L.C.  
 United Arab Emirates  
 phone +971 4 880 25 05  
 info@weicon.ae

WEICON Inc.  
 Canada  
 phone +1 877 620 8889  
 info@weicon.ca  
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
 Turkey  
 phone +90 (0) 212 465 33 65  
 info@weicon.com.tr  
 www.weicon.com.tr

WEICON Romania SRL  
 Romania  
 phone +40 (0) 3 65 730 763  
 office@weicon.com

WEICON SA (Pty) Ltd  
 South Africa  
 phone +27 (0) 21 709 0088  
 info@weicon.co.za

WEICON South East Asia Pte Ltd  
 Singapore  
 phone (+65) 6710 7671  
 info@weicon.com.sg

WEICON Czech Republic s.r.o.  
 Czech Republic  
 phone +42 (0) 417 533 013  
 info@weiconcz.cz

WEICON Ibérica S.L.  
 Spain  
 phone +34 (0) 914 7997 34  
 info@weicon.es

## Technical Datasheet

Create Date: 17.11.2017 - Seite 2/2

13250009	Compressed Air Cartridge Gun,
13309997	Special Mixing Nozzle,
13550125	Primer M 100, 250 ml
13550225	Primer K 200, 250 ml
13550325	Primer S 300, 250 ml
13550425	Primer P 400, 250 ml
13559500	Smoothing Agent,

---

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

---

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weiconcz.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es