

# Isolation Spray



use till the mixing ball can be heard. Spray on evenly at room temperature (approx. +20 °C) and at about 25 cm distance from surface.

## Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding +50 °C.

## Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Available sizes:

11551400 Isolation Spray 400 ml

## Dielectric Strength Resistant Crystal clear

WEICON Isolation Spray is a clear isolation and covering paint based on alkyd resin. It “hardens” into a flexible and resistant film, with excellent adhesion to most common surfaces such as metal, glass, plastic, wood, etc. Isolation Spray is resistant to UV rays, acids, oil and alkalis, it is moisture and weatherproof and is especially characterized by its high dielectric strength.

The spray serves as a protective coating on electrical connections, switches, switchboards, electronic components and electric coils, as universal sealing in electrical engineering or for repairing isolations on electric motors, windings and frames.

## Technical Data

Composition	Modified Acrylic Resin
Odour	solvent
Features	high dielectric strength, material compatible
density	1,0 g/cm <sup>3</sup>
Specific surface resistance DIN EN 62631	7,59 · 10 <sup>14</sup> Ω
Dielectric strength (DIN EN 60243-1) (20°C)	67,8 kV/mm
Thermal conductivity 20 °C (DIN EN ISO 821)	0,215 W/m·K
Storage stability	24 months
Effectiveness	2-3 m <sup>2</sup>
Colour	transparent
Dust dry after	15 min.
Temperature resistance	-40 (-40 °F) to +120 (+248 °F) °C
Solids content approx.	50 %
Final hardness after	2 h
Cross cutting DIN 53151/ ISO 2409	Gt 0-1 on steel

## Processing

Clean and degrease surfaces with WEICON Surface Cleaner. The surface should be dry, free of dust and grease. Shake can before

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG  
(Headquarters)  
Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca  
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr  
www.weicon.com.tr

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com  
www.weicon.com.ro

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz  
www.weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es  
www.weicon.es

WEICON Italia S.r.l.  
Italy  
phone (+39) 0102924871  
info@weicon.it  
www.weicon.it