

# Mould Release Agent Wax P 500


**Safety and health**

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

**Available sizes:**

10604500 Mould Release Agent Wax P 500 500 g  
 10604515 Mould Release Agent Wax P 500 150 g

**Accessories:**

10953001 Processing Spatula, short  
 11207400 Surface Cleaner, 400 ml

**solvent-containing**

Wax P 500 as a release agent on a waxy basis for epoxy resins and polyurethanes. It is especially suitable for release processes from rough and/or porous surfaces.

**Technical Data**

Composition	Wax, solvent-containing
Consistency	pasty
Density at +20°C (+68°F)	0,8 g/cm <sup>3</sup>
Consumption	50 to 150 ml/m <sup>2</sup>
Processing temperatur	+15 to +25 °C
Application temperature	to +50 °C
Colour	white
IMPA-Code	81 29 64/79

**Surface pre-treatment**

The surface to be treated must be clean, dry and free of grease (e.g. cleaning and degreasing with WEICON Surface Cleaner).

**Processing**

Apply Mould Release Agent Wax with a fibre-free pulp cloth or with a lint-free paper cloth and polish uniformly. Repeat the process in case of new moulds or highly absorbing surfaces. Excessive Mould Release Agent or residues can be removed with WEICON Surface Cleaner without leaving residual layers.

**Note**

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON GmbH & Co. KG  
 (Headquarters)  
 Germany  
 phone +49 (0) 251 9322 0  
 info@weicon.de

WEICON Middle East L.L.C.  
 United Arab Emirates  
 phone +971 4 880 25 05  
 info@weicon.ae

WEICON Inc.  
 Canada  
 phone +1 877 620 8889  
 info@weicon.ca  
 www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.  
 Turkey  
 phone +90 (0) 212 465 33 65  
 info@weicon.com.tr  
 www.weicon.com.tr

WEICON Romania SRL  
 Romania  
 phone +40 (0) 3 65 730 763  
 office@weicon.com

WEICON SA (Pty) Ltd  
 South Africa  
 phone +27 (0) 21 709 0088  
 info@weicon.co.za

WEICON South East Asia Pte Ltd  
 Singapore  
 phone (+65) 6710 7671  
 info@weicon.com.sg

WEICON Czech Republic s.r.o.  
 Czech Republic  
 phone +42 (0) 417 533 013  
 info@weiconcz.cz

WEICON Ibérica S.L.  
 Spain  
 phone +34 (0) 914 7997 34  
 info@weicon.es