

WEICON UW Epoxy Resin



Paste-like, mineral-filled, cures under water as well as on wet and damp surfaces

WEICON UW is a 2-component epoxy resin, which is fast-curing and especially suitable for repair works, for example on pipes, pumps, tanks and containers.

Due to its special formula, WEICON UW shows very good adhesion in underwater applications to different materials and can therefore be used in the entire marine and shipping sector, in sewage systems and wherever wetness and moisture can otherwise cause adhesive problems.

Technical Data

Composition	Epoxy resin mineral-filled
Specific Properties	pasty, cures even under water
Colour after curing	white
Mixing ratio by weight resin/hardener	100:100
Density of the mixture (200g preparation)	1,35 g/cm ³
Viscosity of the mixture	670.000 mPa·s
Consumption at a coating thickness of 1,0 mm	1,35 kg/m ²
Maximum layer thickness for each working step	12 mm
Pot life at +20°C (+68°F) 200g preparation	20 min.
Curing time mechanical loads	4 h
Final hardness after	24 h
Mean strength at +25°C (+77°F) acc. to DIN EN 1465/ASTM D 1002:	
Pressure	60 Mpa
Bending	38 Mpa
E-Modul	2.000 - 2.500 Mpa
Shore D (ATSM D 1706)	70
Shrinkage	0,02 %
Tg nach Aushärtung bei Raumtemperatur	42,8 Tg (°C)
Tg nach Tempern (bei 120 °C)	36,4 Tg (°C)

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Thermoforming resistance	+50 °C
Temperature resistance	-35 to +120 °C
Resistivity	1,64 * 10 ¹¹ Ωm
Thermal diffusivity (23°C)	0,182 mm ² /s
Thermal conductivity	0,28 W/m·K
Specific heat capacity	1,178 J/(g·K)
ISSA-Code	75.509.24/25
IMPA-Code	812935/36

Information about surface pre-treatment and processing can be found in the manual.

Storage

Store WEICON Plastic Metal at room temperature (but up to max. +25°C) in a dry place. Unopened containers can be stored for 18 months at temperatures from +18 to +28°C (Epoxy Resin Putty max. 3 years). Opened containers should be used within 6 months.

Safety and health

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

10440002	WEICON UW Epoxy Resin 0,2 kg
10440005	WEICON UW Epoxy Resin 0.5 kg
10440020	WEICON UW Epoxy Resin 2.0 kg

Accessories:

10850005	Glass Fibre Cloth Tape, 50 mm x 1 m
10953001	Processing Spatula, short
10953003	Processing Spatula, long
10953020	Contour Spatula Flexy,

WEICON GmbH & Co. KG
(Headquarters)
Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca
www.weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr
www.weicon.com.tr

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com
www.weicon.com.ro

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
phone (+65) 6710 7671
info@weicon.com.sg

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz
www.weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es
www.weicon.es

WEICON Italia S.r.l.
Italy
phone (+39) 0102924871
info@weicon.it
www.weicon.it