

Test Report

No.: T31620270508SC

Date: NOV 14, 2016 Page 1 of 2

CAFELAT LTD FLAT C, 4/F, CHEN YIP INDUSTRIAL BUILDING,NO. 5 LAI YIP STREET,KWUN TONG,HONG KONG

The following samples were submitted and identified on behalf of the client as:

MODERN LEVER PORTAFILTER GASKET

	hence Article 3 of European Regulation No. 1935/2004. Silicone rubber – Overall migration	PASS
	Council of Europe Resolution AP (2004) 5 and	
,	Test Requested	Conclusion
Result Summary :		
Test Method & Results :	Please refer to next page(s).	
Test Requested :	Please refer to the result summary.	
SGS Case No. Manufacturer Country of Origin Sample Receiving Date Test Performing Date	 CA316202708649 CAFELAT CHINA NOV 04, 2016 NOV 04 – 14, 2016 	

Signed for and on behalf of SGS Hong Kong Ltd.

Che Wai Leuk, Jerry Technical Manager



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sos.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sos.com/en/Terms-and-Conditions.aspx Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document is enpoduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



Test Report

:

No.: T31620270508SC

Date: NOV 14, 2016 Page 2 of 2

Test Results

Council of Europe Resolution AP (2004) 5

Silicone rubber - Overall migration

Method : With reference to EN 1186-1:2002 for selection of conditions and test methods (3rd migration); EN 1186-3:2002 aqueous food simulants by total immersion method

Simulant Used	Test Condition	Result (mg/dm ²) 1	Reporting Limit (mg/dm ²)	Permissible Limit (mg/dm ²)
20% Ethanol (V/V) Aqueous Solution	2 hours at 70℃	ND	3.0	10
Comment		PASS		

Sample Description :

1. Blue Silicone Rubber

- Note : 1. mg/dm^2 = milligram per square decimeter
 - 2. °C = degree Celsius
 - 3. ND = Not Detected

Photo Appendix



*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sos.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sos.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document is enpoduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.