

Heat Transfer Vinyl Guide

Uniquely Whynot HTV

Type	Temperature ¹	Pressure	Press Time	Peel	Cricut Settings ²	Mat Grip
Premium PU ³	285°F / 140°C	Medium	4s	Hot	Everyday Iron-On	Standard
Mirror	302°F / 150°C	Medium	12s	Warm	Glitter Iron-On	Standard
Reflective	285°F / 140°C	Medium	12s	Warm	Glitter Iron-On	Strong
Glitter / Sandy Glitter	302°F / 150°C	Medium	10s	Hot	Glitter Iron-On	Standard

TeckWrap™ HTV

Type	Temperature ¹	Pressure	Press Time	Peel	Cricut Settings ²	Mat Grip
Buffalo Plaid Pattern	285°F / 140°C	Medium	12s	Warm	Everyday Iron-On	Standard
Chameleon	285°F / 140°C	Medium	12s	Cool	Everyday Iron-On	Standard
Colour Changing	285°F / 140°C	Medium	12s	Cool	Everyday Iron-On	Standard
Flock	320°F / 160°C	Medium	12s	Cool	Glitter Iron-On	Standard
Galaxy	285°F / 140°C	Medium	12s	Warm	Everyday Iron-On	Standard
Glitter	320°F / 160°C	Medium	10s	Cool	Holographic Iron-On	Strong
Glow In The Dark	285°F / 140°C	Medium	12s	Cool	Everyday Iron-On More Pressure	Strong
Holographic	285°F / 140°C	Medium	12s	Cool	Holographic Iron-On	Standard
Marble PU	285°F / 140°C	Medium	12s	Warm	Everyday Iron-On	Standard
Metallic	285°F / 140°C	Medium	12s	Warm	Glitter Iron-On	Standard
Metallic PU	285°F / 140°C	Medium	12s	Warm	Everyday Iron-On	Standard
Opal	285°F / 140°C	Medium	12s	Cold ⁴	Glitter Iron-On	Standard
Puff	295°F / 146°C	Medium - High	18s	Hot	Everyday Iron-On	Strong
Rainbow Stripes PU	285°F / 140°C	Medium	12s	Warm	Everyday Iron-On	Standard
UV Colour Changing	285°F / 140°C	Medium	12s	Cool	Everyday Iron-On	Standard

It is always advisable to do a small test cut and press before beginning your project to prevent wasting materials. These settings are meant to be a guide in helping you find the best setting for your machine.

HTV is cut with the shiny side placed down on the cutting mat and your design mirrored.

WASHING: Wait at least 24 hours to wash. Machine wash inside out on warm or cold water setting using a mild detergent. Do not use bleach or other harsh chemicals. Tumble dry on low setting or hang to dry.

Cricut Mini Press: For 285°F / 140°C use low setting, otherwise use medium setting for higher press temperatures.

Clothes Iron: Medium Setting (Polyester, Wool, Silk)

1. Heat press temperature accuracy may vary. It is recommended to do a test press to determine the best settings for your press.
2. Cricut settings are for the Maker, Maker 3, Explore Air 3 and the Explore Air 2 (Smart Set dial on Custom), using a sharp premium fine point blade.
3. Grey, Light Green, Navy Blue, Pink and Sky Blue require a temperature of 302°F / 150°C for 10s.
4. Cold peel otherwise wrinkling will occur around the edges.



uniquelywhynotcraft.ca

