



Product Description

Polyprime® FMB is a clear, two component, 100% solids, low odor, low viscosity epoxy primer that is specifically formulated as a moisture barrier coating to treat new and existing concrete floors with high moisture and high pH. Polyprime® FMB can be used as a one-coat moisture vapor barrier coating suitable for various types of concrete. The low viscosity formula not only promotes deeper concrete penetration for superior substrate adhesion, but also generates higher propensity for sealing and blocking moisture drive than standard epoxy flooring product.

Features

- 100% Solids, Low VOC, Low Odor
- Controlled Vapor Pressure up to 25lbs
- Excellent Concrete Adhesion
- Fast Drying Times
- Low Viscosity for Deeper Concrete Slab Penetration
- One-Coating Moisture Vapor Barrier
- Vapor Control for High Moisture and High pH Slabs

Typical Uses

- Animal Care Areas
- Excellent Moisture Blocker
- Institution Facilities
- Laboratories
- Loading Docks
- Manufacturing & Warehouse Floors
- Mechanical Rooms
- Multiple-Unit Housing
- Pharmaceutical Plants
- Retail Stores
- Shop Floors
- Underneath any Coatings Showing Concrete Contamination
- Underneath Various Floorings

Packaging

3-Gallon Kit	One 3.5 gallon pail, net fill 2 gallons (7.57 liters) of Side-A and One 1 gallon (3.78 liters) can of Side-B
15-Gallon Kit	Two 5 gallon (18.9 liters) pails of Side-A and One 5 gallon (18.9 liters) pail of Side-B

Color

Clear

Coverage

Approximately 100 sqft/gallon @ 16 mils.

Surface Preparation

Technical Data (Based on Draw Down Film)

Components	2 Side
Visual Appearance	High Gloss
Density	9.0 lb/gal
VOC Content	<5g/l
Pot Life @ 70°F (21°C), 50% RH	10-15 Minutes
Equipment	Brush, Roller, & Flat Rubber Squeegee
Number of Coats	1 @ 16 mils
Theoretical Coverage	100 ft ² /gal 16 mils WFT
Dry to Touch @ 70°F (21°C), 50% RH	3-4 Hours
Life Traffic	N/A
Full Cure	N/A
Recoat Time @ 70°F (21°C)	12 to 24 Hours
Min. Application Temp.	50°F

Mechanical Properties

Surface Prep Requirements	ICRI CSP-3, Primed
Adhesion, ASTM D7234	>400psi, Concrete Failure
Hardness, Konig (15 mils) ASTM D4366	100
Tensile Strength, ASTM D2370	7500 psi
Tensile Elongation, ASTM D2370	1.5%
Compression, ASTM D695	10,000 psi
Hardness (Shore D), ASTM D2240	75-85
Water Absorption, ASTM D570	<0.1%
Flame Test, ASTM D648	Class 1
Abraision Resistance, ASTM D4060	30 mg loss
Coefficient of Friction, ASTM D2047	0.7 Smooth
Impact Resistance, ASTM D2794	160 in/lb

Chemical Data @ 70°F (21°C)

pH	4 to 13
Inorganic Acids	Good
Organic Acids	Good
Alkali	Excellent
Solvents	Good

Note: Although testing is critical, it is not a guarantee against future problems. This is especially true if there is no vapor barrier or the vapor barrier is not functioning properly and/or you suspect you may have concrete contamination from oils, chemical spills or excessive salts

CHECK THE CONCRETE

Concrete must be structurally sound and free of curing membrane, paint or other sealer. If you suspect that the concrete has been previously sealed, call Polycoat Products technical support for further instructions.

CHECK FOR MOISTURE

Concrete must be dry before application of this floor coating material. Concrete moisture testing must occur. Calcium chloride testing or "In-situ" relative humidity testing is recommended. Test methods can be purchased at www.astm.org, see ASTM F1869-11 or F2170-11, respectively or follow manufacturer's instructions. Readings must be below the defined threshold as specified for each Polycoat Products system to be installed directly to the concrete substrate. Please refer to the appropriate Technical Data Sheet for this information.

CHECK THE TEMPERATURE & HUMIDITY

Floor temperature and materials should be between 65°F (18°C) and 90°F (32°C). Humidity must be less than 95%. DO NOT coat unless floor temperature is more than (5°F) over the dew point.

SURFACED PREPARATION

Requires ICRI CSP 3

This product requires proper surface profile to perform as expected. Substrate must be mechanically profiled (ASTM 4259-83), clean, sound, and dry.

Mixing

The temperature of the (A) and (B) portions should be between 70°F and 80°F (20°-25°C). Mix them separately to ensure a uniform consistency. For a 3 gallon kit add (Side-B) into (Side-A) in a 3.5 gallon bucket. Mix contents thoroughly until all components are completely incorporated and no streaking is observed. Thinning is not recommended. The portions of each side is accurately measured to ensure optimum product performance. Pouring from one container to the other (boxing) during mixing is very helpful in ensuring complete mixing. Mix for 2 minutes.

Application

APPLICATION EQUIPMENT

Tools: 3" Disposable brush, low speed drill (450 rpm) with a 3.5" Jiffiler blade, 3/8" nap non-shedding phenolic core roller, and flat rubber squeegee.

ROLL ON

After mixing all contents as instructed, immediately pour out into a ribbon on the surface. Squeegee the material out evenly and check for desired film thickness by using a wet-film thickness gauge. Back-rolling and then cross rolling is critical. Allow to dry minimum of 12 hours before recoat.

Limited Warranty: Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and preferably applied by professionals who have prior experience with the Polycoat Products materials or have undergone training in application of Polycoat Products materials. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data, instructions, and project specific recommendations.

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products' current published physical properties. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

Disclaimer: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests accurately represent all environments. Polycoat Products is not responsible for typographical errors. © 2020 Polycoat Products. All rights reserved. Revision 20200915.DM

Storage

This product has a maximum shelf life of one year when stored off the ground in a dry area at 50° to 110°F, in the original sealed container.

Clean-Up

Clean-up mixing station, tools and application equipment immediately after completion. Use suitable solvent as specified by Polycoat Products' Technical Services Team or if permissible by law, xylene, as a general over-the-counter solvent. Observe all fire hazards, legal, and health and safety precautions when handling or storing solvents, particularly in confined spaces. Make sure the working area is well ventilated at all times during application and curing times. Dispose all excess materials, packaging, and other waste in accordance with federal, state, and local regulations.

Maintenance

Occasionally inspect the installed floor by spot cleaning and spot repairing any damaged or cracked areas. To prolong the life of the flooring system, a daily cleaning maintenance program is highly recommended to ensure the floor is safe for its intended purpose.

First Aid

Warning! Eye and skin irritant. May cause dermatitis and sensitization. In case of contact: Avoid contact with eyes, skin or clothing. Avoid breathing vapor, mist or spray. Use with good ventilation.

Eyes: Immediately flush with water for at least 15 minutes.
Skin: Immediately remove from skin with dry cloth followed by thorough washing with soap and water.

Inhalation: Remove to fresh air. If breathing is difficult, give oxygen.

Ingestion: Immediately call a Poison Center/Doctor. Do NOT induce vomiting. If vomiting occurs naturally, lie on your side, in the recovery position.

Limitations

This product is best suited for application in temperatures between 60°F and 90°F. Do not use to grout coat over aggregate. [Certain colors appear white when scratched such as blue based.] Higher temperatures will result in faster dry times and/or poor workability. Color may vary due to batch-to-batch variation, especially in higher temperature. Do not apply over ponding water. Always read and understand the specific product data guide and SDS sheets before using this product. For more information contact Polycoat Products.

USE PRODUCT AS DIRECTED. KEEP OUT OF THE REACH OF CHILDREN.