

<u>Test R</u>	<u>eport</u>			Number:	SHAH01238506S1
Applicant:	16732 Šep	, CA 91343		Date:	Jul 21, 2020
Item Name Style Labelled Age Packaging Pro Buyer Goods Export Country Of Or	s of submitte Group ovided By A ed To igin	oplicant : : : : : : : : : :	Plunder: A Pirate's Life. 1 style. 10+ Yes. Lost Boy Entertainment LLC. EU. China.	****	****
Conclusion: <u>Tested Sample</u> Submitted Sam Tested compor	nple set	EN71-2: 2011+A1:	1: 2018 for Mechanical And Phys 2014 Flammability Test nigration of certain elements	ical Properties	<u>Result</u> Pass Pass Pass
submitted sam	ple	EN 71-3: 2019 on i amending 2009/48 migration	migration of certain elements & E B/EC (effective from May, 20,202	1) for Aluminiur	Pass n (Al)

Authorized By: For Intertek Testing Services Ltd., Shanghai

Bill Zhang General Manager



Page 1 of 10

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司 Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





Tests Conducted

## 1 Mechanical and Physical Test

As Per European Standard on Safety of Toys EN71-1: 2014+ A1: 2018.

Applicant's Specified Age Group for Testing: For ages 10 years and up

Clause	Testing Items	Assessment
4	General Requirements	•
4.1	Material	Р
4.2	Assembly	NA
4.3	Flexible plastic sheeting	NA
4.4	Toy bags	NA
4.5	Glass	NA
4.6	Expanding materials	NA
4.7	Edges	Р
4.8	Points and metallic wires	Р
4.9	Protruding parts	NA
4.10	Parts moving against each other	NA
4.11	Mouth actuated toys and other toys intended to be put in the mouth	NA
4.12	Balloons	NA
4.13	Cords of toy kites and other flying toys	NA
4.14	Enclosures	NA
4.15	Toys intended to bear the mass of a child	NA
4.16	Heavy immobile toys	NA
4.17	Projectile toys	NA
4.18	Aquatic toys and inflatable toys	NA
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	NA
4.20	Acoustics	NA
4.21	Toys containing a non-electrical heat source	NA
4.22	Small balls	NA
4.23	Magnets	NA
4.24	Yo-yo balls	NA
4.25	Toys attached to food	NA
4.26	Toy disguise costumes	NA
4.27	Flying toys	NA
5	Toys intended for Children under 36 Months	
5.1	General requirements	NA
5.2	Soft-filled toys and soft-filled parts of a toy	NA
5.3	Plastic sheeting	NA
5.4	Cords, chains and electrical cables in toys	NA
5.5	Liquid filled toys	NA
5.6	Speed limitation of electrically-driven ride-on toys	NA

Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233 Tel: +86 21 6120 6060 Fax: +86 21 6127 9708 www.intertek.com www.intertek.com.cn

SHAH01238506S1

Number:

Page 2 of 10



intertek	
Total Quality. Assured.	

Number: SHAH01238506S1

<u>Clause</u>	Testing Items	Assessment
5.7	Glass and porcelain	NA
5.8	Shape and size of certain toys	NA
5.9	Toys comprising monofilament fibres	NA
5.10	Small balls	NA
5.11	Play figures	NA
5.12	Hemispheric-shaped toys	NA
5.13	Suction cups	NA
5.14	Straps intended to be worn fully or partially around the neck	NA
5.15	Sledges with cords for pulling	NA
6	Packaging	Р
7	Warnings, markings and instructions for use	
7.1	General	Р
7.2	Toys not intended for children under 36 months	NA
7.3	Latex balloons	NA
7.4	Aquatic toys	NA
7.5	Functional toys	NA
7.6	Hazardous sharp functional edges and points	NA
7.7	Projectile toys	NA
7.8	Imitation protective masks and helmets	NA
7.9	Toy kites	NA
7.10	Roller skates, inline skates and skateboards and certain other ride-on toys	NA
7.11	Toys intended to be strung across a cradle, cot, or perambulator	NA
7.12	Liquid-filled teethers	NA
7.13	Percussion caps specifically designed for use in toys	NA
7.14	Acoustics	NA
7.15	Toy bicycles	NA
7.16	Toys intended to bear the mass of a child	NA
7.17	Toys comprising monofilament fibres	NA
7.18	Toy scooters	NA
7.19	Rocking horses and similar toys	NA
7.20	Magnetic/electrical experimental sets	NA
7.21	Toys with electrical cables exceeding 300 mm in length	NA
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	NA
7.23	Toys intended to be attached to a cradle, cot or perambulator	NA
7.24	Sledges with cords for pulling	NA
7.25	Flying toys	NA
7.26	Improvised projectiles	NA

To be continued

Page 3 of 10

Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





Test Report Number: SHAH01238506S1

**Tests Conducted** 

Remark: P = Pass

NA = Not Applicable

Remark: Additional information according to the Toy Safety Directives 2009/48/EC requirement. These information also appears as a note within the EN71 but are not standard requirements: 1. Marking

The manufacturer's and importer's name, registered trade name or registered trade mark, the address and the CE-marking shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompany the toy. In addition, manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.

- Manufacturer's name and address was on the packaging only.

- Importer's name and address was missed.

- Product identification code was on the packaging only.

- CE-marking was on the packaging.

Date Sample Received: Jul.8, 2020 Testing Period: Jul.8, 2020 to Jul.13, 2020

## 2 Flammability Test

As per European Standard on Safety of Toys EN71-2: 2011+A1: 2014

Clause	Testing Items		Assessment
4.1	General		Р
4.2	Toys to be worn on the head		
4.2.2	Beards, moustaches, wigs, etc., made from ha features, which protrude 50 mm or more from t	•	NA
4.2.3	Beards, moustaches, wigs, etc., made from ha features, which protrude less than 50 mm from		NA
4.2.4	Full or partial moulded head masks		NA
4.2.5	Flowing elements of toys to be worn on the hea	ad	NA
4.3	Toy Disguise Costumes and Toys Intended to	be Worn by a Child in Play	NA
4.4	Toys Intended to be Entered by a Child		NA
4.5	Soft Filled Toys		NA
Remark :	P = Pass	NA = Not Applicable	

Date Sample Received: Jul.8, 2020

Testing Period: Jul.8, 2020 to Jul.13, 2020

To be continued

Page 4 of 10

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司 Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





# Tests Conducted

# Number: SHAH01238506S1

#### 3 19 Toxic Elements Migration Test

## (A) Test Result

As per EN 71-3:2019 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, and Gas Chromatographic - Mass Spectrometry.

#### Category (III): Scraped-off toy material

<u>Element</u>		Result (m	ng/kg)		Limit (mg/kg)
	(1)	(2)#	(3)	(4)	
Aluminium (Al)	< 300	727	< 300	< 300	70000/28130©
Antimony (Sb)	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	17	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) **	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) **	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	33	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	180000
Organic tin **	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	46000
***************************************	*****	**********************	*******	******	*********

To be continued

Page 5 of 10



Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233



**Tests Conducted** 

SHAH01238506S1

Element		Result (n	<u>ng/kg)</u>		Limit (mg/kg)
	(5)#	(6)	(7)	(8)#	
Aluminium (Al)	< 300	< 300	< 300	< 300	70000/28130©
Antimony (Sb)	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) **	< 10	< 10	< 10	< 10	460
Chromium (VÍ) (Cr VÍ) **	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	180000
Organic tin <sup>++</sup>	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	46000
<u>Element</u>		<u>Result (n</u>			<u>Limit (mg/kg)</u>
	(9)	(10)	(11)	(12)	
<u>Element</u> Aluminium (Al)	(9) < 300			(12) < 300	<u>Limit (mg/kg)</u> 70000/28130©
Aluminium (AI)		(10)	(11)		
	< 300	(10) < 300	(11) < 300	< 300	70000/28130©
Aluminium (Al) Antimony (Sb)	< 300 < 10	(10) < 300 < 10	(11) < 300 < 10	< 300 < 10	70000/28130© 560
Aluminium (AI) Antimony (Sb) Arsenic (As)	< 300 < 10 < 10	(10) < 300 < 10 < 10	(11) < 300 < 10 < 10	< 300 < 10 < 10	70000/28130© 560 47
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba)	< 300 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 10	70000/28130© 560 47 18750
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup>	< 300 < 10 < 10 < 10 < 50	(10) < 300 < 10 < 10 < 10 < 50	(11) < 300 < 10 < 10 < 10 < 50	< 300 < 10 < 10 < 10 < 50	70000/28130© 560 47 18750 15000
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup>	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025	(10) < 300 < 10 < 10 < 10 < 50 < 5 < 10 < 0.025	(11) < 300 < 10 < 10 < 10 < 50 < 5 < 10 < 0.025	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025	70000/28130 © 560 47 18750 15000 17 460 0.053
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup>	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700 23
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700 23
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700 23 15000
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn) Mercury (Hg)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10	70000/28130 © 560 47 18750 15000 17 460 0.053 130 7700 23 15000 94
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn) Mercury (Hg) Nickel (Ni) Selenium (Se) Strontium (Sr)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	$\begin{array}{c} 70000/28130 \circledcirc \\ 560 \\ 47 \\ 18750 \\ 15000 \\ 17 \\ 460 \\ 0.053 \\ 130 \\ 7700 \\ 23 \\ 15000 \\ 94 \\ 930 \\ 460 \\ 56000 \end{array}$
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn) Mercury (Hg) Nickel (Ni) Selenium (Se) Strontium (Sr) Tin (Sn)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	$\begin{array}{c} 70000/28130 \circledcirc \\ 560 \\ 47 \\ 18750 \\ 15000 \\ 17 \\ 460 \\ 0.053 \\ 130 \\ 7700 \\ 23 \\ 15000 \\ 94 \\ 930 \\ 460 \\ 56000 \\ 180000 \end{array}$
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn) Mercury (Hg) Nickel (Ni) Selenium (Se) Strontium (Sr)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	$\begin{array}{c} 70000/28130 \circledcirc \\ 560 \\ 47 \\ 18750 \\ 15000 \\ 17 \\ 460 \\ 0.053 \\ 130 \\ 7700 \\ 23 \\ 15000 \\ 94 \\ 930 \\ 460 \\ 56000 \\ 180000 \\ 12 \end{array}$
Aluminium (AI) Antimony (Sb) Arsenic (As) Barium (Ba) Boron (B) Cadmium (Cd) Chromium (III) (Cr III) <sup>++</sup> Chromium (VI) (Cr VI) <sup>++</sup> Cobalt (Co) Copper (Cu) Lead (Pb) Manganese (Mn) Mercury (Hg) Nickel (Ni) Selenium (Se) Strontium (Sr) Tin (Sn)	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(10) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	(11) < 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	< 300 < 10 < 10 < 50 < 5 < 10 < 0.025 < 10 < 10 < 10 < 10 < 10 < 10 < 10 < 10	$\begin{array}{c} 70000/28130 \circledcirc \\ 560 \\ 47 \\ 18750 \\ 15000 \\ 17 \\ 460 \\ 0.053 \\ 130 \\ 7700 \\ 23 \\ 15000 \\ 94 \\ 930 \\ 460 \\ 56000 \\ 180000 \end{array}$

To be continued



(in)

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司 Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233



**Tests Conducted** 

SHAH01238506S1

Element		<u>Limit (mg/kg)</u>			
	(16)	(17)	(18)	(19)	
Aluminium (Al)	< 300	< 300	< 300	< 300	70000/28130©
Antimony (Sb)	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) **	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	180000
Organic tin <sup>++</sup>	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	46000

Remark: mg/kg = Milligram per kilogram

++ = Unless the test results were marked with "#" or "△", Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.

- Organic tin test result was expressed as tributyl tin.
- © = The new Aluminium (AI) migration limit [2250mg/kg for Category (I), 560mg/kg for Category (II), 28130mg/kg for Category (III)] was quoted from directive (EU) 2019/1922 amending 2009/48/EC effective from 20 May 2021.
- # = Confirmation of Chromium (VI) test was performed on the tested component. And the reported value of migration of Chromium (III) = migration value of total Chromium - migration value of Chromium(VI).
- @ = Since the sample weight of the components (13) To (15) were less than 10 mg, soluble heavy metal analysis was not applicable.

The results only apply to the items tested.

Tested Component(s): See component list in the last section of this report.

To be continued

Page 7	of 10
1	7

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司

Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





**Tests Conducted** 

Number: SHAH01238506S1

#### (B) Categories of various toy materials

Category I: Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II: Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III: Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).

Date Sample Received: Jul.8, 2020

Testing Period: Jul.8, 2020 to Jul.13, 2020

To be continued



Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233 Tel: +86 21 6120 6060 Fax: +86 21 6127 9708 www.intertek.com www.intertek.com.cn



Page 8 of 10



**Tests Conducted** 

Number: SHAH01238506S1



To be continued

Page 9 of 10

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司 Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





**Tests Conducted** 

Components List:

- White paper with four-color printed coatings. (instruction) (1)
- (2)Brown paper board with transparent plastic film and underlying coatings. (chess board)
- (3) Red soft plastic. (boat)
- (4) Deep yellow soft plastic. (boat)
- (5) Purple soft plastic. (boat)
- Green soft plastic. (boat) (6)
- (7)Brown soft plastic. (boat)
- Black soft plastic. (boat) (8)
- (9) Black plastic. (pointer)
- (10)Grey soft plastic. (canvas)
- (11)Red soft plastic. (people)
- (12)Dark grey soft plastic. (weapon)
- (13)Black coating on plastic. (on dice)
- (14)Dark beige coating on plastic. (on dice)
- (15)Red coating on plastic. (on dice)
- (16)Red plastic excluding coating. (dice)
- Brown plastic excluding coating. (dice) (17)
- Greyish black plastic excluding coating. (dice) (18)
- Dark beige plastic. (pane) (19)

End of report

SHAH01238506S1

Number:

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.

This statement of conformity is only based on the actual measured test result by the laboratory, without taking the influence of uncertainty into accord.

Page 10 of 10

Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司

Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233





To:Lost Boy Entertainment LLCAttention:KC Schrimpl

Date: Jul

Jul 21, 2020

Re: Report Revision Notification

# Intertek Testing Services Report Number SHAH01238506 Dated 14 Jul, 2020 .

Please be informed that all the content recorded in the above captioned report will be void. This captioned report is now superseded by a revised Intertek Testing Services Report Number **SHAH01238506S1**.

Reason for report revision: Update the name and address of the client.

Thank you for your attention.

Authorized By: For Intertek Testing Services Ltd., Shanghai

Bill Zhang General Manager



Intertek Testing Services Ltd., Shanghai 上海天祥质量技术服务有限公司 Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233 上海市宜山路 801 号金陵商务广场 B 座 200233

