

# KPNOX 27



## DECONTAMINATION AND PASSIVATION GEL FOR STAINLESS STEEL SURFACE

Made in / Fabriqué au Canada 🍁

**Freshly pickled stainless steel can easily be contaminated by particles of metallic dust present in the workplace. KPNOX<sup>27</sup> removes rust and contamination from stainless steel SURFACE. It eliminates all traces of corrosion discoloration, rust, grease, lime and biofouling without impairing the original finish.**

### DIRECTIONS

Apply a uniform layer of KPNOX<sup>27</sup> gel using a non-metallic brush OR spray surface using stainless steel paint gun. KPNOX<sup>27</sup> gel covers approximately 30 sq. ft. per kg. Let stand 5-15 minutes.

Rinse using high-pressure water jet.

### STORAGE AND HANDLING

Store in a cool, well-ventilated area. Keep away from heat, sparks and flames. Keep away from caustic solutions and alkaline reducing agents. Keep containers well closed. Fast-opening packaging compliant with UN standards.

### NEUTRALIZATION METHOD

Residues and contaminated water must be neutralized to pH6-8. Heavy metals released in the cleaning of stainless steel must be disposed of, along with residues and neutralized solutions, in facilities authorized to treat hazardous waste in compliance with applicable regulations.

## TO ORDER

| PRODUCT CODE | FORMAT | CURRENT PRICE |
|--------------|--------|---------------|
| KP2702G-1G   | 4 L    |               |
| KP2702G-20G  | 20L    |               |

### PRECAUTIONS

Wear rubber boots, impervious gloves, a plastic apron and protective glasses. Avoid all contact with skin. Keep away from sources of ignition. Handle in a well-ventilated area or wear a suitable breathing apparatus. Use non-metallic tools.

### FIRST AID

In case of discomfort, move to well-ventilated area. If a person has stopped breathing, administer artificial respiration and get medical attention. In case of contact with eyes, flush thoroughly with water and get medical attention. See Safety Data Sheet.

Pour plus d'informations sur nos produits et nos solutions personnalisées, ou pour une démonstration gratuite, contactez-nous !

T. 1-514-333-0754      E. [info@gkemplus.com](mailto:info@gkemplus.com)  
F. 1-514-333-5780      W. [gkemplus.com](http://gkemplus.com)

6020, Vanden Abeele, Saint-Laurent, Québec, Canada H4S 1R9