



Sales & Engineering:
5607 Palmyra Road, PO Box 348
Pittsford, NY 14534-9998, USA
Phone: 877-486-5595

Manufacturing:
219 Hope Rd
Smithfield, PA 15478 USA

Product Data Sheet

Grade: VC-BMC-1025

Characteristics	Typical Properties Metric Units
Density	1.90 g/cc
Specific Resistance (In-plane)	20 $\mu\Omega$ m
Specific Resistance (Thru-plane)	10 $\mu\Omega$ m
Electrical Conductivity (In-plane)	50 S/cm
Electrical Conductivity (Thru-plane)	100 S/cm
Flexural Strength	40 MPa
Elastic Modulus	11 GPa
Compressive Strength	75 MPa
Thermal Conductivity (In-plane)	46.2 W/mK
Thermal Conductivity (Thru-plane)	19.2 W/mK
C.T.E.	30 ppm/°C
Leak Test	<0.10% - 24hrs/23°C
Max Work Temp	190 °C

Carbon is our specialty