

TECHNICAL SPECIFICATIONS

Polyester and polyester blends for seating in residential, hospitality, and office complexes.

PERFORMANCE PROPERTIES



MOISTURE REPELLENCY

- Spray Rating of 80-100 (AATCC Test Method 22-2010)



STAIN RESISTANCE

- Class 4-5 (AATCC Test Method 130-2010 modified)*
- Ease of cleaning utilizing various cleaning products

* Common household stains such as wine, coffee, ketchup, chocolate syrup, etc.

* For most products

For a complete listing, please contact us at livesmartbyculp.com/contact

FABRIC TYPES

- **WOVEN TEXTURES**
Plain, Satin, Jacquard, Dobby
- **KNITS**
- **WOVEN VELVETS**
- **PRINTED**

Environmental Impact

- Does not contain PFOS (perfluorooctane sulfonate) or PFOA (perfluorooctanoic acid)
- No Proposition 65 chemicals present
- No REACH listed chemicals (Substances of Very High Concern)
- No EPA regulated Section 313 chemicals present
- Low VOC's (Volatile Organic Compounds)
- No formaldehyde, phthalates, heavy metals, bishphenol BPA, or dioxin
- No Halogenated Flame Retardants (i.e. PBDEs)
- PVC free

Physical Property Performance

FLAMMABILITY	TB 117-2013 Pass, UFAC Class 1
SEAM SLIPPAGE	ASTM D4034- 25 lbs. minimum
SEAM BREAKING STRENGTH	ASTM D4034- 50 lbs. minimum
TENSILE STRENGTH	ASTM D5034- 50 lbs. minimum
TEAR STRENGTH	ASTM D2261- 6 lbs. minimum
ABRASION	ASTM D4157 modified- Heavy Duty 15,000 double rubs*
COLORFASTNESS TO CROCKING	AATCC 8, Dry - Class 4 minimum, Wet - Class 3 minimum
COLORFASTNESS TO LIGHT	AATCC 16- Class 4 @ 40 hours exposure